

by Wickman (1948) who assumed that Harcourt (1942) really was dealing with a member of the tetrahedrite family.

REFERENCES

- DONNAY, J. D. H. AND W. NOWACKI (1954) *Crystal Data*, p. 554.
 HARCOURT, G. A. (1942) *Am. Mineral.* **27**, 63-113.
 ROSI, F. D. *et al.* (1961) RCA Progress Report #8, Contract No. NOBS 77057, p. 11.
 WERNICK, J. H., S. GELLER AND K. E. BENSON (1958) *Jour. Phys. Chem. Solids* **7**, 247.
 WICKMAN, F. E. (1948) *Am. Mineral.* **33**, 262.


THE AMERICAN MINERALOGIST, VOL. 50, JANUARY-FEBRUARY, 1965

SYNTHESIS AND PROPERTIES OF CALCIUM
 VANADIUM GARNET (GOLDMANITE)

R. G. J. STRENS, *Department of Geology and Geophysics,
 University of California, Berkeley, California.*

In the course of a study of garnets containing trivalent ions of the first transition series, $\text{Ca}_3\text{V}_2\text{Si}_3\text{O}_{12}$ was prepared hydrothermally at 530° and 3.0 kilobars, in a 30-day run at the oxygen partial pressure of the hematite-magnetite buffer. The starting material was glass with a Ca:V ratio of 3:2, but with excess silica to suppress the substitution of $(\text{OH})_4^{4-}$ for SiO_4^{4-} . Garnet was obtained in theoretical yield, as a dark green equigranular powder, with n 1.834 ± 0.003 , a 12.070 ± 0.005 , and D_{calc} 3.765.

Moench and Meyrowitz (1964) have recently described a natural vanadium garnet, containing 60% of the Ca-V end-member, for which they have proposed the name *goldmanite*. Their analysis gives the formula:



with n 1.821 ± 0.001 , a 12.011, and D_{calc} 3.737. Applying corrections for the content of Mg, Mn, and Fe with the aid of Skinner's (1956) data for the garnet end-members, the writer calculates n 1.836 and a 12.086 for the Ca-V end-member, in reasonable agreement with the values found above.

REFERENCES

- MOENCH, R. H. AND R. MEYROWITZ (1964) Goldmanite, a vanadium garnet from Laguna, New Mexico. *Am. Mineral.* **49**, 644-655.
 SKINNER, B. J. (1956) Physical properties of end-members of the garnet group. *Am. Mineral.* **41**, 428-436.