

MINERALOGICAL NOTES

The Unit Cell of Volborthite

ERIK S. LEONARDBSEN
Institute of Mineralogy,

OLE V. PETERSEN
Mineralogical Museum,

University of Copenhagen, Denmark

Abstract

Indexed powder diagrams of volborthite, $\text{Cu}_3(\text{VO}_4)_2 \cdot 3\text{H}_2\text{O}$, from Monument Valley, Arizona, disclose it to be monoclinic (space group $C2$, Cm , or $C2/m$), the unit cell [$a = 10.604(2)$, $b = 5.879(1)$, $c = 7.202(2)$ Å, $\beta = 94.81(2)^\circ$] containing two formula units. Calculated density, 3.52 g/cm^3 , compares with 3.42 g/cm^3 , the value measured by Guillemin (1956).

Introduction

In the Mineralogical Museum, Copenhagen, Guinier-Hägg powder diffraction exposures have formed part of the routine examination of newly acquired mineral specimens since 1971. Such an examination of volborthite from Monument No. 1 Mine, Monument Valley, Navajo County, Arizona, permitted indexing of the pattern and thus, for the first time, determination of its unit cell. The specimen (M.M. No. 1972.307), according to Witkind (1961), originates from the outermost zone of oxidized minerals of the ore body, the mineral assemblage of which includes carnotite, hewettite, metatyuyamunite, rauvite, tyuyamunite, and volborthite. The specimen consists of a light gray siltstone matrix profusely covered on one side with olive green to citron yellowish-green microcrystalline globules of volborthite, some of which are themselves partly covered with numerous small crystals.

X-Ray Diffraction Data

Guillemin (1956) published an unindexed powder pattern of volborthite, which is reproduced by Joint Committee of Powder Diffraction Standards, card no. 12-523. No other diffraction data were found.

Our pattern is in excellent agreement with this standard, except for some splitting up of the lines due to the Guinier-technique. The pattern was readily indexed by the method of Ito (1950). Least squares refinement gave the following unit cell dimensions: $a_0 = 10.604 \pm 0.002$ Å, $b_0 = 5.879 \pm 0.001$ Å, $c_0 = 7.202 \pm 0.002$ Å, and $\beta = 94.81 \pm 0.02^\circ$.

¹Numbers in parentheses represent estimated standard deviation in respect to the last decimal cited. (See *Am. Mineral.* 59, 223.

TABLE I. X-Ray Diffraction Data for Volborthite

JCPDS, card no. 12-523		Present investigation ^{xx}					
Int.	d (Å)	Int.	d _{obs.} Å	10 ⁴ Q _{obs.} (Å ⁻²)	10 ⁴ Q _{calc.} (Å ⁻²)	hkl	
100	7.26	10	7.16	195.0	194.2	001	
			5.291	357.2	358.2	200	
20	5.21	3	5.136	379.1	378.9	110	
			4.426	510.3	508.1	201	
10	4.19 ^x	4			550.9	111	
10	4.03	5	4.103	594.1	595.2	111	
					596.6	201	
10	3.56	1	3.583	779.0	776.6	002	
30	3.08	5	3.090	1047.1	1046.3	202	
			4	3.022	1074.9	1095.4	310
40	2.98	5	2.998	1112.4	1111.2	112	
			1	2.940	1157.3	1157.3	020
80	2.87	5	2.887	1199.8	1199.8	112	
			5	2.859	1223.5	1223.4	311
					1351.4	1351.4	021
20	2.71	5	2.722	1349.7	1355.9	311	
20	2.64	7	2.643	1432.1	1432.9	400	
80	2.56	7	2.571	1513.3	1515.5	220	
			5	2.551	1537.2	1538.6	401
					1665.4	221	
					1715.6	401	
					1739.2	312	
					1747.4	003	
80	2.38	7	2.389	1752.2	1753.9	221	
					1933.9	022	
					1972.9	203	
					2004.7	312	
30	2.21	1	2.216	2036.3	2032.5	402	
					2059.9	113	
					2192.7	113	
10	2.12 ^x				2203.6	222	
					2238.4	203	
30	2.04	4	2.049	2381.9	2380.7	222	
					2386.6	402	
					2528.3	510	
					2590.2	420	
					2611.8	511	
					2643.6	313	
					2693.4	130	
					2695.9	421	
		1	1.9247	2699.3	2833.1	511	
		1	1.8688	2863.3	2865.5	131	
					2872.9	421	
					2904.7	023	
					2909.7	131	
10	1.85	1	1.8521	2915.1	2914.8	403	
					3041.9	313	
					3083.6	512	
					3105.0	004	
30	1.78	2	1.8021	3079.2	3130.2	223	
			1	1.7946	3129.2	3130.2	223
			3	1.7876	3129.2	3130.2	223
				1.7703	3191.0	3189.8	422
					3224.1	600	
					3283.5	601	
					3287.7	205	
					3395.7	223	
		3	1.7170	3392.2	3396.9	114	
					3409.9	330	
30	1.71	2	1.7081	3427.7	3425.8	132	
					3445.9	403	
					3514.3	132	
30	1.67		1.6838	3527.1	3526.2	512	
					3537.7	331	
					3543.9	422	

^x Lines in position of strong quartz lines.

^{xx} Pattern obtained with Guinier Hägg focusing camera, radius 40.3 mm. $\text{CuK}\alpha_1$ ($\lambda = 1.54051$ Å) radiation, Ni-filter, and curved crystal monochromator. Internal standard quartz. Intensities visually estimated. All possible Q-values below $Q_{\text{calc}} = 3550.0$ have been calculated.

The systematic reflection condition led to the space-groups $C2$, Cm , or $C2/m$. Multiple indexed lines were omitted from the least squares refinement. The formula $Cu_3(VO_4)_2 \cdot 3H_2O$, unit cell volume = 447.42 \AA^3 , and $Z = 2$, gives the calculated density $D_x = 3.52 \text{ g/cm}^3$. Guillemin (1956) has measured the density as 3.42 g/cm^3 .

Acknowledgments

The authors wish to thank Mrs. G. Sjørring who typed the table.

References

- GUILLEMIN, C. (1956) Contribution à la Minéralogie des Arséniates Phosphates et Vanadates de Cuivre. *Bull. Soc. franc. Minéral. Cristallogr.* **79**, 219–275.
- ITO, T. (1950) *X-ray Studies on Polymorphism*. Tokyo, Maruzen.
- WITKIND, I. J. (1961) The uranium-vanadium ore deposit at the Monument No. 1—Mitten No. 2 Mine, Monument Valley, Navajo County, Arizona. *U.S. Geol. Surv. Bull.* **1107-C**.

Manuscript received, July 23, 1973; accepted for publication, October 30, 1973.