

New data on rasvumite and djerfisherite

GERALD K. CZAMANSKE, RICHARD C. ERD

U.S. Geological Survey, Menlo Park, California 94025

MAJA N. SOKOLOVA, MAJA G. DOBROVOL'SKAYA AND MARGRET T. DMITRIEVA

Academy of Sciences, Moscow, USSR

Abstract

Electron microprobe analyses and X-ray diffraction studies have shown the identity of rasvumite from a new occurrence at Coyote Peak, Humboldt County, California, and holotype material from the Khibina massif, Kola Peninsula, USSR. The electron microprobe analyses have established that the correct formula is KFe_2S_3 instead of $K_3Fe_9S_{14}$, as originally proposed. We compare new electron microprobe analyses of djerfisherite from the two localities and show that these djerfisherites do not contain magnesium.

Introduction

The occurrence at Coyote Peak, Humboldt County, California, of at least five unusual iron sulfide minerals containing essential potassium or sodium has led to a thorough review of the mineral chemistry of such phases. Although three new alkali-iron sulfide phases— $K_3Fe_{10}S_{14}$, $NaFe_3S_5 \cdot 2H_2O$, and $NaFeS_2 \cdot 2H_2O$ —have been found in the mafic alkalic diatreme at Coyote Peak (Czamanske *et al.*, 1977), in this report we describe the discovery there of two previously described minerals: rasvumite, KFe_2S_3 , and djerfisherite, $K_6Na(Fe,Cu,Ni)_{24}S_{26}Cl$.

The occurrence of rasvumite at Coyote Peak is only the second reported, after that in the Khibina massif in the USSR (Sokolova *et al.*, 1970). Djerfisherite is a more widely known potassium-bearing sulfide that has been found in meteorites (*e.g.*, Fuchs, 1966), Talnakh ore (Genkin *et al.*, 1969), alkalic rocks and pegmatites of the Khibina massif (Sokolova *et al.*, 1971), Tazheran skarns (Konev *et al.*, 1972), Yakutian kimberlites (Dobrovol'skaya *et al.*, 1975), and South African kimberlites (Clarke *et al.*, 1977). Our report, and the progress it represents in the understanding of these unusual minerals, has been made possible by the generous exchange of specimens, data, and ideas between the Russian and American coauthors.

Rasvumite

Rasvumite was named and first described from the Khibina massif, Kola Peninsula, USSR by Sokolova

et al. (1970). X-ray diffraction studies of the holotype rasvumite from Khibina and of the newly discovered material from Coyote Peak have established their identity. Rasvumite from Coyote Peak is orthorhombic, aspect C^*c^* ; $a = 9.035(1)$, $b = 11.022(1)$, $c = 5.426(1)A$, $V = 540.4(1)A^3$; cell contents, 4 KFe_2S_3 ; density = 3.035 g cm^{-3} (calc); specific gravity, 3.1(1) (meas). Study of Khibina and Coyote Peak minerals by electron microprobe under identical conditions has shown that rasvumite has the most constant composition of all known potassium-iron sulfide minerals and contains the least amount of other elements. Typical analyses are presented in Table 1.

An important conclusion of our study is that the correct formula for rasvumite is KFe_2S_3 . Because rasvumite alters readily in the supergene environment, we believe that the original wet-chemical analyses that led to the proposed formula $K_3Fe_9S_{14}$ were of altered material from which the potassium had been partly leached. Subsequent microprobe analyses of Khibina rasvumite (Dobrovol'skaya *et al.*, 1979) proved that the potassium content of rasvumite falls in the range of 14 to 16 weight percent K.

Table 2 presents X-ray powder-diffraction data for the Coyote Peak rasvumite; the observed pattern is essentially identical to that given by Sokolova *et al.* (1970) for the Khibina rasvumite. Note, however, that the lines reported at 2.01, 1.949, 1.857, and 1.799A for the rasvumite from Khibina do not appear in the pattern for this rasvumite from Coyote Peak. Khibina rasvumite is commonly intergrown

Table 1. Electron microprobe analyses of rasvumite (in weight percent)*

	Khibina		Coyote Peak		Ideal KFe ₂ S ₃
	Grn.1	Grn.2	CYP-9	CYP-133	
K	16.3	16.1 + 0.1** - 0.4	16.1	16.0	15.8
Fe	45.2	45.0 ± 0.2	44.8	46.5	45.2
S	38.0	37.8 + 1.2 - 0.2	37.3	38.6	38.9
Total***	99.5	98.9	98.2	101.1	99.9

* Analyses made at 10 and 15 kV on an ARL-EMX electron microprobe; standards used were natural biotite containing 8.3 wt% K and pure synthetic FeS. Data were corrected by the theoretical scheme FRAME (Yakowitz *et al.*, 1973). Continuing comparisons suggest that: (1) the use of a biotite and FRAME gives K contents for sulfides that are about 0.2 wt% high at the 10-wt% level, and (2) the use of pure FeS and FRAME gives S contents for K-Fe sulfides that are about 1.0 wt% low.

** Estimated limits of error for each analysis.

*** Cl, Cu, Mg, Na, and Ni have not been detected above the 0.01 wt% level, except that 0.06 wt% Na is indicated for sample CYP-9.

with djerfisherite and an unidentified copper-iron sulfide phase, so these four lines may be due to such impurities.

Djerfisherite

Typical analyses of Coyote Peak djerfisherite are compared in Table 3 to analyses obtained under identical conditions for Khibina djerfisherite and the "djerfisherite-like" compound synthesized at Argonne National Laboratory (Mrazek and Battles, 1977; Tani, 1977). The djerfisherite formula, K₂Na(Fe,Cu,Ni)₂₄S₂₆Cl, is based on structural studies and chemical data for djerfisherites from several known occurrences (Dmitrieva *et al.*, 1977).

Of special importance is the fact that the Khibina djerfisherite discussed by Sokolova *et al.* (1971) and Dmitrieva and Ilyukhin (1975) is now shown to be free of magnesium. Russian microprobe analyses have also failed to confirm the presence of magnesium in the Khibina djerfisherite, and it is presumed that the original wet-chemical analysis was on material contaminated with a magnesium-bearing silicate. Therefore, no natural djerfisherite analyzed to date contains magnesium.

Knowing that magnesium is not a constituent of djerfisherite, the senior author questioned the presence of 0.23 to 0.29 weight percent Li in the djerfisherite-like compound synthesized at Argonne National Laboratory. Evidence for lithium within the compound was considered desirable because: (1) the compound was synthesized in a LiCl-KCl melt, (2) Li₂FeS₂ and Li₂S are known products of the cell reac-

tion, and (3) the compound was analyzed in bulk. Ion microprobe analysis for lithium by I. M. Steele (written communication, 1978) has proved that lithium at about the reported level is, indeed, uniformly distributed within grains of djerfisherite-like phase.

The original structural determination for djerfisherite (Dmitrieva and Ilyukhin, 1975) was based on chemical data presented with the initial description of material from the Khibina occurrence (Sokolova *et al.*, 1971). According to these data, location of an

Table 2. X-ray powder-diffraction data for rasvumite from Coyote Park, Humboldt County, California

hkl	Calculated*		Observed**	
	d _{hkl} (Å)	d _{hkl} (Å)	I _a	I _b
110	6.988	6.98	62	60
020	5.511	5.513	100	60
200	4.518	4.521	2	---
111	4.286	---	---	---
021	3.867	---	---	---
220	3.494	3.492	17	15
130	3.403	3.403	43	30
221	2.938	2.935	12	100
310	2.905	2.905	12	5
131	2.883	2.882	3	---
040	2.756	---	---	---
002	2.713	2.707	2	---
311	2.561	2.560	1	---
112	2.529	2.529	5	10
041	2.457	---	---	---
022	2.434	2.435	1	15
240	2.352	2.352	2	---
330	2.329	2.329	12	20
202	2.326	---	---	---
150	2.142	2.141	1	---
331	2.140	---	---	---
420	2.090	2.091	6	10
151	1.992	---	---	---
312	1.983	1.983	2	30
060	1.837	1.837	6	5
350	1.779	1.778	14	30
440	1.747	1.747	12	30
530	1.622	1.622	1	---
170	1.551	1.552	2	---
600	1.506	1.506	1	---
080	1.378	1.378	3	---
710	1.282	1.282	2	---

* All calculated hkl's listed for d_{hkl} ≥ 2.300Å; all d_{hkl}'s are indexed. Indices are from least-squares analysis of X-ray powder diffraction data, using the digital computer program of Appleman and Evans (1973).

** Sample 77-CYP-9. X-ray diffractometer conditions are: chart X-4292; Cu/Ni radiation, λCuK_{α1} = 1.540598Å; Si internal standard; scanned at 1/8°min⁻¹ from 12 to 80°(2θ). I_a = intensities in diffractometer trace; I_b = visual estimate of intensities in Film 861 (Debye-Scherrer photograph).

Table 3. Electron microprobe analyses of djerfisherite (in weight percent)*

	Khibina	Coyote Peak		Argonne
		CYP-133	CYP-134	DS-11 & RD21-22
K	9.60 ±0.15**	9.45	9.00	9.90
Na	0.70 ±0.05	0.10	0.76	0.00
Mg	0.00	<0.05	<0.05	0.00
Cu	14.0 ±0.2	9.69	8.37	0.00
Ni	0.04 ±0.05	0.76	1.41	0.00
Fe	41.5 ±0.2	44.2	45.4	54.2
S	33.2 ±0.6	33.8	33.8	34.5
Cl	1.20 ±0.03	1.13	1.26	1.49
Total---100.24		99.18	100.05	100.09***

* Analyses and corrections as in Table 1 except that K and S values are averages between: (1) values obtained by using biotite and pure FeS as standards, and (2) values obtained using natural rasvumite as a presumed stoichiometric standard. As suggested in footnotes to Table 1, these values differ by about 0.2 and 1.0 wt%, respectively. Fe values typically differ by less than 0.1 wt% regardless of use of FeS or rasvumite as standard. Additional standards used were: (1) synthetic CuFeS₂ for Cu, (2) crocidolite containing 4.63 wt% Na, (3) sodalite containing 6.82 wt% Cl, and (4) synthetic monosulfide solid solution containing 9.89 wt% Ni.

** Estimated limits of error for each analysis.

*** Also reported to contain 0.23 to 0.29 wt% Li and nine trace elements totaling 0.51 wt%. (Mrzsek and Battles, 1977; L. H. Fuchs, personal communication, 1978).

Mg atom in position 1a of space group *Pm3m* (i.e., at the origin) seemed quite reasonable because of the appropriate bond distance (Mg-S, 2.626Å) and low *R* factor (0.073).

Electron microprobe analyses have shown that, although djerfisherite contains no magnesium, the sodium content approaches 0.8 Na atoms per unit cell in djerfisherites from the Khibina massif and Coyote Peak. Accordingly Na should be placed at the origin position instead of Mg. This replacement should not change the *R* factor significantly because of the close similarity between the X-ray scattering factors for Mg and Na, although the Na-S distance may be somewhat short.

The origin position 1a or, by a shift in origin, the body-centered position 1b could be occupied by still other atoms. For example, Tani (1977) assigned Li to position 1b in a djerfisherite-like compound, K₆LiFe₂₄S₂₆Cl. For iron-rich djerfisherite, the presence of octahedrally coordinated Fe at position 1a or 1b seems a reasonable hypothesis.

Acknowledgments

Ian M. Steele of the University of Chicago performed the ion probe analysis for lithium under NSF grants 76-02754 and 77-27100 to R. N. Clayton and J. V. Smith. For helpful reviews we

thank Joan R. Clark and L. B. Wiggins of the U.S. Geological Survey and Louis Fuchs of Argonne National Laboratory, Illinois.

References

- Appleman, D. E. and H. T. Evans, Jr. (1973) Job 9214: Indexing and least squares refinement of powder diffraction data. *Natl. Tech. Inf. Serv. U.S. Dept. Commerce, Springfield, Virginia. PB-216 188.*
- Clarke, D. B., G. G. Mackay, K. R. Gill, M. H. O'Hara and J. A. Gard (1977) A new potassium-iron-nickel sulphide from a nodule in kimberlite. *Earth Planet. Sci. Lett.*, 35, 421-428.
- Czamanske, G. K., C. E. Meyer, R. C. Erd and M. B. Norman II (1977) The Coyote Peak diatreme, Humboldt County, California (abstr.). *EOS (Am. Geophys. Union Trans.)*, 58, 1247.
- Dmitrieva, M. T. and V. V. Ilyukhin (1975) Crystal structure of djerfisherite. *Sov. Phys.—Dokl.* 20, 469-470 (pub. 1976). Transl. from *Dokl. Akad. Nauk SSSR*, 223, 343-345.
- , G. B. Bokiy, M. G. Dobrovolskaya and M. N. Sokolova (1977) Crystal chemical interpretation of djerfisherite heterogeneity from different deposits. In *Heterogeneity of Mineral and Fine Mineral Mixtures*, p. 69-74. Nauka, Moscow.
- Dobrovolskaya, M. G., A. I. Tsepin, A. I. Iluhin and A. I. Ponomarenko (1975) Djerfisherite from Yakutian kimberlites. In P. M. Tatarinov, Ed., *Miner. Paragenезis Miner. Endog. Mestorozhd.*, 1975, p. 3-11. Nauka, Leningrad, USSR.
- , M. N. Sokolova and A. I. Tsepin (1979) New data on chemical composition of K-bearing sulphides from the Khibina massif. *Akad. Nauk SSSR Izv. Ser. Geol.* (in press).
- Fuchs, L. (1966) Djerfisherite, alkali copper-iron sulfide; a new mineral from enstatite chondrites. *Science*, 133, 166-167.
- Genkin, A. D., N. V. Troneva and N. N. Zhuravlev (1969) The first occurrence in ores of the sulfide of potassium, iron, and copper—djerfisherite. *Geol. Rudnykh Mestorozhd.*, 11 (5), 57-64.
- Konev, A. A., V. P. Afonin, L. A. Perfil'yeva and Z. F. Ushchapovskaya (1972) Djerfisherite from Tazheran skarns. In B. M. Shmakin, Ed., *Vopr. Mineral. Gorn. Porod Rud Vost. Sib.* 1972, p. 15-22. Akad. Nauk SSSR, Sib. Otd., Inst. Geokhim., Irkutsk, USSR.
- Mrzsek, F. C. and J. E. Battles (1977) Electrochemical formation and chemical characterization of a djerfisherite-like compound. *J. Electrochem. Soc.*, 124, 1556-1558.
- Sokolova, M. N., M. G. Dobrovolskaya, N. I. Organova, M. E. Kazakova and A. L. Dmitrik (1970) A sulfide of iron and potassium—the new mineral rasvumite. *Vses. Mineralog. Obshch. Zap.* 99, 712-720.
- , ———, ———, ——— and G. L. Vasil'yeva (1971) On the occurrence and distribution of djerfisherite in pegmatites of the Khibina massif. *Geol. Rudnykh Mestorozhd.*, 13 (2), 62-71.
- Tani, B. S. (1977) X-ray study of K₆LiFe₂₄S₂₆Cl, djerfisherite-like compound. *Am. Mineral.*, 54, 819-823.
- Yakowitz, H., R. L. Myklebust and K. F. J. Heinrich (1973) FRAME: An on-line correction procedure for quantitative electron probe analyses. *Nat. Bur. Stand. Tech. Note* 796.

Manuscript received, February 13, 1979.
accepted for publication, March 15, 1979.