

Dielectric constants of diaspore and B-, Be-, and P-containing minerals, the polarizabilities of B₂O₃ and P₂O₅, and the oxide additivity rule

ROBERT D. SHANNON, MUNIRPALLAM A. SUBRAMANIAN

Central Research Department, Experimental Station 356/329, E.I. Du Pont de Nemours, Wilmington, Delaware 19880-0356, U.S.A.

ANTHONY N. MARIANO

48 Page Brook Road, Carlisle, Massachusetts 01741, U.S.A.

THURMAN E. GIER

P.O. Box 884, Chadds Ford, Pennsylvania 19317, U.S.A.

GEORGE R. ROSSMAN

Division of Geological and Planetary Sciences, California Institute of Technology, Pasadena, California 91125, U.S.A.

ABSTRACT

The 1-MHz dielectric constants and loss factors of the minerals diaspore, euclase, hambergite, sinhalite, danburite, datolite, beryllonite, and montebasite and of the synthetic oxides La₂Be₂O₅, AlP₃O₉, and NdP₅O₁₄ were determined. The dielectric polarizabilities of B₂O₃ and P₂O₅ derived from the dielectric constants of these compounds are 6.15 and 12.44 Å³, respectively. The dielectric constants of the above minerals and oxides, along with the dielectric polarizabilities of Li₂O, Na₂O, BeO, MgO, CaO, Al₂O₃, Nd₂O₃, La₂O₃, SiO₂, diaspore, and the derived values of the polarizabilities of B₂O₃ and P₂O₅, were used to calculate dielectric polarizabilities from the Clausius-Mosotti equation and to test the oxide additivity rule. The oxide additivity rule is valid to ±0.5% for all except beryllonite. These compounds with deviations from additivity of 0.5–1.5%, along with previously studied aluminate and gallate garnets, chrysoberyl, spinel, phenacite, zircon, and olivine-type silicates, form a class of well-behaved oxides that can be used as a basis for comparison of compounds that show larger deviations (>5%) caused by ionic or electronic conductivity, the presence of H₂O or CO₂, or structural peculiarities.

INTRODUCTION

Dielectric polarizability, α_D , is related to the measured dielectric constant, κ' , by the Clausius-Mosotti equation:

$$\alpha_D = 1/b[(V_m)(\kappa' - 1)/(\kappa' + 2)] \quad (1)$$

where V_m is the molar volume in Å³, b is assumed to be $4\pi/3$, and κ' , the real part of the complex dielectric constant, was measured in the range 1 KHz to 10 MHz (Roberts, 1950, 1951). The Clausius-Mosotti equation is strictly valid only for compounds in which the molecule or ion has cubic symmetry (Szigeti, 1949; Bosman and Havinga, 1963; Duffin, 1980; Kip, 1962; Megaw, 1957; Roberts, 1949, 1950, 1951; Dunmur, 1972) but has been shown to be approximately valid for a number of noncubic crystals (Roberts, 1949, 1951; Lasaga and Cygan, 1982; Shannon et al., 1989, 1990).

The concept of additivity of molecular polarizabilities implies that the molecular polarizability of a complex substance can be divided into the molecular polarizabilities of simpler substances according to

$$\alpha_D(M_2M'X_4) = 2\alpha_D(MX) + \alpha_D(M'X_2) \quad (2)$$

Previous applications of the additivity rule to minerals were reviewed by Shannon and Subramanian (1989).

The purpose of this paper is to determine the 1-MHz dielectric constants of diaspore and several Be-, B-, and P-containing oxides and minerals, to derive the polarizabilities of B₂O₃ and P₂O₅, and to evaluate the validity of the oxide additivity rule in these materials.

EXPERIMENTAL

The sources of the crystals were as follows: diaspore—grayish green crystal from Turkey; euclase—clear, colorless crystals, one from San Sebastao de Maranhao, Minas Gerais, and the other from Diamantina, Minas Gerais, Brazil; La_{1.98}Nd_{0.02}Be₂O₅—from Allied-Signal Corp.; hambergite—clear, colorless crystal from Antsirabe, Tananarive, Madagascar; sinhalite—greenish yellow crystal from the Ellawalla River, Ratnapura, Sri Lanka; danburite—clear, colorless crystal from Charcus, Mexico; datolite—clear, colorless crystal from Westfield, Massachusetts; AlPO₄—clear, colorless crystals grown hydrothermally from a hydrochloric acid-phosphoric acid solution at 170 °C as described by Ozimek and Chai (1978); NdP₅O₁₄—light purple crystals obtained from Ferro-

TABLE 1. Cell dimensions and molar volumes

	a (Å)	b (Å, β°)	c (Å)	V_m (Å ³)	Reference
Al _{0.99} Fe _{0.01} OOH	4.4005(3)	9.4268(6)	2.8458(2)	29.51	This work
BeAlSiO ₄ OH	4.7795(4)	14.332(1)	4.6323(5)	78.05	This work
La ₂ Be ₂ O ₅	7.5356	100.296(6) 7.348 91.55	7.4387	102.94	Harris and Yakei (1968)
Be ₂ BO ₃ OH	9.7641(5)	12.2080(8)	4.4335(3)	66.06	This work
Mg _{0.98} Fe _{0.02} AlBO ₄	9.8806(7)	5.6788(4)	4.3295(4)	60.73	This work
CaB ₂ Si ₂ O ₈	8.0477(5)	8.7628(9)	7.7330(5)	136.33	This work
CaBSiO ₄ OH	9.634(2)	7.610(1)	4.8334(7)	88.59	This work
Zn ₄ B ₆ O ₁₃	7.4659	90.15(1)	7.4659	209.08	Smith-Verdier and Garcia-Blanco (1980)
BaB ₂ O ₄	12.547	7.4659	12.736	96.46	Eimerl et al. (1987)
AlPO ₄	4.9423	12.547	10.9446	77.17	Thong and Schwarzenbach (1979)
AlP ₃ O ₉	13.729	4.9423	13.729	161.73	NBS Mon 25
NdP ₅ O ₁₄	8.7672	13.729	13.0326	256.93	Allbrand et al. (1974)
LiAlPO ₄ OH	5.1988(4)	90.481	5.0415(5)	80.54	This work
	112.29(1)	7.1721(7)	67.848(6)		
NaBePO ₄	8.1354(4)	97.840(7)	14.2030(6)	75.11	This work
		7.8003(3)			
		90.000(4)			

TABLE 2. Summary of single-crystal dielectric constants

	$\kappa'_a, \tan \delta$	$\kappa'_b, \tan \delta$	$\kappa'_c, \tan \delta$	$\langle \kappa' \rangle$	Frequency	Reference
Al _{0.99} Fe _{0.01} OOH	8.335 ± 0.05	9.146 ± 0.05	7.848 ± 0.05	8.443	1 MHz	This work
	0.0009	0.0008	0.0007			
	7.70	8.38	7.27			Takubo et al. (1953)
	5.7, undefined orientation				1 MHz	Olhoeft (1981)
	0.0264					
BeAlSiO ₄ OH	6.481 ± 0.02	6.663 ± 0.05	6.764 ± 0.03	6.64	1 MHz	This work
	0.0005	0.0006	0.0006			
La ₂ Be ₂ O ₅	38.74 ± 0.8	25.93 ± 0.02	22.65 ± 0.2	29.11	1 MHz	This work
	0.0010	0.0009	0.0012			
Be ₂ BO ₃ OH	4.451 ± 0.02	4.738 ± 0.05	5.28 ± 0.1	4.82	1 MHz	This work
	0.0014	0.0013	0.0011			
Mg _{0.98} Fe _{0.02} AlBO ₄	7.753 ± 0.01	8.339 ± 0.02	8.113 ± 0.01	8.075	1 MHz	This work
	0.0009	0.0008	0.0007			
CaB ₂ Si ₂ O ₈	6.720 ± 0.01	6.618 ± 0.01	6.869 ± 0.01	6.735	1 MHz	This work
	0.0007	0.0009	0.0009			
	6.35	6.34	6.58	6.4	500 Hz	Takubo et al. (1953)
	—	6.34	6.77			Takubo et al. (1953)
	6.9, undefined orientation				1 MHz	Olhoeft (1981)
CaBSiO ₄ OH	6.84 ± 0.2	8.328 ± 0.02	6.86 ± 0.1	7.34	1 MHz	This work
	0.020	0.002	0.010			
	7.2, undefined orientation				1 MHz	Olhoeft (1981)
	0.006					
Zn ₄ B ₆ O ₁₃	7.24			7.24	100 KHz	Bohaty et al. (1982)
BaB ₂ O ₄	5.78		6.6	6.05	1 MHz	Guo and Bhalla (1989)
	<0.001		<0.001			
AlPO ₄	4.57 ± 0.05		4.54 ± 0.05	4.56	1 MHz	Shannon et al. (1990)
	0.001		0.001			
AlP ₃ O ₉	5.185 ± 0.05			5.185	1 MHz	This work
	0.0005					
NdP ₅ O ₁₄	6.567 ± 0.05	5.699 ± 0.02	6.722 ± 0.06	6.33	1 MHz	This work
	0.0009	0.0009	0.0037			
LiAlPO ₄ OH	6.808 ± 0.005	8.342 ± 0.007	8.159 ± 0.15	7.77	1 MHz	This work
	0.005	0.010	0.008			
	7.7, undefined orientation				1 MHz	Olhoeft (1981)
	0.0178					
NaBePO ₄	6.34 ± 0.06	6.44 ± 0.07	6.32 ± 0.06	6.37	1 MHz	This work
	0.0005	0.0005	0.0005			

Note: $\kappa'_a = \kappa'_{11}$, $\kappa'_b = \kappa'_{22}$, $\kappa'_c = \kappa'_{33}$ except for La₂Be₂O₅, NbP₅O₁₄, euclase, datolite, and montebrasite. See experimental section for details.

TABLE 3. Dielectric constants and molar polarizabilities

Compound	$\langle \kappa' \rangle$	V_m (\AA^3)	α_D (\AA^3)	Reference
Li ₂ O	8.06		4.11	Osaka and Shindo (1984)
Na ₂ O			5.59	Shannon (1991)
BeO	7.16	13.79	2.213	Subramanian et al. (1989)
MgO	9.830	18.69	3.331	Fontanella et al. (1974)
ZnO	8.49	23.55	4.01	Kobiakov (1980)
CaO	11.95	27.83	5.22	Subramanian et al. (1989)
BaO	14.40	41.59	8.11	Jonker and VanSanten (1947)
Al ₂ O ₃	10.126	42.45	7.627	Fontanella et al. (1974)
Nd ₂ O ₃			16.3*	This work
La ₂ O ₃			17.7**	This work
SiO ₂	4.559	37.66	4.878	Fontanella et al. (1974)
Al _{0.99} Fe _{0.01} OOH	8.443	29.51	5.021	This work
BeAlSiO ₄ OH	6.64	78.05	12.16	This work
La ₂ Be ₂ O ₅	29.11	102.94	22.21	This work
Be ₂ BO ₃ OH	4.82	66.06	8.80	This work
Mg _{0.98} Fe _{0.02} AlBO ₄	8.075	60.73	10.181	This work
CaB ₂ Si ₂ O ₈	6.735	136.33	21.29	This work
CaBSiO ₄ OH	7.34	88.59	14.36	This work
Zn ₄ B ₆ O ₁₃	7.24	209.08	33.71	Bohaty et al. (1982)
BaB ₂ O ₄	6.05	96.46	14.44	Guo and Bhalla (1989)
AlPO ₄	4.56	77.17	10.0	Shannon (unpublished data)
AlP ₃ O ₉	5.185	161.73	22.49	This work
NdP ₃ O ₁₄	6.33	256.93	39.24	This work
LiAlPO ₄ OH	7.77	80.54	13.32	This work
NaBePO ₄	6.37	75.11	11.502	This work

* Obtained from $\alpha_D(\text{Nd}_2\text{O}_3) = [\alpha_D(\text{Nd}_3\text{Ga}_5\text{O}_{12}) - 2.5\alpha_D(\text{Ga}_2\text{O}_3)]/1.5$; Shannon et al. (1990).

** Obtained from $\alpha_D(\text{La}_2\text{O}_3) = \alpha_D(\text{La}_2\text{Be}_2\text{O}_5) - 2\alpha_D(\text{BeO})$.

cube, Saugerties, New York; beryllonite—clear, colorless crystal from Stoneham, Maine; and montebasite—clear, colorless crystal from Minas Gerais, Brazil (USNM 157924).

Crystals of AlP₃O₉ were grown hydrothermally in an Au tube charged with 1.40 g Al₂O₃, 3.50 g 86% H₃PO₄, and 28.0 g polyphosphoric acid (85% P₂O₅). The tube was held 4 h at 900 °C and cooled 1 °C/h to 800 °C. Clear, colorless crystals 8 × 8 × 5 mm were recovered.

Samples were oriented for cutting by polarized light and by back reflection Laue photographs. X-ray diffraction patterns were obtained using a Guinier-type focusing camera using CuK α_1 radiation and Si SRM 640 as an internal standard. Cell dimensions (Table 1) were obtained by least-squares refinement.

Electron microprobe analyses were made using a JEOL 733 electron microprobe. Electron microprobe data reduction methods are described by Armstrong (1982, 1988). Although no systematic effort was made to obtain information on possible chemical zonation, significant color variations were not observed in any of the crystals. Microprobe analyses of points on individual crystals did not reveal any significant chemical heterogeneities.

The composition of diaspore was determined by microprobe analysis to be Al_{0.99}Fe_{0.05}OOH. Euclase analysis gave composition Be_{1.00}Al_{0.99}Si_{1.00}O₄OH, assuming the theoretical value for Be. The F content of the hambergite was determined by electron microprobe analysis. Assuming Be : B = 2:1, the composition is Be₂BO₃[F_{0.04}(OH)_{0.96}]. Microprobe analysis of the danburite and sinhalite crystals led to the compositions Ca_{1.00}B_{1.99}Al_{0.01}Si_{2.00}O₈ and Mg_{0.98}Fe_{0.02}Al_{1.99}BO₄, respectively, assuming theoretical values for B. Microprobe analysis of beryllonite indicated

a composition of Na_{1.00}Be_{1.00}P_{1.00}O₄, assuming the theoretical value for Be. A typical analysis of the montebasite crystals indicated a composition Li_{1.00}Al_{1.00}P_{1.00}O₄[(OH)_{0.98}F_{0.02}]. This analysis and the unit-cell volume of 161.08 Å³ indicate a composition close to that of pure montebasite (Cerna et al., 1972).

Rectangular- or triangular-shaped samples were cut from the bulk crystals using a low-speed diamond wheel saw. Slabs were cut perpendicular to the reciprocal axes of all crystals, allowing determination of κ'_{11} , κ'_{22} , and κ'_{33} in the cubic, hexagonal, and orthorhombic crystals. To determine κ'_{11} and κ'_{33} of monoclinic crystals, it was necessary to obtain values of κ' in at least three directions in the (*h*0*l*) plane. Similarly, to determine κ'_{11} , κ'_{22} , and κ'_{33} of triclinic crystals, it was necessary to measure κ' in directions other than parallel to **a***, **b***, and **c***. A detailed description of the determination of κ'_{11} , κ'_{22} , and κ'_{33} of anisotropic crystals is given by Takubo (1941). Because of insufficient sample size, slabs were not cut in a third orientation parallel to **b*** of the monoclinic crystals or in directions other than perpendicular to the reciprocal axes of montebasite. Thus, values of κ'_{11} , κ'_{22} , κ'_{33} , and κ'_{13} were not determined for the monoclinic crystals of La₂Be₂O₅, NdP₄O₁₄, euclase, or beryllonite, and κ'_{11} , κ'_{22} , κ'_{33} , κ'_{12} , κ'_{13} , and κ'_{23} were not determined for triclinic montebasite. However, for La₂Be₂O₅, NdP₄O₁₄, datolite, and beryllonite, the deviations from orthorhombic symmetry are very slight, so the deviations of κ'_{11} , κ'_{22} , and κ'_{33} from the values κ'_{a^*} , κ'_{b^*} , and κ'_{c^*} indicated in Table 2 are believed to be small. For monoclinic euclase $\kappa_{a^*} \cong \kappa_{b^*} \cong \kappa_{c^*}$, so the mean value of $\langle \kappa' \rangle$ listed in Tables 2 and 3 is probably close to the actual value of $\langle \kappa' \rangle$. For triclinic montebasite, the deviations are probably larger, and the mean value of $\langle \kappa' \rangle$

TABLE 4. Dielectric polarizability data for B₂O₃ and P₂O₅

Compound	$\alpha_D(\text{total}), \text{\AA}^3$	$\alpha_D(\text{B}_2\text{O}_3)^*, \text{\AA}^3$
B₂O₃		
Mg _{0.98} Fe _{0.02} AlBO ₄	10.181	6.04
CaB ₂ Si ₂ O ₈	21.29	6.31
Zn ₄ B ₆ O ₁₃	33.71	5.89
BaB ₂ O ₄	14.44	6.33
	$\langle \alpha_D(\text{B}_2\text{O}_3) \rangle = 6.15$	
P₂O₅		
AlPO ₄	10.0	12.37
AlP ₃ O ₉	22.49	12.45
LiAlPO ₄ OH	13.32	12.49
NdP ₅ O ₁₄	39.24	12.44
NaBePO ₄	11.502	12.98
	$\langle \alpha_D(\text{P}_2\text{O}_5) \rangle = 12.44$ omitting NaBePO ₄	

* Obtained from $\alpha_{\text{tot}} = \Sigma (\alpha_{\text{oxide}})$.

TABLE 5. Comparison of observed and predicted beryllate, borate, and phosphate single-crystal dielectric polarizabilities

Compound	$\langle \kappa' \rangle$	Pred. α_T	Measured $\alpha_T(\text{exp})$	Δ (%)
BeAlSiO ₄ OH	6.64	12.11	12.16	+0.4
La ₂ Be ₂ O ₅	29.11	22.23	22.21	0.0
Mg _{0.98} Fe _{0.02} AlBO ₄	8.075	10.24	10.18	-0.6
CaB ₂ Si ₂ O ₈	6.735	21.13	21.29	+0.8
AlPO ₄	4.56	10.03	10.0	-0.3
AlP ₃ O ₉	5.185	22.47	22.49	+0.1
NdP ₅ O ₁₄	6.33	39.25	39.24	-0.0
LiAlPO ₄ OH	7.77	13.30	13.32	+0.2
NaBePO ₄	6.37	11.23	11.50	+2.4
				$\langle \Delta \rangle = 0.5\%$

in Tables 2 and 3 can be expected to deviate considerably from the actual mean $\langle \kappa' \rangle$ value.

The datolite crystal contained numerous veils and a few small inclusions, and it was difficult to obtain dielectric specimens free of chipped edges. These imperfections resulted in larger estimated errors than found in other crystals. The crystal of NdP₅O₁₄ showed pronounced {010} cleavage, and most specimens cut perpendicular to **b*** contained small delaminated areas at the sample perimeter. These delaminations may be responsible for the unusually high dissipation factors of the samples cut perpendicular to **c***. Sample thickness and area varied from 0.02 to 0.12 cm and 0.05 to 1.5 cm², respectively. Sputtered Au electrodes were applied over the entire parallel surfaces of the sample using a Denton Vacuum Desk II sputtering unit. Sample preparation is described in detail by Subramanian et al. (1989).

Dielectric constant measurements were performed over the frequency range 30 KHz to 3 MHz with a parallel plate capacitance technique using a Hewlett-Packard (1984) 4275A LCR bridge and fixture 16034B (Test Tweezers) according to the procedure described by Subramanian et al. (1989). Edge corrections were made using the expression

$$C_e = (0.019 \ln P/t - 0.043)P \quad (3)$$

where t = sample thickness and P = perimeter in centimeters.

The overall accuracy of the dielectric constant measurements using the above techniques is estimated to be 1.0–1.5%. Dielectric loss errors are estimated to be 5–20% at levels of $\tan \delta = 0.002$ and 50–100% at levels of 0.0004–0.0005.

RESULTS

Table 1 summarizes unit-cell dimensions of the crystals studied here and of Zn₄B₆O₁₃ and β BaB₂O₄, used for derivation of the polarizability of B₂O₃. Table 2 lists the dielectric constants and dielectric loss ($\tan \delta$) values at 1 MHz of the crystals studied here and compares them with previously reported dielectric data. The dielectric constants showed deviations of less than 0.2% over the range of frequencies 30 KHz to 3 MHz. In Table 2 we also

compare our data with previously reported dielectric data for diasopore, danburite, datolite, and amblygonite. The values of $\kappa'_a = 7.70$, $\kappa'_b = 8.38$, and $\kappa'_c = 7.27$ for diasopore reported by Takubo et al. (1953) are all $\sim 8\%$ smaller than the values reported by us. Because their values obtained for quartz are also $\sim 8\%$ low, there is apparently a systematic error in the Takubo et al. technique for measuring dielectric constants. The value of 5.7 reported by Olhoeft (1981) for a sample of diasopore from Rosebud, Missouri, is anomalously low. The relatively high value of $\tan \delta = 0.0264$ suggests poor sample quality. The value of $\kappa' = 6.9$ reported by Olhoeft for a sample of danburite of unknown orientation from New York is consistent with our mean value of 6.735. The values of Takubo et al. for danburite from Toroku, Japan, are lower than our values by $\sim 5\%$. The value of 7.7 obtained for amblygonite by Olhoeft is in good agreement with our mean value of 7.77, although the dielectric loss of his specimen is significantly higher than that found for our sample of mon-tebrasite.

DISCUSSION

Table 3 lists mean dielectric constants and molar volumes of the crystals studied here and the oxides that are used to test the oxide additivity rule. Arithmetic, rather than geometric, mean values are used. Geometric mean values are smaller by 0.0–0.2% for crystals with little or no anisotropy, whereas they can amount to 2.7% for crystals such as La₂Be₂O₅ with significant anisotropy. Table 4 lists the total polarizabilities of the ternary oxides and the polarizabilities of B₂O₃ and P₂O₅ derived by subtracting the components of polarizabilities due to the binary oxides. Composite values for $\alpha_D(\text{B}_2\text{O}_3)$ of 6.15 \AA^3 and $\alpha_D(\text{P}_2\text{O}_5)$ of 12.44 \AA^3 were extracted from $\alpha_D(\text{B}_2\text{O}_3 \text{ or } \text{P}_2\text{O}_5) = \alpha_D(\text{complex oxide}) - \alpha_D(\text{simple oxide})$.

Table 5 compares the total molecular dielectric polarizabilities determined from the measured dielectric constants using the Clausius-Mosotti relationship (Eq. 1) and from the oxide additivity rule using what we believe are the most accurate dielectric constants of Li₂O, Na₂O, BeO, MgO, CaO, Al₂O₃, Nd₂O₃, La₂O₃, SiO₂, and AlOOH (Table 3). The agreement between the observed dielectric

polarizabilities and those calculated from the sum of the oxide polarizabilities according to the oxide additivity rule (Eq. 2) is excellent and is comparable to the typical 1% variation observed previously for a series of aluminates, gallates, and silicates (Shannon and Subramanian, 1989; Subramanian and Shannon, 1989; Shannon et al., 1989, 1990, 1991).

The slightly larger deviation of beryllonite might be caused by the inaccuracy of $\alpha_D(\text{Na}_2\text{O})$ estimated from the polarizability of NaF in conjunction with a value of $\alpha_D(\text{O}^{2-}) = 2.01 \text{ \AA}$ (Shannon, 1991). It might also be caused by the "rattling cation" effect, which was described by Dunitz and Orgel (1960) as a progressive "loosening of the central cation at the center of its surrounding octahedron to off-center displacements characteristic of ferroelectric and antiferroelectric substances" as the size of the central cation in an octahedron decreases. The polyhedron can adjust its configuration to adapt to the small cation by movement of the cation, the anions, or both, resulting in polyhedral distortion such as in the Na1 site of beryllonite. When crystal symmetry restricts the motion of both cation and anion such as is observed in cubic pyrope, larger than normal bond distances and thermal motion may occur (Shannon and Rossman, 1992). In both instances evidence for rattling cations can be seen from decreased apparent bond valences or increased thermal motion. Na1, which occupies a nine-coordinated site in NaBePO_4 (Giuseppetti and Tadini, 1973), is characterized by unusually large thermal parameters and by bond valence sums, calculated from the Brown and Altermatt (1985) parameters, which are somewhat low, 0.87 valence units (vu), relative to its theoretical value of 1.0 vu. Na2 and Na3 occupy distorted octahedral sites and have more normal apparent bond valences of 1.06 and 1.15 vu, respectively.

This group of beryllates, borates, and phosphates, along with several other groups of oxides including Y and RE aluminates, chrysoberyl, spinel, olivine-type silicates, phenacite, and zircon form a class of well-behaved oxides whose dielectric polarizabilities follow the oxide additivity rule to ± 0.5 –1.5%. This group forms a basis for comparison with compounds that show larger deviations ($>5\%$) because of ionic or electronic conductivity, the presence of H_2O or CO_2 , or structural peculiarities (Shannon, 1991). This latter type of deviation is illustrated by several structural groups such as silicate garnets and melilite-type compounds that contain certain members (pyrope, hardystonite, akermanite) that show strong deviations ($\pm \sim 5\%$) from the additivity rule.

ACKNOWLEDGMENTS

We thank B.H.T. Chai for providing the crystal of $\text{La}_{1.98}\text{Nd}_{0.02}\text{Be}_2\text{O}_5$; T.J. Muro of Ferroxcube, Saugerties, New York; for the crystal of $\text{NdP}_3\text{O}_{14}$; D.A. Appleman of the Smithsonian Institution for providing the crystal of montebrazite (USNM 157924); R.W. Shiffer for sample preparation; R.A. Oswald for making the capacitance measurements; A. Brown (Studsvisk Energiteknik AB, Nykoping, Sweden), L.F. Lardear, and R.L. Harlow for crystal orientation and C. Foris for obtaining cell dimensions; and J.T. Armstrong (California Institute of Technology, Pasadena, Cali-

fornia) for microprobe data. This work was supported in part by NSF grant EAR-8618200. Contribution no. 5672.

REFERENCES CITED

- Allbrand, K.R., Attig, R., Fenner, J., Jeser, J.P., and Mootz, D. (1974) Crystal structure of the laser material $\text{NdP}_3\text{O}_{14}$. *Materials Research Bulletin*, 9, 129–140.
- Armstrong, J.T. (1982) New ZAF and α -factor correction procedures for the quantitative analysis of individual microparticles. In K.F.J. Heinrich, Ed., *Microbeam analysis*, 1982, p. 175–180. San Francisco Press, San Francisco.
- (1988) Quantitative analysis of silicate and oxide materials: Comparison of Monte Carlo, ZAF and $\phi(\rho-z)$ procedures. In D.E. Newbury, Ed., *Microbeam analysis*, 1988, p. 239–256. San Francisco Press, San Francisco.
- Bohaty, L., Haussuhl, S., Liebertz, J., and Stahr, S. (1982) Single crystal growth and physical properties of cubic $\text{Zn}_4(\text{BO}_2)_6$. *Zeitschrift für Kristallographie*, 161, 157–158.
- Bosman, A.J., and Havinga, E.E. (1963) Temperature dependence of dielectric constants of cubic ionic compounds. *Physical Review*, 129, 1593–1600.
- Brown, I.D., and Altermatt, D. (1985) Bond-valence parameters obtained from a systematic analysis of the inorganic crystal structure database. *Acta Crystallographica*, B41, 244–247.
- Cerna, I., Černý, P., and Ferguson, R.B. (1972) The Tanco pegmatite at Bernic Lake, Manitoba. III. Amblygonite-montebrazite. *Canadian Mineralogist*, 11, 643–659.
- Duffin, W.J. (1980) *Electricity and magnetism* (3rd edition), p. 307–329. McGraw-Hill, London.
- Dunitz, J.D., and Orgel, L.E. (1960) Stereochemistry of ionic solids. *Advances in Inorganic Chemistry and Radiochemistry*, 2, 1–60.
- Dunmur, D.A. (1972) The local electric field in anisotropic molecular crystals. *Molecular Physics*, 23, 109–115.
- Eimerl, D., Davis, L., Velsko, S., Graham, E.K., and Zalkin, A. (1987) Optical, mechanical and thermal properties of barium borate. *Journal of Applied Physics*, 62, 1968–1983.
- Fontanella, J., Andeen, C., and Schuele, D. (1974) Low frequency dielectric constants of α -quartz, sapphire, MgF_2 , and MgO . *Journal of Applied Physics*, 45, 2852–2854.
- Giuseppetti, G., and Tadini, C. (1973) Refinement of the crystal structure of beryllonite, NaBePO_4 . *Tschermaks Mineralogische und Petrographische Mitteilungen*, 20, 1–12.
- Guo, R., and Bhalla, A.S. (1989) Pyroelectric, piezoelectric and dielectric properties of β - BaB_2O_7 single crystal. *Journal of Applied Physics*, 66, 6186–6188.
- Harris, L.A., and Yakel, H.L. (1968) The crystal structure of $\text{La}_2\text{Be}_2\text{O}_5$. *Acta Crystallographica*, B24, 672–676.
- Hewlett-Packard (1984) Operating manual for 4275A multi-frequency LCR meter. Yokogawa-Hewlett-Packard Ltd., Tokyo.
- Jonker, G.H., and VanSanten, J.H. (1947) De dielectrische eigenschappen van titanaten van het perovskiet-type. *Chemisch Weekblad*, 43, 672–679.
- Kip, A.F. (1962) *Fundamentals of electricity and magnetism*, 78–103. McGraw-Hill, New York.
- Kobiakov, I.B. (1980) Elastic, piezoelectric and dielectric properties of ZnO and CdS single crystals in a wide range of temperatures. *Solid State Communications*, 35, 305–310.
- Lasaga, A.C., and Cygan, R.T. (1982) Electronic and ionic polarizabilities of silicate minerals. *American Mineralogist*, 67, 328–334.
- Megaw, H.D. (1957) *Ferroelectricity in crystals*, p. 165–178. Methuen, London.
- Olhoeft, G.R. (1981) Electrical properties of rocks. In Y.S. Touloukian, W.R. Judd, and R.F. Roy, Eds., *Physical properties of rocks and minerals*, p. 257–329. McGraw-Hill, New York.
- Osaka, T., and Shindo, I. (1984) Infra-red reflectivity and Raman scattering of lithium oxide single crystals. *Solid State Communications*, 51, 421–424.
- Ozimek, E.J., and Chai, B.H.T. (1978) Piezoelectric properties of single crystal berillite. *Frequency Control Symposium*, 80–87.

- Roberts, R. (1949) Dielectric constants and polarization of ions in simple crystals and barium titanate. *Physical Review*, 76, 1215–1220.
- (1950) A theory of dielectric polarization in alkali halide crystals. *Physical Review*, 77, 258–263.
- (1951) Polarizabilities of ions in perovskite-type crystals. *Physical Review*, 81, 865–868.
- Shannon, R.D. (1991) Factors affecting the dielectric constants of oxides and fluorides. *Chemistry of electronic ceramic materials. Proceedings of the International Conference on the Chemistry of Electronic Ceramic Materials, Jackson Hole, Wyoming, Aug. 17–22. NIST Special Publication*, 804, 457–471.
- Shannon, R.D., and Rossman, G.R. (1992) Dielectric constants of silicate garnets and the oxide additivity rule. *American Mineralogist*, 77, 94–100.
- Shannon, R.D., and Subramanian, M.A. (1989) Dielectric constants of chrysoberyl, spinel, phenacite and forsterite and the oxide additivity rule. *Physics and Chemistry of Minerals*, 16, 747–751.
- Shannon, R.D., Subramanian, M.A., Mariano, A.M., and Rossman, G.R. (1989) Mineral dielectric constants and the oxide additivity rule. *Proceedings of the Materials Research Society Symposium on Materials for Magneto-Optic Data Storage, San Diego, April 24–27*.
- Shannon, R.D., Subramanian, M.A., Allik, T.H., Kimura, H., Kokta, M.R., Randles, M.H., and Rossman, G.R. (1990) Dielectric constants of yttrium and rare earth garnets, the polarizability of gallium oxide and the oxide additivity rule. *Journal of Applied Physics*, 67, 3798–3802.
- Shannon, R.D., Subramanian, M.A., Hosoya, S., and Rossman, G.R. (1991) Dielectric constants of tephroite, fayalite and olivine and the oxide additivity rule. *Physics and Chemistry of Minerals*, 18, 1–6.
- Smith-Verdier, P., and Garcia-Blanco, S. (1980) Redetermination of the structure of anhydrous $Zn_4O(BO_3)_6$. *Zeitschrift für Kristallographie*, 151, 175–177.
- Subramanian, M.A., and Shannon, R.D. (1989) Dielectric constant of Y-stabilized zirconia, the polarizability of zirconia and the oxide additivity rule. *Materials Research Bulletin*, 24, 1477–1483.
- Subramanian, M.A., Shannon, R.D., Chai, B.H.T., Abraham, M.M., and Wintersgill, M.C. (1989) Dielectric constants of BeO, MgO and CaO using the two-terminal method. *Physics and Chemistry of Minerals*, 16, 741–746.
- Szigeti, B. (1949) Polarizability and dielectric constant of ionic crystals. *Transactions of the Faraday Society*, 45, 155–166.
- Takubo, J. (1941) Versuche über die Dielektrizitätskonstanten einiger Mineralien und über das dielektrische Verhalten derselben bei Erhitzung. *Memoirs of the College of Science, Kyoto Imperial University, series B*, no. 2., 16, 95–154.
- Takubo, J., Ukai, Y., and Kakitani, S. (1953) On the dielectric constants of minerals. *Mineralogical Journal*, 1, 3–24.
- Thong, N., and Schwarzenbach, D. (1979) The use of dielectric field gradient calculations in charge density refinements. II. Charge density refinement of the low-quartz structure of aluminum phosphate. *Acta Crystallographica*, A35, 658–664.

MANUSCRIPT RECEIVED NOVEMBER 26, 1990

MANUSCRIPT ACCEPTED SEPTEMBER 11, 1991