

Törnebohmitite, $\text{RE}_2\text{Al}(\text{OH})[\text{SiO}_4]_2$: crystal structure and genealogy of $\text{RE}(\text{III})\text{Si}(\text{IV}) \rightleftharpoons \text{Ca}(\text{II})\text{P}(\text{V})$ isomorphisms

JINCHUAN SHEN

*X-ray Laboratory, Graduate School
Wuhan College of Geology
Beijing, China*

AND PAUL BRIAN MOORE

*Department of the Geophysical Sciences
The University of Chicago
Chicago, Illinois 60637*

Abstract

Törnebohmitite, $\text{RE}_2\text{Al}(\text{OH})[\text{SiO}_4]_2$, monoclinic, $a = 7.383(3)$, $b = 5.673(3)$, $c = 16.937(6)\text{Å}$, $\beta = 112.04(2)^\circ$, $Z = 4$, space group $P2_1/c$, is structurally allied to the brackebuschite and pyrobelonite groups of minerals. It is isostructural with fornacite. $R = 0.033$ for 2586 independent reflections.

The basis of the structure consists of linear $\frac{1}{2}[\text{Al}(\text{OH})(\text{O}_7)_3]$ octahedral chains which run parallel to $[010]$. Insular $[\text{SiO}_4]$ which corner-link to the octahedral chains are arranged in *trans* configuration to these chains. These admit the large RE (rare earth) cations which form a serrated wall of linked $\text{RE}\phi_{10}$ polyhedra which is oriented parallel to the $\{001\}$ plane. Average distances are $^{110}\text{RE}(1)-\text{O} = 2.64$, $^{110}\text{RE}(2)-\text{O} = 2.68$, $^{16}\text{Al}-\text{O}$, $\text{OH} = 1.90$, $^{14}\text{Si}(1)-\text{O} = 1.62$ and $^{14}\text{Si}(2)-\text{O} = 1.63\text{Å}$.

Törnebohmitite is yet another example where isomorphisms of the type $\text{RE}^3\text{Si}^{4+} \rightleftharpoons \text{Ca}^{2+}\text{P}^{5+}$ can be found.

Introduction

Törnebohmitite is a hydrous rare earth silicate, consisting principally of the rare earth elements (= RE) lanthanum, cerium and neodymium. It was first discovered as a minor constituent of the cerite ores from the Bastnäs Mine, Riddarhyttan, Parish of Skinnskatteberg, Province of Västmanland, central Sweden. Geijer (1921) first announced the new species, and Geijer and Carlborg (1923) offered a comprehensive document from a geological and historical standpoint of this remarkable region, which is rich in mining history and has been a site of extensive mineralogical-chemical investigations. Jorpes (1966), for example, documents the journeys of Jöns Jacob Berzelius, in search of minerals which provided him with several new rare earth elements. Of the rare earth silicate species, cerite appeared to be the most predominant, along with allanite. Geijer discerned törnebohmitite in thin sections, where it occurs as green, pleochroic grains embedded in the

cerite ore and recognized its distinction from cerite. He named it after Alfred Elis Törnebohm (1838-1911), former Director of the Geological Survey of Sweden.

The chemical composition of törnebohmitite was obtained by Mauzelius and reported by Geijer. It is listed in Table 1 along with a calculated composition derived from our structure analytical study. Agreement between the chemical analysis of Mauzelius and the theoretical end member formula $\text{Ce}_2\text{Al}(\text{OH})[\text{SiO}_4]_2$ is good, bearing in mind that reported FeO could be Fe_2O_3 and that minor CaO probably substitutes for RE. Water was not reported; the low F content is not sufficient to warrant predominant $\text{F}^- - \text{OH}^-$ substitution. The hydroxyl anion is so tightly bound that it may be included with "ignition". The ignition content (1.70%) and theoretical water content (1.77%) make this proposition appealing.

Despite subsequent attempts to rationalize törnebohmitite's crystal chemistry, the literature is fraught

Table 4. Tornebohmitte $|F_o| - |F_c|$ table.
Shen and Moore.

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITTE CRYSTAL STRUCTURE										PAGE 1				
H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
1	0	0	125	123	3	3	0	45	40	8	6	0	164	157
2	0	0	271	-306	4	3	0	120	-117	1	7	0	87	91
3	0	0	453	-481	5	3	0	276	-279	2	7	0	72	74
4	0	0	424	440	6	3	0	36	33	3	7	0	85	-84
5	0	0	299	311	7	3	0	155	155	4	7	0	122	-118
6	0	0	155	165	8	3	0	148	149	5	7	0	95	-94
7	0	0	325	-341	9	3	0	107	-105	6	7	0	78	76
8	0	0	132	-138	10	3	0	108	-103	7	7	0	60	59
9	0	0	36	33	11	3	0	772	770	8	7	0	199	201
10	0	0	149	144	12	4	0	21	19	9	8	0	31	-24
11	0	0	26	-6	13	4	0	151	-145	10	8	0	38	30
1	1	0	75	71	14	4	0	342	-339	11	8	0	115	-116
2	1	0	64	-63	15	4	0	234	232	12	8	0	44	44
3	1	0	139	-139	16	4	0	163	162	13	8	0	26	-7
4	1	0	104	102	17	4	0	144	142	14	8	0	98	-99
5	1	0	336	349	18	4	0	218	215	15	9	0	61	-59
6	1	0	15	-16	19	4	0	114	-108	16	9	0	25	30
7	1	0	185	-192	20	4	0	49	-48	17	9	0	34	34
8	1	0	187	-193	21	5	0	71	-66	18	1	1	41	-45
9	1	0	111	114	22	5	0	52	50	19	1	1	20	-19
10	1	0	137	135	23	5	0	142	141	20	1	1	15	5
0	2	0	806	-795	24	5	0	191	191	21	1	1	88	89
1	2	0	238	-227	25	5	0	48	-42	22	1	1	17	-31
2	2	0	710	694	26	5	0	100	94	23	1	1	27	-12
3	2	0	307	313	27	5	0	100	-94	24	1	1	17	-31
4	2	0	69	-68	28	5	0	74	-69	25	1	1	81	-83
5	2	0	352	-359	29	5	0	103	98	26	1	1	51	53
6	2	0	32	32	30	6	0	234	-236	27	1	1	76	74
7	2	0	-35	238	31	6	0	95	-90	28	1	1	28	-28
8	2	0	241	247	32	6	0	211	210	29	1	1	63	-64
9	2	0	66	-66	33	6	0	129	130	30	1	1	40	-38
10	2	0	69	-64	34	6	0	27	21	31	1	1	58	59
1	3	0	15	-13	35	6	0	132	-132	32	1	1	13	-9
2	3	0	75	69	36	6	0	25	-19	33	1	1	30	-34
3	3	0			37	6	0	73	70	34	1	1	48	50

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 3

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
-5	5	2	224	-223	-4	7	2	81	83	0	1	3	100	99	-7	3	3	86	85	9	4	3	76	-70
-1	5	2	137	-133	-2	7	2	168	-170	1	1	3	34	-37	-6	3	3	89	-86	-8	5	3	143	-132
-3	5	2	81	77	-1	7	2	63	-66	2	1	3	88	-90	-5	3	3	150	-152	-7	5	3	111	-109
-2	5	2	416	416	0	7	2	53	54	4	1	3	101	105	-4	3	3	24	26	-5	5	3	101	96
-1	5	2	116	115	1	7	2	151	150	5	1	3	40	40	-3	3	3	243	241	-5	5	3	171	171
0	5	2	95	-91	2	7	2	34	32	6	1	3	26	-26	-2	3	3	88	89	-4	5	3	63	-61
1	5	2	124	-225	3	7	2	63	-63	7	1	3	32	-36	-1	3	3	291	-283	-3	5	3	289	-289
2	5	2	110	112	4	7	2	56	-53	8	1	3	26	23	0	3	3	250	-246	-2	5	3	105	-106
3	5	2	165	167	5	7	2	63	66	9	1	3	34	23	1	3	3	88	87	-1	5	3	291	293
4	5	2	100	98	6	7	2	141	134	10	1	3	20	16	2	3	3	225	224	0	5	3	250	253
5	5	2	122	-119	-5	8	2	131	128	-11	2	3	56	-48	4	3	3	218	-219	1	5	3	114	-115
6	5	2	133	-128	-4	8	2	56	-54	-10	2	3	56	-49	5	3	3	99	-96	2	5	3	271	-272
7	5	2	28	-26	-3	8	2	82	-82	-9	2	3	36	31	6	3	3	114	111	3	5	3	24	-17
8	5	2	36	33	-1	8	2	145	148	-8	2	3	81	84	7	3	3	94	91	4	5	3	260	257
-8	6	2	51	45	0	8	2	47	47	-7	2	3	19	14	8	3	3	21	-13	5	5	3	115	-110
-7	6	2	39	-32	1	8	2	39	-36	-6	2	3	88	-91	9	3	3	76	-68	6	5	3	125	-121
-6	6	2	101	-95	2	8	2	107	-106	-5	2	3	46	-45	-10	4	3	94	-88	7	5	3	136	-129
-5	6	2	82	-79	3	8	2	69	-67	-4	2	3	96	100	-9	4	3	51	-51	8	5	3	33	28
-4	6	2	30	-25	4	8	2	39	33	-3	2	3	82	81	-8	4	3	133	-129	-8	6	3	158	148
-3	6	2	151	151	5	8	2	86	83	-2	2	3	16	-18	-7	4	3	27	-28	-7	6	3	34	32
-2	6	2	31	-25	-2	9	2	100	105	-1	2	3	63	-62	-6	4	3	151	149	-6	6	3	144	-142
-1	6	2	51	-47	0	9	2	55	56	0	2	3	61	63	-5	4	3	78	77	-5	6	3	107	-103
0	6	2	172	-174	1	9	2	72	65	1	2	3	121	121	-4	4	3	113	-115	-4	6	3	88	89
1	6	2	81	79	0	9	2	62	-64	2	2	3	30	-29	-3	4	3	107	-105	-3	6	3	86	84
2	6	2	62	63	-10	1	3	18	6	3	2	3	49	-52	-2	4	3	45	48	-2	6	3	40	-42
3	6	2	247	249	-9	1	3	19	-9	4	2	3	43	43	-1	4	3	93	95	-1	6	3	96	27
4	6	2	81	-83	-8	1	3	53	-57	5	2	3	70	74	0	4	3	58	-58	0	6	3	24	24
5	6	2	87	-87	-7	1	3	17	10	6	2	3	22	-7	1	4	3	125	-125	1	6	3	74	80
6	6	2	104	-100	-6	1	3	36	34	7	2	3	70	-70	2	4	3	41	42	2	6	3	45	-43
7	6	2	145	142	-5	1	3	36	34	8	2	3	39	-27	3	4	3	69	74	3	6	3	44	-48
8	6	2	37	32	-4	1	3	34	-34	9	2	3	47	46	4	4	3	70	-69	4	6	3	73	73
-7	7	2	63	-64	-3	1	3	131	-136	10	2	3	35	25	5	4	3	103	-103	5	6	3	107	108
-6	7	2	23	-17	-2	1	3	73	-68	-10	2	3	57	-51	7	4	3	121	117	6	6	3	18	-23
-5	7	2	116	115	-1	1	3	117	111	-8	3	3	96	94	8	4	3	44	35	7	6	3	115	-106

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHNITE CRYSTAL STRUCTURE

PAGE 4

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
-7	7	3	78	76	-5	0	4	136	-143	7	1	4	23	-20	-3	3	4	13	3	-8	5	4	54	55
-6	7	3	124	-116	-4	0	4	557	-683	8	1	4	302	302	-2	3	4	346	-334	-7	5	4	113	111
-5	7	3	165	-164	-3	0	4	77	-76	9	1	4	151	143	-1	3	4	128	-123	-6	5	4	67	65
-4	7	3	54	52	-2	0	4	316	318	10	1	4	98	-94	0	3	4	210	202	-5	5	4	80	-77
-3	7	3	244	248	-1	0	4	229	220	-11	2	4	198	-192	1	3	4	573	568	-4	5	4	94	-91
-2	7	3	67	69	0	0	4	203	-199	-10	2	4	71	72	2	3	4	27	26	-3	5	4	64	63
-1	7	3	254	-257	0	0	4	374	-375	-9	2	4	189	193	3	3	4	252	-250	-2	5	4	250	251
0	7	3	220	-223	2	0	4	228	-220	-8	2	4	115	115	4	3	4	246	-248	-1	5	4	69	68
1	7	3	102	105	3	0	4	197	206	-7	2	4	363	-372	5	3	4	219	218	0	5	4	131	-130
2	7	3	251	252	4	0	4	147	151	-6	2	4	284	-291	6	3	4	252	250	1	5	4	303	-305
3	7	3	31	28	5	0	4	85	-91	-5	2	4	57	58	7	3	4	27	17	2	5	4	33	33
4	7	3	216	-214	6	0	4	30	30	-4	2	4	543	551	8	3	4	258	-251	3	5	4	178	177
5	7	3	109	-104	7	0	4	44	-41	-3	2	4	22	15	9	3	4	129	-121	4	5	4	165	165
6	7	3	127	122	8	0	4	34	-35	-2	2	4	372	-356	-10	4	4	45	-40	5	5	4	133	-132
-5	8	3	101	99	9	0	4	91	-93	-1	2	4	292	-283	-9	4	4	162	-158	6	5	4	147	-144
-4	8	3	37	-34	10	0	4	64	63	0	2	4	18	23	-8	4	4	88	-85	7	5	4	17	-3
-3	8	3	67	-68	-11	0	4	33	-25	1	2	4	207	212	-7	4	4	223	222	-8	5	4	178	170
-2	8	3	18	19	-10	1	4	31	-25	2	2	4	98	95	-6	4	4	211	209	-8	6	4	76	73
-1	8	3	63	67	-9	1	4	27	18	3	2	4	275	-280	-5	4	4	93	-85	-7	6	4	158	-150
0	8	3	21	8	-8	1	4	23	17	4	2	4	190	-196	-4	4	4	424	-422	-6	6	4	119	-118
1	8	3	25	-26	-7	1	4	137	144	5	2	4	41	-33	-3	4	4	127	-125	-5	6	4	21	-13
2	8	3	35	30	-6	1	4	203	211	6	2	4	52	-46	-2	4	4	121	114	-4	6	4	255	256
3	8	3	19	18	-5	1	4	50	-49	7	2	4	29	-28	-1	4	4	124	121	-3	6	4	65	64
4	8	3	73	72	-4	1	4	255	-259	8	2	4	27	24	0	4	4	81	-84	-2	6	4	23	-16
-2	9	3	43	-44	-3	1	4	24	16	9	2	4	29	23	1	4	4	241	-241	-1	6	4	82	84
-1	9	3	188	193	-2	1	4	462	447	10	2	4	76	-71	2	4	4	149	-151	1	6	4	134	135
0	9	3	160	162	-1	1	4	246	241	-11	3	4	43	40	3	4	4	77	81	2	6	4	72	-74
-1	9	3	72	-78	0	1	4	242	-239	-10	3	4	56	50	4	4	4	160	155	3	6	4	148	-143
-10	0	4	65	185	1	1	4	743	-763	-9	3	4	19	-4	5	4	4	14	-10	4	6	4	92	-86
-9	0	4	253	-257	2	1	4	69	-72	-8	3	4	31	-20	5	4	4	29	26	5	6	4	20	-14
-8	0	4	107	-110	3	1	4	325	334	-7	3	4	114	-113	7	4	4	61	-59	6	6	4	35	30
-7	0	4	341	363	4	1	4	296	309	-6	3	4	127	-128	8	4	4	25	-23	7	7	4	74	-69
-6	0	4	311	322	5	1	4	253	-263	-5	3	4	91	88	9	4	4	45	-39	7	7	4	30	14
-6	0	4	311	322	6	1	4	318	-227	-4	3	4	206	203	-9	5	4	27	15	-6	7	4	30	14

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHRITE CRYSTAL STRUCTURE

PAGE 5

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC		
-5	7	7	4	112	109	0	1	1	5	48	46	-2	3	5	134	132	-4	5	5	97	101	-1	7	5	22	-23
-4	7	7	4	13	45	2	1	1	5	52	-53	-1	3	5	21	17	-3	5	5	23	23	0	7	5	115	-117
-3	7	7	4	56	-53	3	1	1	5	71	-76	0	3	5	106	-107	-2	5	5	122	-126	1	7	5	26	-25
-2	7	7	4	131	-135	4	1	1	5	20	17	1	3	5	32	-34	-1	5	5	19	-3	2	7	5	140	139
-1	7	7	4	47	43	5	1	1	5	38	36	2	3	5	142	145	0	5	5	133	132	3	7	5	123	120
0	7	7	4	107	108	7	1	1	5	45	-45	3	3	5	146	149	1	5	5	38	39	4	7	5	71	-71
1	7	7	4	169	171	-10	2	2	5	73	-69	4	3	5	121	-118	2	5	5	152	-151	5	7	5	145	-141
2	7	7	4	10	-42	-9	2	2	5	49	-48	5	3	5	103	98	3	5	5	163	-163	-5	8	5	211	211
3	7	7	4	57	-59	-8	2	2	5	61	63	7	3	5	103	98	4	5	5	61	61	-4	8	5	227	23
4	7	7	4	76	-73	-7	2	2	5	95	95	8	3	5	63	60	5	5	5	148	143	-3	8	5	227	-230
5	7	7	4	91	90	-6	2	2	5	68	-70	9	3	5	59	-58	7	5	5	140	-132	-2	8	5	180	-184
6	7	7	4	58	58	-5	2	2	5	193	-199	-10	4	5	116	110	8	5	5	79	-69	-1	8	5	98	98
-5	8	8	4	23	15	-4	2	2	5	45	-45	-9	4	5	66	61	-8	5	5	124	119	0	8	5	189	192
-4	8	8	4	117	-119	-3	2	2	5	149	147	-8	4	5	116	-114	-7	5	5	165	159	1	8	5	16	-15
-3	8	8	4	88	-86	-2	2	2	5	111	107	-7	4	5	172	-170	-6	5	5	103	-101	2	8	5	176	-174
-2	8	8	4	39	-36	-1	2	2	5	155	-151	-6	4	5	91	92	-5	5	5	284	-282	3	8	5	83	-83
-1	8	8	4	55	58	0	2	2	5	209	-206	-5	4	5	270	269	-4	5	5	44	-46	4	8	5	85	83
0	8	8	4	51	51	1	2	2	5	32	31	-4	4	5	42	42	-3	5	5	259	257	-1	9	5	48	44
1	8	8	4	66	-69	2	2	2	5	131	134	-3	4	5	261	-258	-2	5	5	196	199	C	9	5	86	85
2	8	8	4	121	-120	3	2	2	5	34	36	-2	4	5	196	-193	-1	5	5	152	-153	-11	0	6	84	83
3	8	8	4	30	-22	4	2	2	5	70	-72	-1	4	5	168	169	0	5	5	250	-253	-9	0	6	164	-170
4	8	8	4	124	122	5	2	2	5	61	-61	0	4	5	265	262	1	5	5	31	31	-8	0	6	237	-247
-2	9	9	4	83	85	6	2	2	5	27	29	1	4	5	46	-46	2	5	5	209	210	-7	0	6	109	112
-1	9	9	4	52	-49	7	2	2	5	45	47	2	4	5	210	-210	3	5	5	82	81	-6	0	6	132	129
0	9	9	4	58	-60	9	2	2	5	22	-14	3	4	5	65	-65	4	5	5	115	-112	-5	0	6	78	75
-1	9	9	4	24	-21	-11	3	3	5	33	31	4	4	5	113	114	5	5	5	125	-118	-4	0	6	592	-598
-10	1	1	5	26	-28	-10	3	3	5	61	60	5	4	5	109	108	6	5	5	20	20	-3	0	6	541	-517
-8	1	1	5	29	28	-9	3	3	5	41	-31	6	4	5	35	-32	7	5	5	72	66	-2	0	6	137	133
-7	1	1	5	12	2	-8	3	3	5	89	-88	7	4	5	71	11	-6	5	5	34	36	0	0	6	882	830
-6	1	1	5	32	-29	-7	3	3	5	23	-22	-9	5	5	18	11	-7	5	5	34	36	0	0	6	82	-65
-4	1	1	5	36	38	-6	3	3	5	48	45	-8	5	5	89	88	-5	5	5	18	12	1	0	6	608	-604
-3	1	1	5	13	15	-5	3	3	5	18	18	-7	5	5	24	19	-4	5	5	62	-65	2	0	6	433	-441
-2	1	1	5	81	-78	-4	3	3	5	113	-117	-6	5	5	58	58	-3	5	5	17	-11	3	0	6	396	404
-1	1	1	5	20	-11	-3	3	3	5	34	-27	-5	5	5	16	-11	-2	5	5	80	80	4	0	6	306	317

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 8

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
-5	3	3	209	199	-9	5	8	79	76	-5	7	8	27	21	-11	2	9	47	-44
-4	3	8	182	-177	-8	5	8	118	115	-4	7	8	47	-48	-10	2	9	46	45
-3	3	8	505	-587	-7	5	8	32	-27	-3	7	8	200	-202	-9	2	9	87	89
-2	3	8	24	-23	-6	5	8	279	-277	-2	7	8	32	-32	-8	2	9	20	-15
-1	3	8	352	341	-5	5	8	142	-139	-1	7	8	36	27	-7	2	9	104	-105
0	3	8	221	217	-4	5	8	90	87	0	7	8	81	80	-6	2	9	54	-55
1	3	8	334	-338	-3	5	8	331	329	1	7	8	106	-110	-5	2	9	61	59
2	3	8	314	-317	-2	5	8	14	9	2	7	8	123	-124	-4	2	9	70	73
3	3	8	32	-32	-1	5	8	206	-205	3	7	8	88	-86	-3	2	9	64	-66
4	3	8	248	248	0	5	8	162	-163	4	7	8	60	61	-2	2	9	125	-121
5	3	8	123	121	1	5	8	166	169	5	7	8	80	73	0	2	9	57	60
6	3	8	51	-54	2	5	8	201	201	-5	8	8	107	-109	1	2	9	15	13
7	3	8	80	-75	3	5	8	30	28	-4	8	8	53	-53	4	2	9	58	63
8	3	8	23	-14	4	5	8	162	-161	-3	8	8	20	16	6	2	9	33	-34
9	3	8	93	-91	5	5	8	135	-128	-2	8	8	168	171	8	2	9	39	39
-10	3	8	41	-36	6	5	8	19	7	-1	8	8	16	7	-11	3	9	61	-59
-11	3	8	180	178	7	5	8	48	42	0	8	8	60	-57	-10	3	9	22	18
-12	3	8	23	-18	-8	6	8	56	-56	1	8	8	107	-111	-9	3	9	45	46
-13	3	8	57	50	-7	6	8	96	-94	3	8	8	51	51	-8	3	9	80	80
-14	3	8	106	-102	-6	6	8	21	13	-11	1	9	16	11	-7	3	9	82	-81
-15	4	8	58	55	-5	6	8	27	23	-10	1	9	42	43	-6	3	9	80	80
-16	4	8	39	-31	-4	6	8	122	126	-9	1	9	33	-33	-5	3	9	54	51
-17	4	8	197	197	-3	6	8	102	-102	-8	1	9	29	27	-4	3	9	239	238
-18	4	8	26	24	-2	6	8	65	-64	-7	1	9	20	13	-3	3	9	39	37
-19	4	8	64	65	-1	6	8	122	-120	-6	1	9	100	99	-2	3	9	145	-142
0	4	8	168	-167	0	6	8	138	139	-5	1	9	35	-35	-1	3	9	143	-142
1	4	8	171	-170	1	6	8	55	51	-4	1	9	33	-34	0	3	9	126	131
2	4	8	24	21	2	6	8	184	184	-3	1	9	27	-24	1	3	9	239	240
3	4	8	204	207	3	6	8	115	-116	-2	1	9	102	97	3	3	9	160	-161
4	4	8	20	21	4	6	8	42	-38	-1	1	9	63	65	4	3	9	72	-75
5	4	8	144	-138	5	6	8	37	-36	0	1	9	32	-44	5	3	9	133	131
6	4	8	102	-95	6	6	8	169	164	1	1	9	74	-83	6	3	9	90	85
7	4	8	80	72	7	7	8	28	18	3	1	9	80	87	8	3	9	98	-87
8	4	8	113	-104	-6	7	8	135	135	6	1	9	58	-60	-10	4	9	75	-74
-9	5	8	209	199	-9	5	8	79	76	-5	7	8	27	21	-11	2	9	47	-44
-10	5	8	182	-177	-8	5	8	118	115	-4	7	8	47	-48	-10	2	9	46	45
-11	5	8	505	-587	-7	5	8	32	-27	-3	7	8	200	-202	-9	2	9	87	89
-12	5	8	24	-23	-6	5	8	279	-277	-2	7	8	32	-32	-8	2	9	20	-15
-13	5	8	352	341	-5	5	8	142	-139	-1	7	8	36	27	-7	2	9	104	-105
-14	5	8	221	217	-4	5	8	90	87	0	7	8	81	80	-6	2	9	54	-55
-15	5	8	334	-338	-3	5	8	331	329	1	7	8	106	-110	-5	2	9	61	59
-16	5	8	314	-317	-2	5	8	14	9	2	7	8	123	-124	-4	2	9	70	73
-17	5	8	32	-32	-1	5	8	206	-205	3	7	8	88	-86	-3	2	9	64	-66
-18	5	8	248	248	0	5	8	162	-163	4	7	8	60	61	-2	2	9	125	-121
-19	5	8	123	121	1	5	8	166	169	5	7	8	80	73	0	2	9	57	60
-20	5	8	51	-54	2	5	8	201	201	-5	8	8	107	-109	1	2	9	15	13
-21	5	8	80	-75	3	5	8	30	28	-4	8	8	53	-53	4	2	9	58	63
-22	5	8	23	-14	4	5	8	162	-161	-3	8	8	20	16	6	2	9	33	-34
-23	5	8	93	-91	5	5	8	135	-128	-2	8	8	168	171	8	2	9	39	39
-24	5	8	41	-36	6	5	8	19	7	-1	8	8	16	7	-11	3	9	61	-59
-25	5	8	180	178	7	5	8	48	42	0	8	8	60	-57	-10	3	9	22	18
-26	5	8	23	-18	-8	6	8	56	-56	1	8	8	107	-111	-9	3	9	45	46
-27	5	8	57	50	-7	6	8	96	-94	3	8	8	51	51	-8	3	9	80	80
-28	5	8	106	-102	-6	6	8	21	13	-11	1	9	16	11	-7	3	9	82	-81
-29	5	8	58	55	-5	6	8	27	23	-10	1	9	42	43	-6	3	9	80	80
-30	5	8	39	-31	-4	6	8	122	126	-9	1	9	33	-33	-5	3	9	54	51
-31	5	8	197	197	-3	6	8	102	-102	-8	1	9	29	27	-4	3	9	239	238
-32	5	8	26	24	-2	6	8	65	-64	-7	1	9	20	13	-3	3	9	39	37
-33	5	8	64	65	-1	6	8	122	-120	-6	1	9	100	99	-2	3	9	145	-142
-34	5	8	168	-167	0	6	8	138	139	-5	1	9	35	-35	-1	3	9	143	-142
-35	5	8	171	-170	1	6	8	55	51	-4	1	9	33	-34	0	3	9	126	131
-36	5	8	24	21	2	6	8	184	184	-3	1	9	27	-24	1	3	9	239	240
-37	5	8	204	207	3	6	8	115	-116	-2	1	9	102	97	3	3	9	160	-161
-38	5	8	20	21	4	6	8	42	-38	-1	1	9	63	65	4	3	9	72	-75
-39	5	8	144	-138	5	6	8	37	-36	0	1	9	32	-44	5	3	9	133	131
-40	5	8	102	-95	6	6	8	169	164	1	1	9	74	-83	6	3	9	90	85
-41	5	8	80	72	7	7	8	28	18	3	1	9	80	87	8	3	9	98	-87
-42	5	8	113	-104	-6	7	8	135	135	6	1	9	58	-60	-10	4	9	75	-74
-43	5	8	209	199	-9	5	8	79	76	-5	7	8	27	21	-11	2	9	47	-44
-44	5	8	182	-177	-8	5	8	118	115	-4	7	8	47	-48	-10	2	9	46	45
-45	5	8	505	-587	-7	5	8	32	-27	-3	7	8	200	-202	-9	2	9	87	89
-46	5	8	24	-23	-6	5	8	279	-277	-2	7	8	32	-32	-8	2	9	20	-15
-47	5	8	352	341	-5	5	8	142	-139	-1	7	8	36	27	-7	2	9	104	-105
-48	5	8	221	217	-4	5	8	90	87	0	7	8	81	80	-6	2	9	54	-55
-49	5	8	334	-338	-3	5	8	331	329	1	7	8	106	-110	-5	2	9	61	59
-50	5	8	314	-317	-2	5	8	14	9	2	7	8	123	-124	-4	2	9	70	73
-51	5	8	32	-32	-1	5	8	206	-205	3	7	8	88	-86	-3	2	9	64	-66
-52	5	8	248	248	0	5	8	162	-163	4	7	8	60	61	-2	2	9	125	-121
-53	5	8	123	121	1	5	8	166	169	5	7	8	80	73	0	2	9	57	60
-54	5	8	51	-54	2	5	8	201	201	-5	8	8	107	-109	1	2	9	15	13
-55	5	8	80	-75	3	5	8	30	28	-4	8	8	53	-53	4	2	9	58	63
-56	5	8	23	-14	4	5	8	162	-161	-3	8	8	20	16	6	2	9	33	-34
-57	5	8	93	-91	5	5	8	135	-128	-2	8	8	168	171	8	2	9	39	39
-58	5	8	41	-36	6	5	8	19	7	-1	8	8	16	7	-11	3	9	61	-59
-59	5	8	180	178	7	5	8	48	42	0	8	8	60	-57	-10	3	9	22	18
-60	5	8	23	-18	-8	6	8	56	-56	1	8	8	107	-111	-9	3	9	45	46
-61	5	8	57	50	-7	6	8	96	-94	3	8	8	51	51	-8	3	9	80	80
-62	5	8	106	-102	-6	6	8	21	13	-11	1	9	16	11	-7	3	9	82	-81
-63	5	8	58	55	-5	6	8	27	23	-10									

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 9

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
7	5	9	57	50	2	8	9	21	12	5	1	10	224	-226	0	3	10	325	325	-1	5	10	158	-158
-9	6	9	184	169	-11	0	10	101	-103	6	1	10	48	41	1	3	10	75	-72	0	5	10	204	-204
-8	6	9	24	3	-10	0	10	240	-249	7	1	10	261	256	2	3	10	204	-202	1	5	10	59	60
-7	6	9	160	-157	-8	0	10	364	377	8	1	10	90	85	3	3	10	123	-123	2	5	10	121	123
-6	6	9	91	-87	-7	0	10	337	345	-11	2	10	147	148	4	3	10	265	269	3	5	10	52	53
-5	6	9	109	107	-6	0	10	291	-296	-10	2	10	181	183	5	3	10	187	181	4	5	10	192	-188
-4	6	9	134	136	-5	0	10	479	-467	-9	2	10	73	74	6	3	10	30	-29	5	5	10	117	-110
-3	6	9	50	-52	-4	0	10	30	29	-8	2	10	390	-399	7	3	10	224	-212	6	5	10	31	29
-2	6	9	144	-148	-3	0	10	520	476	-7	2	10	178	-180	8	3	10	75	-68	-9	6	10	34	34
-1	6	9	20	-7	-2	0	10	147	135	-6	2	10	170	173	-10	4	10	156	-154	-8	6	10	202	-192
0	6	9	73	72	-1	0	10	177	-174	-5	2	10	609	608	-9	4	10	20	22	-7	6	10	76	-74
1	6	9	24	26	0	0	10	426	-416	-4	2	10	117	-114	-8	4	10	258	256	-6	6	10	21	9
2	6	9	42	-42	1	0	10	98	94	-3	2	10	170	-157	-7	4	10	244	243	-5	6	10	263	264
3	6	9	21	17	2	0	10	205	209	-2	2	10	242	-233	-6	4	10	153	-152	-4	6	10	44	-39
4	6	9	70	69	3	0	10	283	291	-1	2	10	438	434	-5	4	10	284	-282	-3	6	10	43	-30
6	6	9	69	-62	4	0	10	103	105	0	2	10	268	272	-3	4	10	298	290	-2	6	10	149	-151
-7	7	9	100	-97	5	0	10	43	47	1	2	10	189	193	-2	4	10	105	107	-1	6	10	140	143
-6	7	9	93	-92	7	0	10	108	105	2	2	10	259	-265	-1	4	10	87	-80	0	6	10	105	108
-5	7	9	82	80	-11	1	10	17	-12	3	2	10	70	-70	0	4	10	281	-281	1	6	10	172	172
-4	7	9	222	220	-10	1	10	67	67	4	2	10	25	28	2	4	10	110	109	2	6	10	110	-111
-2	7	9	201	-204	-9	1	10	40	-39	5	2	10	109	105	3	4	10	227	225	3	6	10	78	-71
-1	7	9	161	-165	-8	1	10	32	31	6	2	10	41	-39	4	4	10	62	-63	4	6	10	35	-28
0	7	9	121	122	-7	1	10	78	76	7	2	10	25	4	5	4	10	25	21	5	6	10	83	79
1	7	9	217	219	-6	1	10	49	-49	8	2	10	34	-30	6	4	10	38	-39	-7	7	10	30	28
2	7	9	32	-34	-5	1	10	92	-84	-11	3	10	31	20	7	4	10	78	69	-6	7	10	76	77
3	7	9	213	-208	-4	1	10	70	65	-10	3	10	70	-67	7	5	10	64	59	-5	7	10	31	-30
4	7	9	102	-96	-3	1	10	395	375	-8	3	10	42	-38	-9	5	10	34	34	-4	7	10	111	-111
-5	8	9	64	-67	-2	1	10	137	131	-7	3	10	54	-51	-8	5	10	46	43	-3	7	10	120	-120
-4	8	9	115	-117	-1	1	10	237	-226	-6	3	10	62	59	-7	5	10	19	-10	-2	7	10	82	80
-3	8	9	28	26	0	1	10	385	-387	-5	3	10	47	44	-6	5	10	74	-70	-1	7	10	89	92
-2	8	9	114	114	1	1	10	81	78	-4	3	10	79	-77	-5	5	10	27	-23	0	7	10	105	107
-1	8	9	39	41	2	1	10	279	281	-3	3	10	311	-299	-4	5	10	103	103	1	7	10	72	-69
0	8	9	34	-36	3	1	10	171	175	-2	3	10	53	-48	-3	5	10	184	179	2	7	10	41	-39
1	8	9	19	-22	4	1	10	302	-306	-1	3	10	196	187	-2	5	10	27	-24	4	7	10	129	129

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 10

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC					
-5	8	10	70	-68	6	2	11	32	34	5	4	11	32	-37	-5	7	11	49	-49	-8	1	12	106	-109
-4	8	10	45	-44	8	2	11	37	-34	6	4	11	67	-64	-4	7	11	65	-63	-7	1	12	358	-357
-3	8	10	54	55	-11	3	11	91	88	-9	5	11	115	111	-3	7	11	22	23	-6	1	12	19	11
-2	8	10	45	42	-9	3	11	75	-73	-8	5	11	28	25	-2	7	11	15	9	-5	1	12	311	300
-1	8	10	43	41	-8	3	11	31	32	-7	5	11	101	-100	-1	7	11	62	-62	-4	1	12	136	131
0	8	10	99	-105	-7	3	11	104	104	-6	5	11	63	-63	0	7	11	30	-24	-3	1	12	300	-292
1	8	10	66	-65	-6	3	11	20	20	-5	5	11	94	93	1	7	11	92	94	-2	1	12	275	-269
-11	1	11	23	-23	-5	3	11	82	-84	-4	5	11	57	57	2	7	11	67	66	-1	1	12	72	-73
-10	1	11	18	-6	-4	3	11	83	-82	-3	5	11	33	-34	3	7	11	65	-62	0	1	12	109	110
-9	1	11	37	40	-3	3	11	36	33	-2	5	11	38	-41	-4	8	11	200	-195	1	1	12	85	84
-7	1	11	33	-31	-2	3	11	22	13	-	5	11	85	89	-3	8	11	114	-115	2	1	12	51	-45
-6	1	11	30	-31	-1	3	11	97	-98	0	5	11	53	55	-2	8	11	156	159	3	1	12	54	52
-5	1	11	45	45	0	3	11	82	-86	1	5	11	101	-100	-1	8	11	178	181	5	1	12	23	7
-2	1	11	30	-30	1	3	11	59	61	2	5	11	83	-83	0	8	11	39	-39	6	1	12	27	-11
-1	1	11	34	36	2	3	11	66	68	3	5	11	48	48	1	8	11	193	-195	7	1	12	111	113
1	1	11	35	-38	2	3	11	54	-57	4	5	11	109	105	-10	0	12	65	-68	-10	2	12	104	108
4	1	11	23	40	4	3	11	81	-81	5	5	11	21	-19	-9	0	12	73	-74	-9	2	12	53	48
6	1	11	26	-23	6	3	11	102	96	6	5	11	113	-104	-8	0	12	137	138	-8	2	12	76	-75
8	1	11	30	30	7	3	11	26	22	8	6	11	135	133	-7	0	12	151	151	-7	2	12	140	-136
-11	2	11	47	-48	-10	4	11	55	51	-7	6	11	103	-102	-5	0	12	399	-379	-6	2	12	87	84
-10	2	11	25	-19	-9	4	11	113	-114	-6	6	11	211	-208	-4	0	12	130	-121	-5	2	12	339	332
-9	2	11	76	77	-8	4	11	107	-110	-5	6	11	22	-14	-3	0	12	218	196	-4	2	12	198	186
-8	2	11	90	90	-7	4	11	91	90	-4	6	11	278	277	-2	0	12	653	619	-3	2	12	209	-196
-7	2	11	45	-43	-6	4	11	220	217	-3	6	11	156	159	-1	0	12	120	-108	-2	2	12	462	-454
-6	2	11	112	-113	-5	4	11	27	22	-2	6	11	170	-170	0	0	12	381	-372	-1	2	12	77	75
-5	2	11	15	-4	-4	4	11	255	-252	-1	6	11	199	-201	1	0	12	182	-183	0	2	12	400	401
-4	2	11	194	190	-3	4	11	151	-152	0	6	11	70	69	2	0	12	409	417	1	2	12	109	111
-3	2	11	116	114	-2	4	11	192	190	1	6	11	240	241	3	0	12	258	262	2	2	12	305	-311
-2	2	11	111	-110	-1	4	11	204	204	2	6	11	73	72	4	0	12	19	-8	3	2	12	284	-285
-1	2	11	120	-123	0	4	11	55	-57	3	6	11	147	-140	5	0	12	342	-346	4	2	12	53	53
0	2	11	26	47	1	4	11	216	-219	4	6	11	116	-109	6	0	12	97	-96	5	2	12	270	264
1	2	11	141	144	2	4	11	50	-50	5	6	11	47	42	7	0	12	125	118	6	2	12	130	125
3	2	11	84	-99	3	4	11	154	153	7	7	11	90	87	7	0	12	302	310	7	2	12	150	-144
4	2	11	62	-65	4	4	11	106	102	-6	7	11	48	48	-10	1	12	176	181	-10	3	12	251	-249

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 11

H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC	H	K	L	FO	FC
-9	3	12	149	-147	-7	5	12	203	-199	-4	8	12	43	41	-2	3	13	74	78	-7	6	13	49	46
-8	3	12	76	76	-6	5	12	29	-20	-3	8	12	35	38	-1	3	13	168	172	-5	6	13	69	-68
-7	3	12	308	307	-5	5	12	147	146	-2	8	12	92	96	1	3	13	94	-99	-4	6	13	45	41
-5	3	12	218	-214	-4	5	12	130	128	-1	8	12	80	-83	2	3	13	50	-52	-3	6	13	126	130
-4	3	12	130	-130	-3	5	12	75	-73	0	8	12	24	-18	4	3	13	52	48	-1	6	13	142	-142
-3	3	12	227	222	-2	5	12	144	-143	-10	1	13	45	-43	6	3	13	37	-34	0	6	13	92	-92
-2	3	12	224	220	-1	5	12	67	-68	-9	1	13	22	22	-10	4	13	40	34	0	6	13	99	98
-1	3	12	96	100	0	5	12	56	57	-8	1	13	42	43	-9	4	13	61	62	2	6	13	132	128
0	3	12	81	-80	1	5	12	138	139	-7	1	13	30	-26	-7	4	13	46	-46	3	6	13	48	-47
1	3	12	84	-79	2	5	12	46	40	-6	1	13	96	-97	-6	4	13	19	15	4	6	13	153	-144
2	3	12	21	15	3	5	12	35	28	-5	1	13	53	-52	-5	4	13	91	94	-7	7	13	21	14
3	3	12	24	-15	4	5	12	51	28	-3	1	13	15	25	-4	4	13	25	-23	-6	7	13	198	194
4	3	12	41	40	5	5	12	33	28	-2	1	13	59	-65	-3	4	13	132	-132	-5	7	13	82	83
5	3	12	21	6	5	6	12	67	-65	-1	1	13	100	-101	-1	4	13	132	125	-4	7	13	155	-154
7	3	12	94	-90	-7	6	12	17	-7	-10	2	13	23	-24	0	4	13	88	91	-3	7	13	178	-182
-10	4	12	67	-64	-6	6	12	112	111	-9	2	13	38	-41	1	4	13	95	-96	-2	7	13	62	61
-9	4	12	37	-32	-5	6	12	157	157	-7	2	13	30	32	2	4	13	136	-135	-1	7	13	185	187
-8	4	12	117	114	-4	6	12	46	46	-5	2	13	68	-70	3	4	13	25	25	0	7	13	108	-106
-7	4	12	55	51	-3	6	12	100	-105	-3	2	13	89	87	4	4	13	130	125	1	7	13	84	-81
-6	4	12	48	-47	-2	6	12	159	-165	-1	2	13	83	-82	6	4	13	94	-86	2	7	13	98	-98
-5	4	12	283	-276	-1	6	12	67	65	0	2	13	55	-60	-9	5	13	111	110	-3	8	13	23	14
-4	4	12	52	-54	0	6	12	138	142	1	2	13	52	59	-8	5	13	192	193	-2	8	13	119	121
-3	4	12	129	124	2	6	12	147	-147	2	2	13	84	90	-7	5	13	37	-35	-1	8	13	71	71
-2	4	12	380	378	3	6	12	123	124	4	2	13	73	-74	-6	5	13	236	-232	-10	0	14	223	228
-1	4	12	112	-109	7	7	12	138	137	6	2	13	57	54	-5	5	13	105	-104	-9	0	14	112	-113
0	4	12	201	-202	-6	7	12	43	43	7	2	13	49	51	-4	5	13	150	148	-8	0	14	163	-161
1	4	12	104	-103	-5	7	12	31	-29	-10	3	13	59	60	-3	5	13	163	165	-7	0	14	124	-115
2	4	12	294	295	-4	7	12	94	-97	-9	3	13	103	-103	-2	5	13	105	-102	-6	0	14	109	-106
3	4	12	169	168	-3	7	12	40	34	-8	3	13	177	-178	-1	5	13	228	-230	-5	0	14	124	115
4	4	12	22	19	-2	7	12	97	101	-7	3	13	18	11	0	5	13	42	-43	-4	0	14	139	136
5	4	12	231	-224	-1	7	12	124	126	-6	3	13	164	163	1	5	13	101	101	-2	0	14	22	-20
6	4	12	73	-67	1	7	12	93	-92	-5	3	13	61	60	2	5	13	70	69	-1	0	14	30	15
-9	5	12	118	117	2	7	12	54	-49	-4	3	13	145	-142	3	5	13	53	-52	0	0	14	60	-55
-8	5	12	31	-24	3	7	12	44	34	-3	3	13	153	-151	4	5	13	62	-60	1	0	14	176	-181

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

OBSERVED				CALCULATED				TORNEBOHMITE CRYSTAL STRUCTURE				PAGE 12												
H	K	L	FO	H	K	L	FC	H	K	L	FO	H	K	L	FO	H	K	L	FO	H	K	L	FC	
2	0	14	28	24	1	2	14	138	138	1	4	14	102	-105	-3	7	14	58	62	-1	3	15	93	95
3	0	14	119	120	2	2	14	91	-94	2	4	14	44	40	-2	7	14	88	94	0	3	15	105	112
5	0	14	220	-222	3	2	14	121	-121	3	4	14	63	62	-1	7	14	69	70	1	3	15	28	-36
6	0	14	98	-97	4	2	14	52	-46	4	4	14	44	-41	0	7	14	105	-109	2	3	15	156	-153
7	0	14	59	55	5	2	14	201	194	5	4	14	185	-177	1	7	14	75	-77	4	3	15	102	99
-10	1	14	140	142	6	2	14	46	39	-9	5	14	87	84	-10	1	15	32	-34	5	3	15	83	80
-9	1	14	175	181	-10	3	14	126	-128	-8	5	14	61	-63	1	15	14	14	6	6	3	15	29	-33
-8	1	14	48	-50	-9	3	14	131	-134	-7	5	14	218	-215	-7	1	15	24	29	-10	4	15	144	-142
-7	1	14	387	-385	-8	3	14	63	62	-6	5	14	66	-65	-6	1	15	32	-32	-9	4	15	19	14
-6	1	14	201	-188	-7	3	14	332	330	-5	5	14	120	116	-5	1	15	41	-41	-8	4	15	136	134
-5	1	14	252	245	-6	3	14	148	145	-4	5	14	240	233	-3	1	15	65	64	-7	4	15	39	38
-4	1	14	512	499	-5	3	14	175	-172	-3	5	14	65	-67	-2	1	15	28	36	-6	4	15	167	-167
-3	1	14	108	-103	-4	3	14	384	-376	-2	5	14	186	-190	2	1	15	55	59	-5	4	15	125	-124
-2	1	14	397	-389	-3	3	14	113	110	-1	5	14	96	-93	4	1	15	25	-37	-4	4	15	59	62
-1	1	14	165	-166	-2	3	14	320	320	0	5	14	179	180	-10	2	15	76	78	-3	4	15	134	131
0	1	14	462	469	-1	3	14	155	156	3	5	14	148	-145	-9	2	15	23	-11	-2	4	15	17	15
1	1	14	342	345	0	3	14	351	-358	4	5	14	65	-64	-8	2	15	91	-91	0	4	15	99	-102
2	1	14	66	-67	1	3	14	262	-262	5	5	14	65	64	-7	2	15	26	-25	1	4	15	37	-34
3	1	14	277	-279	2	3	14	39	48	5	5	14	65	64	-6	2	15	92	96	1	4	15	57	62
4	1	14	75	-72	3	3	14	238	234	-8	6	14	48	-43	-5	2	15	69	68	2	4	15	22	28
5	1	14	139	134	4	3	14	76	75	-7	6	14	35	34	-4	2	15	53	-56	3	4	15	29	-33
6	1	14	95	89	5	3	14	105	-101	-6	6	14	65	64	-3	2	15	92	-92	4	4	15	18	-16
7	1	14	52	-50	5	3	14	87	-79	-5	6	14	19	8	-1	2	15	45	54	5	4	15	28	22
-10	2	14	88	-29	-10	4	14	31	28	-4	6	14	128	-133	1	2	15	37	-57	-9	5	15	41	-39
-9	2	14	190	-194	-9	4	14	177	175	-3	6	14	115	-116	2	2	15	23	-26	-8	5	15	64	62
-8	2	14	48	47	-8	4	14	30	-33	-2	6	14	43	-40	5	2	15	22	-22	-7	5	15	75	76
-7	2	14	155	152	-7	4	14	80	-76	-1	6	14	90	89	-10	3	15	23	25	-6	5	15	88	-86
-6	2	14	54	52	-6	4	14	100	-101	0	6	14	29	28	-9	3	15	40	41	-5	5	15	141	-142
-5	2	14	95	-93	-5	4	14	61	56	1	6	14	43	43	-8	3	15	76	-75	-4	5	15	16	-11
-4	2	14	194	-192	-4	4	14	117	116	2	6	14	89	-92	-7	3	15	66	-69	-3	5	15	186	184
-3	2	14	50	-50	-3	4	14	87	89	-6	6	14	34	-30	-6	3	15	35	37	-2	5	15	97	101
-2	2	14	62	-52	-2	4	14	16	-7	-5	7	14	16	11	-5	3	15	111	110	-1	5	15	125	-125
-1	2	14	15	-13	-1	4	14	51	-51	-4	7	14	26	-32	-3	3	15	158	-156	0	5	15	147	-148
0	2	14	19	-8	0	4	14	67	-70	-4	7	14	101	-104	-2	3	15	99	-104	1	5	15	54	53

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE

PAGE 13

OBSERVED				CALCULATED				STRUCTURE FACTORS FOR TORNEBOHMITE CRYSTAL STRUCTURE																
H	K	L	FO	H	K	L	FO	H	K	L	FO	FC	H	K	L	FO	FC							
2	5	15	196	192	3	0	16	199	-202	5	2	16	60	-54	-3	5	16	62	-62	-1	2	17	48	55
3	5	15	55	61	4	0	16	67	-63	6	2	16	74	-65	-2	5	16	61	-66	0	2	17	125	129
4	5	15	134	-125	5	0	16	19	-3	-9	3	16	59	58	-1	5	16	89	-92	2	2	17	57	-72
-8	6	15	179	-175	6	0	16	93	88	-8	3	16	28	25	0	5	16	107	110	3	2	17	40	-38
-7	6	15	68	-66	-9	1	16	78	-81	-7	3	16	22	-16	1	5	16	68	60	4	2	17	32	43
-6	6	15	137	138	-8	1	16	23	-5	-6	3	16	16	-5	3	5	16	194	-189	2	2	17	50	51
-5	6	15	117	118	-7	1	16	40	29	-5	3	16	99	-100	4	5	16	75	-68	-9	3	17	21	-17
-4	6	15	81	-79	-6	1	16	30	-24	-4	3	16	165	-160	-7	6	16	46	44	-8	3	17	125	126
-3	6	15	157	-158	-5	1	16	67	63	-2	3	16	99	96	-6	6	16	184	188	-7	3	17	53	56
-2	6	15	44	-46	-4	1	16	196	190	-1	3	16	152	152	-5	6	16	98	-98	-5	3	17	78	-78
-1	6	15	81	84	-3	1	16	18	-10	0	3	16	110	-110	-4	6	16	97	-95	-4	3	17	71	75
0	6	15	33	36	-2	1	16	121	-116	1	3	16	147	-149	-3	6	16	104	-106	-3	3	17	65	68
1	6	15	60	-59	-1	1	16	231	-231	3	3	16	233	228	-2	6	16	137	142	-1	3	17	19	-24
2	6	15	34	-31	0	1	16	106	106	4	3	16	112	106	-1	6	16	90	92	0	3	17	32	37
3	6	15	20	17	1	1	16	173	174	5	3	16	73	-68	0	6	16	71	72	1	3	17	62	66
-6	7	15	81	84	2	1	16	33	27	-9	4	16	230	225	1	6	16	136	-141	3	3	17	36	-37
-5	7	15	137	138	3	1	16	282	-280	-8	4	16	123	123	2	6	16	75	-70	5	3	17	72	69
-3	7	15	161	-161	4	1	16	138	-137	-7	4	16	190	-189	-5	7	16	134	-135	-9	4	17	73	-73
-2	7	15	79	-79	5	1	16	71	68	-6	4	16	244	-238	-4	7	16	64	-66	-8	4	17	81	80
-1	7	15	130	131	6	1	16	195	185	-5	4	16	58	55	-3	7	16	63	64	-7	4	17	164	165
0	7	15	141	140	-9	2	16	388	-395	-4	4	16	266	266	-2	7	16	51	50	-5	4	17	190	-186
1	7	15	48	-49	-8	2	16	124	-125	-3	4	16	31	28	0	7	16	92	-95	-4	4	17	77	77
-8	0	16	350	357	-7	2	16	151	150	-2	4	16	203	-202	-7	1	17	37	-36	-3	4	17	140	143
-9	0	16	194	198	-6	2	16	388	380	-1	4	16	246	-252	-6	1	17	56	57	-2	4	17	147	154
-7	0	16	280	-279	-5	2	16	220	-217	1	4	16	126	125	-5	1	17	22	25	-1	4	17	84	-87
-6	0	16	368	-353	-4	2	16	324	-318	2	4	16	105	104	-2	1	17	31	34	0	4	17	211	-208
-5	0	16	114	104	-3	2	16	163	-163	3	4	16	118	-119	5	1	17	20	-6	2	4	17	118	116
-4	0	16	457	429	-2	2	16	365	366	4	4	16	52	-46	-9	2	17	38	36	3	4	17	76	73
-3	0	16	29	20	-1	2	16	194	195	-9	5	16	38	-36	-8	2	17	58	-57	4	4	17	70	-70
-2	0	16	358	-353	0	2	16	26	33	-8	5	16	39	-42	-7	2	17	115	-115	-9	5	17	19	4
-1	0	16	364	-360	1	2	16	272	-275	-7	5	16	28	-24	-5	2	17	105	107	-8	5	17	89	-87
0	0	16	31	23	2	2	16	48	-55	-6	5	16	47	46	-4	2	17	35	44	-7	5	17	95	-92
1	0	16	177	178	3	2	16	94	91	-5	5	16	109	110	-3	2	17	90	-92	-6	5	17	90	88
2	0	16	85	87	4	2	16	90	85	-4	5	16	124	122	-2	2	17	94	-101	-5	5	17	98	97

OBSERVED AND CALCULATED STRUCTURE FACTORS FOR TORNEBOHMITÉ CRYSTAL STRUCTURE

PAGE 14

-1	5	17	22	-14	-7	1	18	157	150	-1	3	18	119	-121	-2	6	18	74	79	0	4	19	61	-61
-3	5	17	59	-60	-6	1	18	317	309	0	3	18	79	-77	-1	6	18	134	137	1	4	19	56	-57
-2	5	17	35	41	-5	1	18	105	105	1	3	18	64	61	0	6	18	41	-45	2	4	19	57	52
-1	5	17	42	44	-4	1	18	269	-268	2	3	18	47	49	1	6	18	110	-107	3	4	19	108	106
1	5	17	43	-44	-3	1	18	225	-227	4	3	18	72	-65	-5	1	19	92	95	-8	5	19	38	-39
2	5	17	21	23	-2	1	18	29	24	-9	4	18	108	109	-4	1	19	43	49	-7	5	19	153	-155
3	5	17	74	69	-1	1	18	143	146	-8	4	18	32	-34	-2	1	19	40	49	-6	5	19	54	-55
-7	6	17	190	-184	0	1	18	57	57	-7	4	18	45	-44	0	1	19	31	49	-5	5	19	213	211
-5	6	17	186	186	1	1	18	94	-94	-6	4	18	210	-208	3	1	19	24	49	-4	5	19	142	145
-4	6	17	66	68	2	1	18	63	-59	-5	4	18	36	30	-8	2	19	54	53	-3	5	19	81	-80
-3	6	17	167	-169	4	1	18	64	58	-4	4	18	61	63	-6	2	19	20	-27	-2	5	19	171	-174
-2	6	17	171	-177	5	1	18	19	12	-3	4	18	216	219	-4	2	19	46	47	0	5	19	138	135
-1	6	17	78	81	-9	2	18	45	-41	-2	4	18	197	-200	-2	2	19	51	-54	1	5	19	62	58
0	6	17	203	206	-8	2	18	73	-71	-1	4	18	106	-107	-1	2	19	37	-41	2	5	19	60	-60
1	6	17	39	37	-7	2	18	129	130	0	4	18	57	-60	0	2	19	37	40	-6	6	19	26	-22
2	6	17	147	-138	-6	2	18	171	165	1	4	18	286	285	1	2	19	36	39	-5	6	19	21	12
-3	7	17	35	35	-5	2	18	127	129	2	4	18	77	73	3	2	19	61	-61	-4	6	19	74	75
-2	7	17	20	-9	-4	2	18	220	-216	3	4	18	20	4	-7	3	19	162	163	-3	6	19	25	25
-1	7	17	19	-19	-3	2	18	177	-175	-8	5	18	182	-181	-6	3	19	25	32	-2	6	19	74	-77
-9	0	18	106	109	-2	2	18	106	105	-7	5	18	44	43	-5	3	19	129	-132	-1	6	19	38	-36
-7	0	18	37	-32	-1	2	18	286	290	-6	5	18	145	146	-4	3	19	116	-120	0	6	19	90	91
-6	0	18	311	-301	0	2	18	29	-25	-5	5	18	75	73	-3	3	19	88	95	-8	0	20	180	-179
-5	0	18	32	-27	1	2	18	248	-248	-4	5	18	152	-152	-2	3	19	135	136	-7	0	20	95	-95
-4	0	18	115	104	2	2	18	211	-212	-3	5	18	164	-166	0	3	19	90	-98	-6	0	20	235	227
-3	0	18	359	350	3	2	18	101	102	-2	5	18	59	-60	1	3	19	35	-38	-5	0	20	134	131
-2	0	18	242	-238	4	2	18	173	166	-1	5	18	59	57	2	3	19	64	67	-4	0	20	51	48
-1	0	18	175	-172	5	2	18	75	70	0	5	18	67	68	3	3	19	52	45	-3	0	20	101	-100
0	0	18	92	-91	-9	3	18	117	118	1	5	18	46	-42	-8	4	19	66	-63	-2	0	20	26	30
1	0	18	402	407	-8	3	18	243	243	2	5	18	70	-67	-7	4	19	23	-18	-1	0	20	49	48
2	0	18	150	151	-7	3	18	113	-112	-7	6	18	114	120	-6	4	19	47	50	2	0	20	72	74
3	0	18	19	-1	-6	3	18	250	-249	-6	6	18	60	61	-4	4	19	57	-60	3	0	20	43	-41
4	0	18	245	-243	-5	3	18	97	-101	-5	6	18	18	13	-3	4	19	24	-24	4	0	20	108	-107
-9	1	18	157	-157	-4	3	18	215	213	-4	6	18	111	-113	-2	4	19	94	95	-8	1	20	290	-287
-8	1	18	290	-289	-3	3	18	191	193	-3	6	18	32	-34	-1	4	19	61	62	-7	1	20	63	-61

