American Mineralogist, Volume 94, pages 1-16, 2009

## AMORPHOUS MATERIALS: PROPERTIES, STRUCTURE, AND DURABILITY<sup>†</sup> The viscosity of hydrous NaAlSi<sub>3</sub>O<sub>8</sub> and granitic melts: Configurational ent opy models

## ALAN G. WHITTINGTON,<sup>1,\*</sup> M. ALI BOUHIFD,<sup>2</sup> AND PASCAL RICHET<sup>3</sup>

<sup>1</sup>Department of Geological Sciences, 101 Geology Building, University of Missouri-Columbia, Columbia, Missouri 65211, U.S.A. <sup>2</sup>Department of Earth Sciences, Oxford University, Parks Road, Oxford OX1 3PR, U.K. <sup>3</sup>Physique des Minéraux et des Magmas, IPGP, 4 place Jussieu, 75252 Paris Cedex 05, France

## ABSTRACT

We used configurational entropy theory to model the viscosity ( $\eta$ ) of hydrous melts of NaAlSi<sub>3</sub>O<sub>8</sub>, haplogranite (SiO<sub>2</sub>-KAlSi<sub>3</sub>O<sub>8</sub>-NaAlSi<sub>3</sub>O<sub>8</sub>), and complex (natural) granite composition from available measurements and recently published configurational heat-capacity data. The equation  $\log \eta = A_e + \frac{1}{2}$  $B_e/TS^{\text{conf}}(T)$ , where  $S^{\text{conf}}$  is configurational entropy, reproduces viscosity data for individual samples as well as or better than the empirical three-parameter TVF equation (defined below), and has the advantage of being based on thermodynamic theory. The variables  $A_e$ ,  $B_e$ , and  $S^{\text{conf}}(T_e)$ , where  $T_e$  is glass transition temperature, were parameterized as a function of water content for compilations of viscosity data for hydrous NaAlSi<sub>3</sub>O<sub>8</sub>, haplogranite, and peraluminous granite melts. With the simplest assumption of ideal mixing between silicate and water components, configurational entropy models with between 4 and 10 fitting parameters reproduce experimentally determined  $\eta$ -T-X<sub>H20</sub> relationships significantly better than previous literature models based on empirical equations. Our preferred configurational entropy models have root-mean-square deviations of 0.26 log units for NaAlSi<sub>3</sub>O<sub>8</sub> (n= 77), 0.16 log units for haplogranite (n = 55), and 0.28 log units for peraluminous granites (n = 79). The best statistical fits to the data sometimes require thermodynamically unlikely variations in  $A_{e_3} B_{e_3}$ and  $S^{\text{conf}}(T_{a})$  as a function of water content, however, such that further calorimetry data are needed to extract accurate thermodynamic information from viscosity data sets for hydrous melts.

Keywords: Viscosity, configurational entropy, water, silicate melt, albite, granite