

data\_vmx1dc\_abs

\_audit\_creation\_method SHELXL-97  
\_chemical\_name\_systematic ;  
?  
;  
\_chemical\_name\_common ?  
\_chemical\_melting\_point ?  
\_chemical\_formula\_moiety ?  
\_chemical\_formula\_sum  
'H B Ca O5 Si'  
\_chemical\_formula\_weight 159.99

loop\_  
\_atom\_type\_symbol  
\_atom\_type\_description  
\_atom\_type\_scat\_dispersion\_real  
\_atom\_type\_scat\_dispersion\_imag  
\_atom\_type\_scat\_source  
'H' 'H' 0.0000 0.0000  
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'  
'B' 'B' 0.0013 0.0007  
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'  
'O' 'O' 0.0106 0.0060  
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'  
'Si' 'Si' 0.0817 0.0704  
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'  
'Ca' 'Ca' 0.2262 0.3064  
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

\_symmetry\_cell\_setting ?  
\_symmetry\_space\_group\_name\_H-M ?

loop\_  
\_symmetry\_equiv\_pos\_as\_xyz  
'x, y, z'  
'-x, y+1/2, -z+1/2'  
'-x, -y, -z'  
'x, -y-1/2, z-1/2'  
  
\_cell\_length\_a 4.83540(10)  
\_cell\_length\_b 7.60820(10)  
\_cell\_length\_c 9.63350(10)  
\_cell\_angle\_alpha 90.00  
\_cell\_angle\_beta 90.1580(10)  
\_cell\_angle\_gamma 90.00  
\_cell\_volume 354.402(9)  
\_cell\_formula\_units\_Z 4  
\_cell\_measurement\_temperature 293(2)  
\_cell\_measurement\_reflns\_used ?  
\_cell\_measurement\_theta\_min ?

\_cell\_measurement\_theta\_max ?  
\_exptl\_crystal\_description ?  
\_exptl\_crystal\_colour ?  
\_exptl\_crystal\_size\_max ?  
\_exptl\_crystal\_size\_mid ?  
\_exptl\_crystal\_size\_min ?  
\_exptl\_crystal\_density\_meas ?  
\_exptl\_crystal\_density\_diffn 2.998  
\_exptl\_crystal\_density\_method 'not measured'  
\_exptl\_crystal\_F\_000 320  
\_exptl\_absorpt\_coefficient\_mu 1.997  
\_exptl\_absorpt\_correction\_type ?  
\_exptl\_absorpt\_correction\_T\_min ?  
\_exptl\_absorpt\_correction\_T\_max ?  
\_exptl\_absorpt\_process\_details ?

\_exptl\_special\_details

;  
?  
;  
  
\_diffn\_ambient\_temperature 293(2)  
\_diffn\_radiation\_wavelength 0.71073  
\_diffn\_radiation\_type MoK\alpha  
\_diffn\_radiation\_source 'fine-focus sealed tube'  
\_diffn\_radiation\_monochromator graphite  
\_diffn\_measurement\_device\_type ?  
\_diffn\_measurement\_method ?  
\_diffn\_detector\_area\_resol\_mean ?  
\_diffn\_standards\_number ?  
\_diffn\_standards\_interval\_count ?  
\_diffn\_standards\_interval\_time ?  
\_diffn\_standards\_decay\_% ?  
\_diffn\_reflns\_number 8499  
\_diffn\_reflns\_av\_R\_equivalents 0.0321  
\_diffn\_reflns\_av\_sigmaI/netI 0.0253  
\_diffn\_reflns\_limit\_h\_min -8  
\_diffn\_reflns\_limit\_h\_max 8  
\_diffn\_reflns\_limit\_k\_min -12  
\_diffn\_reflns\_limit\_k\_max 13  
\_diffn\_reflns\_limit\_l\_min -17  
\_diffn\_reflns\_limit\_l\_max 17  
\_diffn\_reflns\_theta\_min 4.21  
\_diffn\_reflns\_theta\_max 40.08  
\_reflns\_number\_total 2201  
\_reflns\_number\_gt 1932  
\_reflns\_threshold\_expression >2sigma(I)

\_computing\_data\_collection ?  
\_computing\_cell\_refinement ?  
\_computing\_data\_reduction ?  
\_computing\_structure\_solution ?  
\_computing\_structure\_refinement 'SHELXL-97 (Sheldrick, 1997)'

```

_computing_molecular_graphics    ?
_computing_publication_material ?  

  

_refine_special_details  

;  

Refinement of F^2^ against ALL reflections. The weighted R-factor wR and  

goodness of fit S are based on F^2^, conventional R-factors R are based  

on F, with F set to zero for negative F^2^. The threshold expression of  

F^2^ > 2sigma(F^2^) is used only for calculating R-factors(gt) etc. and is  

not relevant to the choice of reflections for refinement. R-factors based  

on F^2^ are statistically about twice as large as those based on F, and R-  

factors based on ALL data will be even larger.  

;  

  

_refine_ls_structure_factor_coef   Fsqd  

_refine_ls_matrix_type           full  

_refine_ls_weighting_scheme     calc  

_refine_ls_weighting_details  

'calc w=1/[s^2^(Fo^2^)+(0.0100P)^2^+0.0000P] where P=(Fo^2^+2Fc^2^)/3'  

_atom_sites_solution_primary     direct  

_atom_sites_solution_secondary   difmap  

_atom_sites_solution_hydrogens   geom  

_refine_ls_hydrogen_treatment    mixed  

_refine_ls_extinction_method    SHELXL  

_refine_ls_extinction_coef      0.075(3)  

_refine_ls_extinction_expression  

'Fc^*^=kFc[1+0.001xFc^2^|I^3^/sin(2|q)]^-1/4^'  

_refine_ls_number_reflns        2201  

_refine_ls_number_parameters    78  

_refine_ls_number_restraints    0  

_refine_ls_R_factor_all         0.0271  

_refine_ls_R_factor_gt          0.0218  

_refine_ls_wR_factor_ref       0.0447  

_refine_ls_wR_factor_gt        0.0442  

_refine_ls_goodness_of_fit_ref  1.446  

_refine_ls_restrained_S_all    1.446  

_refine_ls_shift/su_max         0.001  

_refine_ls_shift/su_mean        0.000  

  

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_U_iso_or_equiv
_atom_site_adp_type
_atom_site_occupancy
_atom_site_symmetry_multiplicity
_atom_site_calc_flag
_atom_site_refinement_flags
_atom_site_disorder_assembly
_atom_site_disorder_group
Ca Ca 0.99168(3) 0.10617(2) 0.336118(16) 0.00643(4) Uani 1 1 d . .

```

Si Si 0.46883(4) 0.26615(3) 0.08438(2) 0.00427(5) Uani 1 1 d . . .  
 B B 0.56839(18) 0.41050(11) 0.34091(9) 0.00516(13) Uani 1 1 d . . .  
 O1 O 0.24051(13) 0.40104(8) 0.03745(6) 0.00739(10) Uani 1 1 d . . .  
 O2 O 0.66987(12) 0.30097(7) 0.45727(6) 0.00633(10) Uani 1 1 d . . .  
 O3 O 0.67508(12) 0.33472(8) 0.21044(6) 0.00621(10) Uani 1 1 d . . .  
 O4 O 0.31509(12) 0.08787(7) 0.14600(6) 0.00696(10) Uani 1 1 d . . .  
 O5 O 0.25854(13) 0.41348(8) 0.33658(7) 0.00738(10) Uani 1 1 d . . .  
 H H 0.207(3) 0.4477(18) 0.4121(17) 0.029(4) Uiso 1 1 d . . .

loop\_

\_atom\_site\_aniso\_label  
 \_atom\_site\_aniso\_U\_11  
 \_atom\_site\_aniso\_U\_22  
 \_atom\_site\_aniso\_U\_33  
 \_atom\_site\_aniso\_U\_23  
 \_atom\_site\_aniso\_U\_13  
 \_atom\_site\_aniso\_U\_12  
 Ca 0.00676(7) 0.00706(6) 0.00548(7) -0.00004(4) 0.00042(4) -0.00045(5)  
 Si 0.00522(9) 0.00423(9) 0.00336(9) -0.00021(6) -0.00002(6) 0.00027(7)  
 B 0.0053(3) 0.0059(3) 0.0042(3) -0.0003(2) 0.0007(2) -0.0002(3)  
 O1 0.0083(2) 0.0071(2) 0.0068(2) -0.00014(18) -0.00082(18) 0.0024(2)  
 O2 0.0071(2) 0.0070(2) 0.0049(2) 0.00189(17) 0.00086(17) 0.00099(19)  
 O3 0.0064(2) 0.0084(2) 0.0039(2) -0.00159(17) 0.00025(17) 0.00030(19)  
 O4 0.0080(2) 0.0043(2) 0.0086(3) 0.00077(17) 0.00239(18) 0.00026(19)  
 O5 0.0055(2) 0.0103(2) 0.0063(2) -0.00092(18) 0.00040(18) 0.0007(2)

\_geom\_special\_details

;

All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

;

loop\_

\_geom\_bond\_atom\_site\_label\_1  
 \_geom\_bond\_atom\_site\_label\_2  
 \_geom\_bond\_distance  
 \_geom\_bond\_site\_symmetry\_2  
 \_geom\_bond\_publ\_flag  
 Ca O1 2.2776(6) 2\_645 ?  
 Ca O1 2.2802(6) 4\_666 ?  
 Ca O4 2.4156(6) 1\_655 ?  
 Ca O2 2.4475(6) . ?  
 Ca O5 2.5238(6) 2\_645 ?  
 Ca O3 2.6121(6) . ?  
 Ca O3 2.6583(6) 2\_745 ?  
 Ca O5 2.6705(6) 1\_655 ?  
 Si O1 1.5728(6) . ?  
 Si O2 1.6468(6) 4\_565 ?  
 Si O3 1.6538(6) . ?  
 Si O4 1.6574(6) . ?

B O4 1.4677(10) 2\_655 ?

B O3 1.4771(10) . ?

B O2 1.4795(10) . ?

B O5 1.4989(11) . ?

O1 Ca 2.2776(6) 2\_655 ?

O1 Ca 2.2802(6) 4\_465 ?

O2 Si 1.6468(6) 4\_566 ?

O3 Ca 2.6583(6) 2\_755 ?

O4 B 1.4677(10) 2\_645 ?

O4 Ca 2.4156(6) 1\_455 ?

O5 Ca 2.5238(6) 2\_655 ?

O5 Ca 2.6705(6) 1\_455 ?

loop\_

\_geom\_angle\_atom\_site\_label\_1

\_geom\_angle\_atom\_site\_label\_2

\_geom\_angle\_atom\_site\_label\_3

\_geom\_angle

\_geom\_angle\_site\_symmetry\_1

\_geom\_angle\_site\_symmetry\_3

\_geom\_angle\_publ\_flag

O1 Ca O1 77.78(2) 2\_645 4\_666 ?

O1 Ca O4 133.40(2) 2\_645 1\_655 ?

O1 Ca O4 107.60(2) 4\_666 1\_655 ?

O1 Ca O2 81.08(2) 2\_645 . ?

O1 Ca O2 86.77(2) 4\_666 . ?

O4 Ca O2 144.12(2) 1\_655 . ?

O1 Ca O5 73.64(2) 2\_645 2\_645 ?

O1 Ca O5 142.90(2) 4\_666 2\_645 ?

O4 Ca O5 77.11(2) 1\_655 2\_645 ?

O2 Ca O5 111.21(2) . 2\_645 ?

O1 Ca O3 114.51(2) 2\_645 . ?

O1 Ca O3 135.84(2) 4\_666 . ?

O4 Ca O3 93.828(19) 1\_655 . ?

O2 Ca O3 56.311(19) . . ?

O5 Ca O3 78.573(19) 2\_645 . ?

O1 Ca O3 81.83(2) 2\_645 2\_745 ?

O1 Ca O3 78.82(2) 4\_666 2\_745 ?

O4 Ca O3 55.481(18) 1\_655 2\_745 ?

O2 Ca O3 159.62(2) . 2\_745 ?

O5 Ca O3 74.169(19) 2\_645 2\_745 ?

O3 Ca O3 142.535(9) . 2\_745 ?

O1 Ca O5 146.92(2) 2\_645 1\_655 ?

O1 Ca O5 76.46(2) 4\_666 1\_655 ?

O4 Ca O5 74.81(2) 1\_655 1\_655 ?

O2 Ca O5 77.106(19) . 1\_655 ?

O5 Ca O5 137.766(14) 2\_645 1\_655 ?

O3 Ca O5 72.572(19) . 1\_655 ?

O3 Ca O5 112.789(19) 2\_745 1\_655 ?

O1 Si O2 113.82(3) . 4\_565 ?

O1 Si O3 115.26(3) . . ?

O2 Si O3 106.73(3) 4\_565 . ?

O1 Si O4 108.77(3) . . ?

O2 Si O4 106.19(3) 4\_565 . ?

O3 Si O4 105.39(3) . . ?  
O4 B O3 107.28(6) 2\_655 . ?  
O4 B O2 109.05(6) 2\_655 . ?  
O3 B O2 108.00(6) . . ?  
O4 B O5 111.84(6) 2\_655 . ?  
O3 B O5 109.49(6) . . ?  
O2 B O5 111.04(6) . . ?  
Si O1 Ca 129.79(3) . 2\_655 ?  
Si O1 Ca 126.67(3) . 4\_465 ?  
Ca O1 Ca 102.22(2) 2\_655 4\_465 ?  
B O2 Si 122.88(5) . 4\_566 ?  
B O2 Ca 100.94(4) . . ?  
Si O2 Ca 122.97(3) 4\_566 . ?  
B O3 Si 122.46(5) . . ?  
B O3 Ca 94.08(4) . . ?  
Si O3 Ca 118.80(3) . . ?  
B O3 Ca 93.07(4) . 2\_755 ?  
Si O3 Ca 119.06(3) . 2\_755 ?  
Ca O3 Ca 103.924(19) . 2\_755 ?  
B O4 Si 127.64(5) 2\_645 . ?  
B O4 Ca 103.71(5) 2\_645 1\_455 ?  
Si O4 Ca 121.09(3) . 1\_455 ?  
B O5 Ca 120.29(5) . 2\_655 ?  
B O5 Ca 118.02(5) . 1\_455 ?  
Ca O5 Ca 106.06(2) 2\_655 1\_455 ?

\_diffn\_measured\_fraction\_theta\_max 0.994  
\_diffn\_reflns\_theta\_full 40.00  
\_diffn\_measured\_fraction\_theta\_full 0.994  
\_refine\_diff\_density\_max 0.616  
\_refine\_diff\_density\_min -0.424  
\_refine\_diff\_density\_rms 0.104