

data_spx2dc_abs

_audit_creation_method SHELXL-97
_chemical_name_systematic
;
?
;
_chemical_name_common ?
_chemical_melting_point ?
_chemical_formula_moiety ?
_chemical_formula_sum
'H B Ca O5 Si'
_chemical_formula_weight 159.99

loop_
_atom_type_symbol
_atom_type_description
_atom_type_scat_dispersion_real
_atom_type_scat_dispersion_imag
_atom_type_scat_source
'H' 'H' 0.0000 0.0000
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'B' 'B' 0.0013 0.0007
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'O' 'O' 0.0106 0.0060
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'Si' 'Si' 0.0817 0.0704
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'Ca' 'Ca' 0.2262 0.3064
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

_symmetry_cell_setting ?
_symmetry_space_group_name_H-M ?

loop_
_symmetry_equiv_pos_as_xyz
'x, y, z'
'-x, y+1/2, -z+1/2'
'-x, -y, -z'
'x, -y-1/2, z-1/2'

_cell_length_a 4.83360(10)
_cell_length_b 7.6076(2)
_cell_length_c 9.6298(2)
_cell_angle_alpha 90.00
_cell_angle_beta 90.165(2)
_cell_angle_gamma 90.00
_cell_volume 354.106(14)
_cell_formula_units_Z 4
_cell_measurement_temperature 293(2)
_cell_measurement_reflns_used ?
_cell_measurement_theta_min ?

_cell_measurement_theta_max ?
_exptl_crystal_description ?
_exptl_crystal_colour ?
_exptl_crystal_size_max ?
_exptl_crystal_size_mid ?
_exptl_crystal_size_min ?
_exptl_crystal_density_meas ?
_exptl_crystal_density_diffn 3.001
_exptl_crystal_density_method 'not measured'
_exptl_crystal_F_000 320
_exptl_absorpt_coefficient_mu 1.999
_exptl_absorpt_correction_type ?
_exptl_absorpt_correction_T_min ?
_exptl_absorpt_correction_T_max ?
_exptl_absorpt_process_details ?

_exptl_special_details
;
?
;

_diffrn_ambient_temperature 293(2)
_diffrn_radiation_wavelength 0.71073
_diffrn_radiation_type MoK\alpha
_diffrn_radiation_source 'fine-focus sealed tube'
_diffrn_radiation_monochromator graphite
_diffrn_measurement_device_type ?
_diffrn_measurement_method ?
_diffrn_detector_area_resol_mean ?
_diffrn_standards_number ?
_diffrn_standards_interval_count ?
_diffrn_standards_interval_time ?
_diffrn_standards_decay_% ?
_diffrn_reflns_number 7902
_diffrn_reflns_av_R_equivalents 0.1225
_diffrn_reflns_av_sigmaI/netI 0.0795
_diffrn_reflns_limit_h_min -7
_diffrn_reflns_limit_h_max 8
_diffrn_reflns_limit_k_min -13
_diffrn_reflns_limit_k_max 13
_diffrn_reflns_limit_l_min -17
_diffrn_reflns_limit_l_max 15
_diffrn_reflns_theta_min 3.41
_diffrn_reflns_theta_max 40.07
_reflns_number_total 2188
_reflns_number_gt 1924
_reflns_threshold_expression >2sigma(I)

_computing_data_collection ?
_computing_cell_refinement ?
_computing_data_reduction ?
_computing_structure_solution ?
_computing_structure_refinement 'SHELXL-97 (Sheldrick, 1997)'

```

_computing_molecular_graphics    ?
_computing_publication_material ?  

  

_refine_special_details  

;  

Refinement of F^2^ against ALL reflections. The weighted R-factor wR and  

goodness of fit S are based on F^2^, conventional R-factors R are based  

on F, with F set to zero for negative F^2^. The threshold expression of  

F^2^ > 2sigma(F^2^) is used only for calculating R-factors(gt) etc. and is  

not relevant to the choice of reflections for refinement. R-factors based  

on F^2^ are statistically about twice as large as those based on F, and R-  

factors based on ALL data will be even larger.  

;  

  

_refine_ls_structure_factor_coef  Fsqd  

_refine_ls_matrix_type          full  

_refine_ls_weighting_scheme    calc  

_refine_ls_weighting_details  

'calc w=1/[s^2^(Fo^2^)+(0.0300P)^2^+0.0000P] where P=(Fo^2^+2Fc^2^)/3'  

_atom_sites_solution_primary   direct  

_atom_sites_solution_secondary difmap  

_atom_sites_solution_hydrogens geom  

_refine_ls_hydrogen_treatment mixed  

_refine_ls_extinction_method  SHELXL  

_refine_ls_extinction_coef    0.002(7)  

_refine_ls_extinction_expression  

'Fc^*^=kFc[1+0.001xFc^2^|I^3^/sin(2|q)]^-1/4^'  

_refine_ls_number_reflns      2188  

_refine_ls_number_parameters  78  

_refine_ls_number_restraints  0  

_refine_ls_R_factor_all       0.0583  

_refine_ls_R_factor_gt        0.0528  

_refine_ls_wR_factor_ref     0.1190  

_refine_ls_wR_factor_gt      0.1174  

_refine_ls_goodness_of_fit_ref 1.522  

_refine_ls_restrained_S_all  1.522  

_refine_ls_shift/su_max      0.000  

_refine_ls_shift/su_mean     0.000  

  

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_U_iso_or_equiv
_atom_site_adp_type
_atom_site_occupancy
_atom_site_symmetry_multiplicity
_atom_site_calc_flag
_atom_site_refinement_flags
_atom_site_disorder_assembly
_atom_site_disorder_group
Ca Ca 0.99172(5) 0.10620(4) 0.33614(3) 0.00620(9) Uani 1 1 d . .

```

Si Si 0.46889(8) 0.26612(5) 0.08436(4) 0.00407(10) Uani 1 1 d . . .
 B B 0.5686(3) 0.4106(2) 0.34082(16) 0.0053(2) Uani 1 1 d . . .
 O1 O 0.2400(2) 0.40078(14) 0.03753(12) 0.00713(18) Uani 1 1 d . . .
 O2 O 0.6697(2) 0.30099(14) 0.45755(11) 0.00605(17) Uani 1 1 d . . .
 O3 O 0.6754(2) 0.33464(15) 0.21044(11) 0.00599(17) Uani 1 1 d . . .
 O4 O 0.3153(2) 0.08795(14) 0.14589(12) 0.00707(19) Uani 1 1 d . . .
 O5 O 0.2586(2) 0.41387(15) 0.33659(12) 0.00727(18) Uani 1 1 d . . .
 H H 0.205(7) 0.449(4) 0.406(5) 0.037(10) Uiso 1 1 d . . .

loop_

_atom_site_aniso_label
 _atom_site_aniso_U_11
 _atom_site_aniso_U_22
 _atom_site_aniso_U_33
 _atom_site_aniso_U_23
 _atom_site_aniso_U_13
 _atom_site_aniso_U_12

Ca 0.00579(13) 0.00661(13) 0.00620(14) 0.00008(7) 0.00002(8) -0.00048(7)
 Si 0.00401(16) 0.00400(16) 0.00419(18) -0.00037(11) -0.00044(11) 0.00051(11)
 B 0.0047(5) 0.0056(5) 0.0057(6) -0.0002(4) -0.0004(4) -0.0002(4)
 O1 0.0069(4) 0.0070(4) 0.0075(4) 0.0001(3) -0.0013(3) 0.0031(3)
 O2 0.0056(4) 0.0071(4) 0.0054(4) 0.0022(3) 0.0004(3) 0.0010(3)
 O3 0.0054(4) 0.0079(4) 0.0047(4) -0.0022(3) -0.0005(3) 0.0002(3)
 O4 0.0069(4) 0.0039(4) 0.0104(5) 0.0010(3) 0.0021(3) -0.0002(3)
 O5 0.0047(4) 0.0097(4) 0.0074(4) -0.0006(3) 0.0002(3) 0.0010(3)

_geom_special_details

;

All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

;

loop_

_geom_bond_atom_site_label_1
 _geom_bond_atom_site_label_2
 _geom_bond_distance
 _geom_bond_site_symmetry_2
 _geom_bond_publ_flag

Ca O1 2.2769(11) 2_645 ?

Ca O1 2.2783(12) 4_666 ?

Ca O4 2.4164(11) 1_655 ?

Ca O2 2.4488(11) . ?

Ca O5 2.5218(12) 2_645 ?

Ca O3 2.6102(11) . ?

Ca O3 2.6575(11) 2_745 ?

Ca O5 2.6725(12) 1_655 ?

Si O1 1.5730(11) . ?

Si O2 1.6433(11) 4_565 ?

Si O3 1.6538(11) . ?

Si O4 1.6558(11) . ?

B O4 1.4665(19) 2_655 ?
B O3 1.4767(19) . ?
B O2 1.4814(19) . ?
B O5 1.4992(19) . ?
O1 Ca 2.2769(11) 2_655 ?
O1 Ca 2.2783(12) 4_465 ?
O2 Si 1.6433(11) 4_566 ?
O3 Ca 2.6575(11) 2_755 ?
O4 B 1.4665(19) 2_645 ?
O4 Ca 2.4164(11) 1_455 ?
O5 Ca 2.5218(12) 2_655 ?
O5 Ca 2.6725(12) 1_455 ?

loop_

_geom_angle_atom_site_label_1
_geom_angle_atom_site_label_2
_geom_angle_atom_site_label_3
_geom_angle
_geom_angle_site_symmetry_1
_geom_angle_site_symmetry_3
_geom_angle_publ_flag
O1 Ca O1 77.75(4) 2_645 4_666 ?
O1 Ca O4 133.32(4) 2_645 1_655 ?
O1 Ca O4 107.67(4) 4_666 1_655 ?
O1 Ca O2 81.14(4) 2_645 . ?
O1 Ca O2 86.65(4) 4_666 . ?
O4 Ca O2 144.15(4) 1_655 . ?
O1 Ca O5 73.65(4) 2_645 2_645 ?
O1 Ca O5 142.98(4) 4_666 2_645 ?
O4 Ca O5 77.11(4) 1_655 2_645 ?
O2 Ca O5 111.20(4) . 2_645 ?
O1 Ca O3 114.61(4) 2_645 . ?
O1 Ca O3 135.78(4) 4_666 . ?
O4 Ca O3 93.80(4) 1_655 . ?
O2 Ca O3 56.37(3) . . ?
O5 Ca O3 78.53(4) 2_645 . ?
O1 Ca O3 81.70(4) 2_645 2_745 ?
O1 Ca O3 78.92(4) 4_666 2_745 ?
O4 Ca O3 55.51(3) 1_655 2_745 ?
O2 Ca O3 159.56(3) . 2_745 ?
O5 Ca O3 74.17(3) 2_645 2_745 ?
O3 Ca O3 142.514(17) . 2_745 ?
O1 Ca O5 146.97(4) 2_645 1_655 ?
O1 Ca O5 76.47(4) 4_666 1_655 ?
O4 Ca O5 74.82(4) 1_655 1_655 ?
O2 Ca O5 77.09(4) . 1_655 ?
O5 Ca O5 137.72(3) 2_645 1_655 ?
O3 Ca O5 72.52(3) . 1_655 ?
O3 Ca O5 112.87(3) 2_745 1_655 ?
O1 Si O2 113.94(6) . 4_565 ?
O1 Si O3 115.32(6) . . ?
O2 Si O3 106.68(6) 4_565 . ?
O1 Si O4 108.67(6) . . ?
O2 Si O4 106.13(6) 4_565 . ?

O3 Si O4 105.40(6) . . ?
O4 B O3 107.44(11) 2_655 . ?
O4 B O2 109.05(12) 2_655 . ?
O3 B O2 108.03(11) . . ?
O4 B O5 111.67(11) 2_655 . ?
O3 B O5 109.59(11) . . ?
O2 B O5 110.94(11) . . ?
Si O1 Ca 129.83(7) . 2_655 ?
Si O1 Ca 126.67(6) . 4_465 ?
Ca O1 Ca 102.25(4) 2_655 4_465 ?
B O2 Si 122.99(9) . 4_566 ?
B O2 Ca 100.78(8) . . ?
Si O2 Ca 122.98(6) 4_566 . ?
B O3 Si 122.40(9) . . ?
B O3 Ca 94.13(8) . . ?
Si O3 Ca 118.82(6) . . ?
B O3 Ca 93.01(8) . 2_755 ?
Si O3 Ca 119.05(6) . 2_755 ?
Ca O3 Ca 103.99(3) . 2_755 ?
B O4 Si 127.77(9) 2_645 . ?
B O4 Ca 103.59(8) 2_645 1_455 ?
Si O4 Ca 121.07(6) . 1_455 ?
B O5 Ca 120.34(9) . 2_655 ?
B O5 Ca 117.90(8) . 1_455 ?
Ca O5 Ca 106.05(4) 2_655 1_455 ?

_diffrn_measured_fraction_theta_max 0.988
_diffrn_reflns_theta_full 40.00
_diffrn_measured_fraction_theta_full 0.988
_refine_diff_density_max 1.162
_refine_diff_density_min -1.181
_refine_diff_density_rms 0.285