

data_lag

_audit_creation_method SHELXL-97
_chemical_name_systematic
;
?
;
_chemical_name_common ?
_chemical_melting_point ?
_chemical_formula_moiety ?
_chemical_formula_sum
'Al Ge2 Li O6'
_chemical_formula_weight 275.10

loop_
_atom_type_symbol
_atom_type_description
_atom_type_scatter_dispersion_real
_atom_type_scatter_dispersion_imag
_atom_type_scatter_source
'Li' 'Li' -0.0003 0.0001
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'O' 'O' 0.0106 0.0060
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'Al' 'Al' 0.0645 0.0514
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
'Ge' 'Ge' 0.1547 1.8001
'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

_symmetry_cell_setting ?
_symmetry_space_group_name_H-M ?

loop_
_symmetry_equiv_pos_as_xyz
'x, y, z'
'-x+1/2, y+1/2, -z+1/2'
'-x, -y, -z'
'x-1/2, -y-1/2, z-1/2'

_cell_length_a 9.9015(11)
_cell_length_b 8.4047(9)
_cell_length_c 5.4036(5)
_cell_angle_alpha 90.00
_cell_angle_beta 110.637(9)
_cell_angle_gamma 90.00
_cell_volume 420.83(8)
_cell_formula_units_Z 4
_cell_measurement_temperature 293(2)
_cell_measurement_reflns_used ?
_cell_measurement_theta_min ?
_cell_measurement_theta_max ?

_exptl_crystal_description ?
 _exptl_crystal_colour ?
 _exptl_crystal_size_max ?
 _exptl_crystal_size_mid ?
 _exptl_crystal_size_min ?
 _exptl_crystal_density_meas ?
 _exptl_crystal_density_diffn 4.342
 _exptl_crystal_density_method 'not measured'
 _exptl_crystal_F_000 512
 _exptl_absorpt_coefficient_mu 14.435
 _exptl_absorpt_correction_type ?
 _exptl_absorpt_correction_T_min ?
 _exptl_absorpt_correction_T_max ?
 _exptl_absorpt_process_details ?

_exptl_special_details

;
 ?
 ;

_diffn_ambient_temperature 293(2)
 _diffn_radiation_wavelength 0.71073
 _diffn_radiation_type MoK\alpha
 _diffn_radiation_source 'fine-focus sealed tube'
 _diffn_radiation_monochromator graphite
 _diffn_measurement_device_type ?
 _diffn_measurement_method ?
 _diffn_detector_area_resol_mean ?
 _diffn_standards_number ?
 _diffn_standards_interval_count ?
 _diffn_standards_interval_time ?
 _diffn_standards_decay_% ?
 _diffn_reflns_number 7346
 _diffn_reflns_av_R_equivalents 0.0373
 _diffn_reflns_av_sigmaI/netI 0.1313
 _diffn_reflns_limit_h_min -18
 _diffn_reflns_limit_h_max 21
 _diffn_reflns_limit_k_min -17
 _diffn_reflns_limit_k_max 18
 _diffn_reflns_limit_l_min -6
 _diffn_reflns_limit_l_max 10
 _diffn_reflns_theta_min 3.85
 _diffn_reflns_theta_max 52.84
 _reflns_number_total 3459
 _reflns_number_gt 1759
 _reflns_threshold_expression >2\sigma(I)

_computing_data_collection ?
 _computing_cell_refinement ?
 _computing_data_reduction ?
 _computing_structure_solution ?
 _computing_structure_refinement 'SHELXL-97 (Sheldrick, 2008)'
 _computing_molecular_graphics ?
 _computing_publication_material ?

```

_refine_special_details
;
Refinement of F^2 against ALL reflections. The weighted R-factor wR and
goodness of fit S are based on F^2, conventional R-factors R are based
on F, with F set to zero for negative F^2. The threshold expression of
 $F^2 > 2\sigma(F^2)$  is used only for calculating R-factors(gt) etc. and is
not relevant to the choice of reflections for refinement. R-factors based
on F^2 are statistically about twice as large as those based on F, and R-
factors based on ALL data will be even larger.
;

_refine_ls_structure_factor_coef Fsqd
_refine_ls_matrix_type full
_refine_ls_weighting_scheme calc
_refine_ls_weighting_details
'calc w=1/[\sigma^2(Fo^2)+(0.0198P)^2+0.0000P] where P=(Fo^2+2Fc^2)/3'
_atom_sites_solution_primary direct
_atom_sites_solution_secondary difmap
_atom_sites_solution_hydrogens geom
_refine_ls_hydrogen_treatment mixed
_refine_ls_extinction_method SHELXL
_refine_ls_extinction_coef 0.0099(4)
_refine_ls_extinction_expression
'Fc^k=kFc[1+0.001xFc^2/l^3/sin(2\q)]^-1/4'
_refine_ls_number_reflns 3459
_refine_ls_number_parameters 92
_refine_ls_number_restraints 0
_refine_ls_R_factor_all 0.0878
_refine_ls_R_factor_gt 0.0325
_refine_ls_wR_factor_ref 0.0606
_refine_ls_wR_factor_gt 0.0551
_refine_ls_goodness_of_fit_ref 0.763
_refine_ls_restrained_S_all 0.763
_refine_ls_shift/su_max 0.001
_refine_ls_shift/su_mean 0.000

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_U_iso_or_equiv
_atom_site_adp_type
_atom_site_occupancy
_atom_site_symmetry_multiplicity
_atom_site_calc_flag
_atom_site_refinement_flags
_atom_site_disorder_assembly
_atom_site_disorder_group
Li1 Li 0.5054(5) 0.2831(6) 0.7996(10) 0.0172(11) Uani 1 1 d . . .
Al3 Al 0.49535(7) 0.08642(8) 0.24667(15) 0.00143(11) Uani 1 1 d . . .
Ge1 Ge 0.29282(3) 0.58271(3) 0.72816(6) 0.00605(6) Uani 1 1 d . . .

```

Ge2 Ge 0.28091(3) 0.38669(3) 0.22912(5) 0.00529(6) Uani 1 1 d . . .
 O1 O 0.10452(16) 0.5728(2) 0.6457(3) 0.0061(3) Uani 1 1 d . . .
 O2 O 0.36111(17) 0.5068(2) 1.0581(3) 0.0086(3) Uani 1 1 d . . .
 O3 O 0.38756(18) 0.7570(2) 0.7989(4) 0.0094(3) Uani 1 1 d . . .
 O4 O 0.35807(17) 0.4358(2) 0.5658(4) 0.0080(3) Uani 1 1 d . . .
 O5 O 0.09141(16) 0.40191(19) 0.1275(3) 0.0069(3) Uani 1 1 d . . .
 O6 O 0.32641(18) 0.1907(2) 0.2155(4) 0.0105(3) Uani 1 1 d . . .

loop_
 _atom_site_aniso_label
 _atom_site_aniso_U_11
 _atom_site_aniso_U_22
 _atom_site_aniso_U_33
 _atom_site_aniso_U_23
 _atom_site_aniso_U_13
 _atom_site_aniso_U_12
 Li1 0.017(2) 0.017(2) 0.014(3) 0.005(2) 0.002(2) 0.0027(19)
 Al3 0.0004(2) 0.0017(3) 0.0023(3) -0.0003(2) 0.0006(2) 0.0003(2)
 Ge1 0.00477(10) 0.00595(10) 0.00831(13) -0.00149(10) 0.00337(9) -0.00147(8)
 Ge2 0.00431(10) 0.00605(10) 0.00586(12) -0.00005(10) 0.00222(9) 0.00064(8)
 O1 0.0040(6) 0.0086(7) 0.0045(8) 0.0005(6) 0.0001(6) -0.0006(6)
 O2 0.0070(7) 0.0118(7) 0.0070(9) 0.0023(7) 0.0023(7) -0.0015(6)
 O3 0.0091(8) 0.0084(7) 0.0106(9) -0.0007(7) 0.0035(7) -0.0036(6)
 O4 0.0080(7) 0.0093(7) 0.0056(8) -0.0021(6) 0.0010(6) 0.0021(6)
 O5 0.0030(6) 0.0093(7) 0.0078(9) -0.0006(6) 0.0014(6) 0.0002(5)
 O6 0.0092(7) 0.0065(7) 0.0192(10) 0.0003(7) 0.0093(7) 0.0023(6)

_geom_special_details
 ;
 All s.u.'s (except the s.u. in the dihedral angle between two l.s. planes)
 are estimated using the full covariance matrix. The cell s.u.'s are taken
 into account individually in the estimation of s.u.'s in distances, angles
 and torsion angles; correlations between s.u.'s in cell parameters are only
 used when they are defined by crystal symmetry. An approximate (isotropic)
 treatment of cell s.u.'s is used for estimating s.u.'s involving l.s. planes.
 ;

loop_
 _geom_bond_atom_site_label_1
 _geom_bond_atom_site_label_2
 _geom_bond_distance
 _geom_bond_site_symmetry_2
 _geom_bond_publ_flag
 Li1 O4 2.018(5) . ?
 Li1 O3 2.079(5) 3_667 ?
 Li1 O5 2.137(5) 4_666 ?
 Li1 O1 2.150(5) 2_546 ?
 Li1 O2 2.177(5) 3_667 ?
 Li1 Ge1 2.860(5) 3_667 ?
 Li1 Al3 2.958(5) 1_556 ?
 Li1 Al3 3.116(5) 3_656 ?
 Li1 Ge1 3.216(5) . ?
 Li1 Ge2 3.218(5) 4_666 ?
 Li1 Ge2 3.220(5) . ?

Al3 O3 1.8269(18) 3_666 ?
 Al3 O6 1.8430(17) . ?
 Al3 O1 1.9165(17) 4_665 ?
 Al3 O5 1.9416(19) 4_666 ?
 Al3 O1 2.0019(18) 2_545 ?
 Al3 O5 2.0041(17) 2_545 ?
 Al3 Li1 2.958(5) 1_554 ?
 Al3 Li1 3.116(5) 3_656 ?
 Ge1 O3 1.7089(17) . ?
 Ge1 O1 1.7595(15) . ?
 Ge1 O4 1.7640(17) . ?
 Ge1 O2 1.7867(18) . ?
 Ge1 Li1 2.860(5) 3_667 ?
 Ge2 O6 1.7158(16) . ?
 Ge2 O2 1.7384(17) 1_554 ?
 Ge2 O4 1.7561(18) . ?
 Ge2 O5 1.7642(15) . ?
 Ge2 Li1 3.218(5) 4_565 ?
 O1 Al3 1.9165(17) 4_566 ?
 O1 Al3 2.0019(18) 2 ?
 O1 Li1 2.150(5) 2_556 ?
 O2 Ge2 1.7384(16) 1_556 ?
 O2 Li1 2.177(5) 3_667 ?
 O3 Al3 1.8269(18) 3_666 ?
 O3 Li1 2.079(5) 3_667 ?
 O5 Al3 1.9416(19) 4_565 ?
 O5 Al3 2.0041(17) 2 ?
 O5 Li1 2.137(5) 4_565 ?

loop_

_geom_angle_atom_site_label_1
 _geom_angle_atom_site_label_2
 _geom_angle_atom_site_label_3
 _geom_angle
 _geom_angle_site_symmetry_1
 _geom_angle_site_symmetry_3
 _geom_angle_publ_flag
 O4 Li1 O3 138.3(3) . 3_667 ?
 O4 Li1 O5 120.1(3) . 4_666 ?
 O3 Li1 O5 101.6(2) 3_667 4_666 ?
 O4 Li1 O1 108.7(2) . 2_546 ?
 O3 Li1 O1 79.62(19) 3_667 2_546 ?
 O5 Li1 O1 76.13(18) 4_666 2_546 ?
 O4 Li1 O2 85.4(2) . 3_667 ?
 O3 Li1 O2 74.94(18) 3_667 3_667 ?
 O5 Li1 O2 117.3(2) 4_666 3_667 ?
 O1 Li1 O2 153.1(3) 2_546 3_667 ?
 O4 Li1 Ge1 115.6(2) . 3_667 ?
 O3 Li1 Ge1 36.31(10) 3_667 3_667 ?
 O5 Li1 Ge1 114.50(19) 4_666 3_667 ?
 O1 Li1 Ge1 115.5(2) 2_546 3_667 ?
 O2 Li1 Ge1 38.63(9) 3_667 3_667 ?
 O4 Li1 Al3 129.9(2) . 1_556 ?
 O3 Li1 Al3 37.69(10) 3_667 1_556 ?

O5 Li1 Al3 94.70(18) 4_666 1_556 ?
 O1 Li1 Al3 42.60(10) 2_546 1_556 ?
 O2 Li1 Al3 110.8(2) 3_667 1_556 ?
 Ge1 Li1 Al3 72.89(12) 3_667 1_556 ?
 O4 Li1 Al3 127.1(2) . 3_656 ?
 O3 Li1 Al3 84.71(17) 3_667 3_656 ?
 O5 Li1 Al3 39.62(10) 4_666 3_656 ?
 O1 Li1 Al3 37.30(9) 2_546 3_656 ?
 O2 Li1 Al3 145.1(2) 3_667 3_656 ?
 Ge1 Li1 Al3 116.47(16) 3_667 3_656 ?
 Al3 Li1 Al3 60.57(10) 1_556 3_656 ?
 O4 Li1 Ge1 29.43(9) . . ?
 O3 Li1 Ge1 108.9(2) 3_667 . ?
 O5 Li1 Ge1 149.5(2) 4_666 . ?
 O1 Li1 Ge1 108.59(18) 2_546 . ?
 O2 Li1 Ge1 72.41(14) 3_667 . ?
 Ge1 Li1 Ge1 91.17(14) 3_667 . ?
 Al3 Li1 Ge1 109.08(15) 1_556 . ?
 Al3 Li1 Ge1 141.98(17) 3_656 . ?
 O4 Li1 Ge2 131.6(2) . 4_666 ?
 O3 Li1 Ge2 84.82(15) 3_667 4_666 ?
 O5 Li1 Ge2 30.82(8) 4_666 4_666 ?
 O1 Li1 Ge2 98.21(18) 2_546 4_666 ?
 O2 Li1 Ge2 88.09(15) 3_667 4_666 ?
 Ge1 Li1 Ge2 85.73(12) 3_667 4_666 ?
 Al3 Li1 Ge2 97.05(13) 1_556 4_666 ?
 Al3 Li1 Ge2 61.74(9) 3_656 4_666 ?
 Ge1 Li1 Ge2 151.52(17) . 4_666 ?
 O4 Li1 Ge2 29.07(9) . . ?
 O3 Li1 Ge2 165.6(2) 3_667 . ?
 O5 Li1 Ge2 91.52(17) 4_666 . ?
 O1 Li1 Ge2 98.16(17) 2_546 . ?
 O2 Li1 Ge2 104.31(18) 3_667 . ?
 Ge1 Li1 Ge2 140.97(18) 3_667 . ?
 Al3 Li1 Ge2 136.26(17) 1_556 . ?
 Al3 Li1 Ge2 102.20(15) 3_656 . ?
 Ge1 Li1 Ge2 58.12(8) . . ?
 Ge2 Li1 Ge2 109.53(15) 4_666 . ?
 O3 Al3 O6 104.11(8) 3_666 . ?
 O3 Al3 O1 90.92(8) 3_666 4_665 ?
 O6 Al3 O1 153.00(9) . 4_665 ?
 O3 Al3 O5 90.55(8) 3_666 4_666 ?
 O6 Al3 O5 99.36(8) . 4_666 ?
 O1 Al3 O5 102.85(7) 4_665 4_666 ?
 O3 Al3 O1 89.91(8) 3_666 2_545 ?
 O6 Al3 O1 80.60(8) . 2_545 ?
 O1 Al3 O1 77.07(8) 4_665 2_545 ?
 O5 Al3 O1 179.54(8) 4_666 2_545 ?
 O3 Al3 O5 166.25(8) 3_666 2_545 ?
 O6 Al3 O5 85.14(7) . 2_545 ?
 O1 Al3 O5 84.75(7) 4_665 2_545 ?
 O5 Al3 O5 77.76(8) 4_666 2_545 ?
 O1 Al3 O5 101.78(8) 2_545 2_545 ?
 O3 Al3 Li1 44.08(11) 3_666 1_554 ?

O6 Al3 Li1 87.14(11) . 1_554 ?
 O1 Al3 Li1 88.46(11) 4_665 1_554 ?
 O5 Al3 Li1 133.83(11) 4_666 1_554 ?
 O1 Al3 Li1 46.63(11) 2_545 1_554 ?
 O5 Al3 Li1 148.36(12) 2_545 1_554 ?
 O3 Al3 Li1 133.68(11) 3_666 3_656 ?
 O6 Al3 Li1 119.38(11) . 3_656 ?
 O1 Al3 Li1 42.83(10) 4_665 3_656 ?
 O5 Al3 Li1 97.00(11) 4_666 3_656 ?
 O1 Al3 Li1 82.63(10) 2_545 3_656 ?
 O5 Al3 Li1 42.85(10) 2_545 3_656 ?
 Li1 Al3 Li1 119.43(10) 1_554 3_656 ?
 O3 Ge1 O1 123.12(8) . . ?
 O3 Ge1 O4 116.30(8) . . ?
 O1 Ge1 O4 112.46(8) . . ?
 O3 Ge1 O2 95.61(8) . . ?
 O1 Ge1 O2 103.33(8) . . ?
 O4 Ge1 O2 99.81(8) . . ?
 O3 Ge1 Li1 46.09(12) . 3_667 ?
 O1 Ge1 Li1 126.11(11) . 3_667 ?
 O4 Ge1 Li1 117.16(11) . 3_667 ?
 O2 Ge1 Li1 49.52(11) . 3_667 ?
 O3 Ge1 Li1 111.10(10) . . ?
 O1 Ge1 Li1 125.69(11) . . ?
 O4 Ge1 Li1 34.19(11) . . ?
 O2 Ge1 Li1 66.38(10) . . ?
 Li1 Ge1 Li1 88.83(14) 3_667 . ?
 O6 Ge2 O2 111.03(8) . 1_554 ?
 O6 Ge2 O4 104.19(9) . . ?
 O2 Ge2 O4 107.50(8) 1_554 . ?
 O6 Ge2 O5 108.83(8) . . ?
 O2 Ge2 O5 115.31(8) 1_554 . ?
 O4 Ge2 O5 109.39(8) . . ?
 O6 Ge2 Li1 79.97(11) . 4_565 ?
 O2 Ge2 Li1 152.34(11) 1_554 4_565 ?
 O4 Ge2 Li1 93.38(10) . 4_565 ?
 O5 Ge2 Li1 38.37(11) . 4_565 ?
 O6 Ge2 Li1 71.25(11) . . ?
 O2 Ge2 Li1 112.06(10) 1_554 . ?
 O4 Ge2 Li1 33.94(11) . . ?
 O5 Ge2 Li1 128.09(10) . . ?
 Li1 Ge2 Li1 95.43(11) 4_565 . ?
 Ge1 O1 Al3 127.92(10) . 4_566 ?
 Ge1 O1 Al3 110.45(8) . 2 ?
 Al3 O1 Al3 102.93(8) 4_566 2 ?
 Ge1 O1 Li1 117.95(16) . 2_556 ?
 Al3 O1 Li1 99.87(15) 4_566 2_556 ?
 Al3 O1 Li1 90.78(15) 2 2_556 ?
 Ge2 O2 Ge1 130.89(10) 1_556 . ?
 Ge2 O2 Li1 128.15(16) 1_556 3_667 ?
 Ge1 O2 Li1 91.85(15) . 3_667 ?
 Ge1 O3 Al3 155.74(12) . 3_666 ?
 Ge1 O3 Li1 97.60(17) . 3_667 ?
 Al3 O3 Li1 98.23(16) 3_666 3_667 ?

Ge2 O4 Ge1 125.30(9) . . ?
Ge2 O4 Li1 116.99(17) . . ?
Ge1 O4 Li1 116.38(17) . . ?
Ge2 O5 Al3 113.80(9) . 4_565 ?
Ge2 O5 Al3 119.12(9) . 2 ?
Al3 O5 Al3 102.24(8) 4_565 2 ?
Ge2 O5 Li1 110.81(16) . 4_565 ?
Al3 O5 Li1 112.12(15) 4_565 4_565 ?
Al3 O5 Li1 97.54(15) 2 4_565 ?
Ge2 O6 Al3 134.13(10) . . ?

_diffn_measured_fraction_theta_max 0.696
_diffn_reflns_theta_full 52.84
_diffn_measured_fraction_theta_full 0.696
_refine_diff_density_max 2.066
_refine_diff_density_min -2.236
_refine_diff_density_rms 0.280