

## Phase transitions and equation of state of forsterite to 90 GPa from single-crystal X-ray diffraction and molecular modeling

GREGORY J. FINKELSTEIN<sup>1,\*</sup>, PRZEMYSŁAW K. DERA<sup>2,3</sup>, SANDRO JAHN<sup>4</sup>, ARTEM R. OGANOV<sup>5</sup>, CHRISTOPHER M. HOLL<sup>1</sup>, YUE MENG<sup>6</sup> AND THOMAS S. DUFFY<sup>1</sup>

<sup>1</sup>Department of Geosciences, Princeton University, Princeton, New Jersey 08544, U.S.A.

<sup>2</sup>GSECARS, University of Chicago, Building 434A, 9700 South Cass Avenue, Argonne, Illinois 60439, U.S.A.

<sup>3</sup>Hawaii Institute of Geophysics and Planetology, School of Ocean and Earth Science and Technology, University of Hawaii, 1680 East West Road (POST Bldg 819E), Honolulu, Hawaii 96822, U.S.A.

<sup>4</sup>GFZ German Research Centre for Geosciences, Telegrafenberg, 14473 Potsdam, Germany

<sup>5</sup>Department of Geosciences and Department of Physics and Astronomy, Stony Brook University, Stony Brook, New York 11794, U.S.A.

<sup>6</sup>HPCAT, Carnegie Institution of Washington, Building 434E, 9700 South Cass Avenue, Argonne, Illinois 60439, U.S.A.

### ABSTRACT

Forsterite,  $\text{Mg}_2\text{SiO}_4$ , the magnesian end-member of the olivine system, is the archetypal example of an orthosilicate structure. We have conducted synchrotron-based single-crystal X-ray diffraction experiments to 90 GPa on synthetic end-member forsterite to study its equation of state and phase transitions. Upon room-temperature compression, the forsterite structure is observed to 48 GPa. By fitting a third-order Birch-Murnaghan equation of state to our compression data, we obtain the zero-pressure isothermal bulk modulus,  $K_{0T} = 130.0(9)$  GPa and its pressure derivative,  $K'_{0T} = 4.12(7)$  for a fixed room-pressure volume,  $V_0 = 290.1(1) \text{ \AA}^3$ , in good agreement with earlier work. At 50 GPa, a phase transition to a new structure (forsterite II) occurs, followed by a second transition to forsterite III at 58 GPa. Forsterite III undergoes no additional phase transitions until at least 90 GPa. There is an  $\sim 4.8\%$  volume reduction between forsterite and forsterite II, and a further  $\sim 4.2\%$  volume reduction between forsterite II and III. On decompression forsterite III remains until as low as 12 GPa, but becomes amorphous at ambient conditions. Using our X-ray diffraction data together with an evolutionary crystal structure prediction algorithm and metadynamics simulations, we find that forsterite II has triclinic space group  $P1$  and forsterite III has orthorhombic space group  $Cmc2_1$ . Both high-pressure phases are metastable. Metadynamics simulations show a stepwise phase transition sequence from 4-coordinated Si in forsterite to mixed tetrahedral and octahedral Si (as in forsterite II), and then fully sixfold-coordinated Si (as in forsterite III), occurring by displacement in  $[001](100)$ . The forsterite III structure is a member of the family of post-spinel structures adopted by compositions such as  $\text{CaFe}_2\text{O}_4$  and  $\text{CaTi}_2\text{O}_4$ .

**Keywords:** Compressibility measurements, olivine, forsterite composition, single-crystal XRD data, synchrotron source, high-pressure olivine phase transition, diamond-anvil cell