

Thermo-compression of pyrope-grossular garnet solid solutions: Non-linear compositional dependence

WEI DU^{1,2,*}, SIMON MARTIN CLARK^{3,4} AND DAVID WALKER¹

¹Lamont-Doherty Earth Observatory and Department of Earth and Environmental Sciences, Columbia University in the City of New York, Palisades, New York 10964, U.S.A.

²Earth-Life Science Institute, Tokyo Institute of Technology, Tokyo 152-8550, Japan

³Department of Earth and Planetary Sciences, Macquarie University, North Ryde, New South Wales 2109, Australia

⁴The Bragg Institute, Australian Nuclear Science and Technology Organization, Locked Bag 2001, Kirrawee DC, New South Wales 2232, Australia

ABSTRACT

Unit-cell parameters of a series of synthetic garnets with the pyrope, grossular, and four intermediate compositions were measured up to about 900 K and to 10 GPa using synchrotron X-ray powder diffraction. Coefficients of thermal expansion of pyrope-grossular garnets are in the range $2.10\text{--}2.74 \times 10^{-5} \text{ K}^{-1}$ and uniformly increase with temperature. Values for the two end-members pyrope and grossular are identical within experimental error $2.74 \pm 0.05 \times 10^{-5} \text{ K}^{-1}$ and $2.73 \pm 0.01 \times 10^{-5} \text{ K}^{-1}$, respectively. Coefficients of thermal expansion for intermediate compositions are smaller than those of end-members and are not linearly dependent on composition. Bulk modulus of grossular is $K_0 = 164.3(1)$ GPa (with K'_0 the pressure derivative of the bulk modulus fixed to 5.92) and bulk modulus of pyrope is $K_0 = 169.2(2)$ GPa (with K'_0 fixed to 4.4) using a third-order Birch-Murnaghan equation of state, which are consistent with previously reported values. The bulk moduli of garnets of intermediate composition are between ~ 155 and ~ 160 GPa, smaller than those of the end-members no matter which K'_0 is chosen. The compositional dependence of bulk modulus resembles the compositional dependence of thermal expansion. Intermediate garnets on this binary have large positive excess volume, which makes them more compressible. We find that excess volumes in the pyrope-grossular series remain relatively large even at high pressure (~ 6 GPa) and temperature (~ 800 K), supporting the observation of crystal exsolution on this garnet join. The curiously “W”-shaped compositional variation of thermal expansion and bulk modulus is anti-correlated with the compositional dependence of microstrain documented in our companion paper (Du et al. in preparation) on the excess volumes in this series of garnets. Minimum thermal expansions and bulk moduli go with maximum microstrains.

Keywords: Pyrope-grossular garnet solid solution, thermal expansion, compressibility, excess volume