

SPECIAL COLLECTION: APATITE: A COMMON MINERAL, UNCOMMONLY VERSATILE

The effects of immobilized carboxylic-functional groups on the dynamics of phase transformation from amorphous to octacalcium phosphate†

YUKI SUGIURA^{1,2,3,*}, KAZUO ONUMA^{2,‡}, MASAHIRO NAGAO¹ AND ATSUSHI YAMAZAKI¹

¹Department of Resources and Environmental Engineering, School of Creative Science and Engineering, Waseda University, 3-1-4, Okubo, Shinjuku, Tokyo, 186-0049 Japan

²National Institute of Advanced Industrial Science and Technology, Central 6, 1-1-1, Higashi, Tsukuba, Ibaraki, 305-8566 Japan

³Department of Biomaterial, Faculty of Dental Science, Kyushu University, 3-1-1, Maidashi, Higashi, Fukuoka, 812-0054 Japan

ABSTRACT

The influence of carboxylic-functional-groups (-COOH) on the phase transformation from amorphous calcium phosphate (ACP) to octacalcium phosphate (OCP) was investigated. 11-Mercaptoundecanoic acid, a carboxylic thiol, was immobilized on gold nanoparticles via covalent bond formation. Time-resolved static light scattering measurements indicated that a structural-reconstruction-type phase transformation occurred with or without the presence of -COOH on the nanoparticles. When it dispersed in calcium phosphate solutions, these nanoparticles inhibited the phase transformation dynamics and also changed the reaction path, forming HPO₄-OH-layer-deficient OCP at pH 6.5 an intermediate phase, which did not show the typical OCP X-ray diffraction (XRD) peak at $2\theta = 4.7^\circ$. This phase was not observed in the reference solution containing gold nanoparticles without bound -COOH. The HPO₄-OH-layer-deficient OCP transformed to conventional OCP gradually, as revealed by XRD, nuclear magnetic resonance, and Raman analyses. Thus, the immobilized -COOH appeared to behave as a negative catalyst, resulting in the formation of the intermediate phase. Such a mechanism partially clarifies complex biomineralization processes, for example teeth enamel and dentin formation, *in vivo*.

Keywords: Biomineralization, calcium phosphate, phase transformation, early tooth formation, intermediate phase