

CHEMISTRY AND MINERALOGY OF EARTH'S MANTLE

Some thermodynamic properties of larnite (β -Ca₂SiO₄) constrained by high T/P experiment and/or theoretical simulation

ZHIHUA XIONG^{1,2}, XI LIU^{1,2,*}, SEAN R. SHIEH³, SICHENG WANG^{1,2}, LINLIN CHANG⁴, JUNJIE TANG^{1,2}, XINGUO HONG⁵, ZHIGANG ZHANG⁶, AND HEJING WANG^{1,2}

¹The Key Laboratory of Orogenic Belts and Crustal Evolution, Ministry of Education of China, Beijing 100871, China

²School of Earth and Space Sciences, Peking University, Beijing 100871, China

³Department of Earth Sciences, University of Western Ontario, London, Ontario N6A 5B7, Canada

⁴College of Earth Science, University of Chinese Academy of Sciences, Beijing 100049, China

⁵Mineral Physics Institute, State University of New York, Stony Brook, New York 11974, U.S.A.

⁶Key Laboratory of Earth and Planetary Physics, Institute of Geology and Geophysics, Chinese Academy of Sciences, Beijing 100029, China

ABSTRACT

Pure larnite (β -Ca₂SiO₄; Lrn) was synthesized at 6 GPa and 1473 K for 6 h by using a cubic press, its thermal expansivity was investigated up to 923 K by using an X-ray powder diffraction technique (ambient P), and its compressibility was investigated up to ~16 GPa by using a diamond-anvil cell coupled with synchrotron X-ray radiation (ambient T). Its volumetric thermal expansion coefficient (α_V) and isothermal bulk modulus (K_T) were constrained as $\alpha_V = 4.24(4) \times 10^{-5} \text{ K}^{-1}$ and $K_T = 103(2) \text{ GPa}$ [the first pressure derivative K'_T obtained as 5.4(4)], respectively. Its compressibility was further studied with the CASTEP code using density functional theory and planewave pseudopotential technique. We obtained the K_T values as 123(3) GPa (LDA; high boundary) and 92(2) GPa (GGA; low boundary), with the values of the K'_T as 4.4(9) and 4.9(5), respectively. The phonon dispersions and vibrational density of states (VDoS) of Lrn were simulated using density functional perturbation theory, and the VDoS was combined with a quasi-harmonic approximation to compute the isobaric heat capacity (C_p) and standard vibrational entropy (S_{298}^0), yielding $C_p = 212.1(1) - 9.69(5) \times 10^2 T^{-0.5} - 4.1(3) \times 10^6 T^{-2} + 5.20(7) \times 10^8 T^{-3} \text{ J/(mol}\cdot\text{K)}$ for the T range of ~298–1000 K and $S_{298}^0 = 129.8(13) \text{ J/(mol}\cdot\text{K)}$. The microscopic and macroscopic thermal Grüneisen parameters of Lrn at 298 K were calculated to be 0.75(6) and 1.80(4), respectively.

Keywords: β -Ca₂SiO₄, compressibility, entropy, heat capacity, larnite, thermal expansivity, thermal Grüneisen parameter, thermodynamic property