

LETTER

**Ca neighbors from XANES spectroscopy: A tool to investigate structure, redox, and nucleation processes in silicate glasses, melts, and crystals**

MARIA RITA CICONI<sup>1,\*</sup>, DOMINIQUE DE LIGNY<sup>1</sup>, TAMIRES M. GALLO<sup>2</sup>, AND DANIEL R. NEUVILLE<sup>3</sup>

<sup>1</sup>Department Werkstoffwissenschaften, Lehrstuhl für Glas und Keramik, Universität Erlangen-Nürnberg, Martensstrasse 5, D-91058 Erlangen, Germany

<sup>2</sup>CNPEM/LNLS, Brazilian Synchrotron Light Laboratory, Campinas, São Paulo 13083-100, Brazil

<sup>3</sup>Institut de Physique du Globe de Paris, CNRS, Géomatériaux, Sorbonne Paris Cité, 1, rue Jussieu, F-75238 Paris, France

ABSTRACT

In this study, Ca *K*-edge X-ray absorption spectroscopy (XAS) has been employed to study the Ca structural role in a set of silicate glasses. For the first time the accurate analysis of the Ca pre-edge peak has been performed, providing information about the different Ca local environments, and on its structural role.

This approach was tested on Ca-aluminosilicate glasses (CAS system) with constant SiO<sub>2</sub> content (50 and 76 mol%), ranging from percalcic to peraluminous domains. In alkali-earth aluminosilicate glasses Al and Si are network formers in a large range of compositions, whereas calcium should act either as network modifier and charge compensator. The results obtained show a different Ca behavior as a function of Al content, which in turn is related to the Al local environment. For example, we observe changes in the pre-edge peak centroid energies depending on the changes in the role of Ca as a network modifier (Al = 0 mol%) to charge compensator (aluminosilicate join) to a more complex role in the peraluminous domain, depending on the fraction of <sup>[4],[5],[6]</sup>Al. This approach was further applied to study Fe-bearing glasses and, a diopside (CaMgSi<sub>2</sub>O<sub>6</sub>) composition at different temperatures. It was possible to correlate the variations occurring in the Ca pre-edge peak centroid positions with both redox state and crystal nucleation mechanism.

**Keywords:** Calcium, XAS, glass structure, redox, nucleation