

Thermodynamics and crystal chemistry of rhomboclase, $(\text{H}_5\text{O}_2)\text{Fe}(\text{SO}_4)_2 \cdot 2\text{H}_2\text{O}$, and the phase $(\text{H}_3\text{O})\text{Fe}(\text{SO}_4)_2$ and implications for acid mine drainage

JURAJ MAJZLAN^{1,*}, KLAUS-DIETER GREVEL¹, BORIS KIEFER², ULLA GRO NIELSEN³,
ELISABETH GRUBE^{3,†}, EDGAR DACHS⁴, ARTUR BENISEK⁴, MARY ANNE WHITE⁵, AND MICHEL B. JOHNSON⁵

¹Institute of Geosciences, Friedrich-Schiller-University, Carl-Zeiss Promenade 10, D-07745 Jena, Germany

²Department of Physics, 1255 N. Horseshoe Drive, New Mexico State University, Las Cruces 88003, New Mexico, U.S.A.

³Department of Physics, Chemistry, and Pharmacy, University of Southern Denmark, Campusvej 55, 5230 Odense M, Denmark

⁴Department of Chemistry and Physics of Materials, Division Mineralogy, University of Salzburg, Hellbrunnerstrasse 34, A-5020 Salzburg, Austria

⁵Department of Chemistry and Institute for Research in Materials, Dalhousie University, Halifax, Nova Scotia B3H 4R2, Canada

ABSTRACT

The system Fe_2O_3 - SO_3 - H_2O contains the most important minerals of acid mine drainage (AMD), iron oxides, and iron sulfates. For geochemical modeling of the AMD systems, reliable thermodynamic data for these phases are needed. In this work, we have determined thermodynamic data for the most acidic sulfates rhomboclase [$(\text{H}_5\text{O}_2)\text{Fe}(\text{SO}_4)_2 \cdot 2\text{H}_2\text{O}$ or $(\text{H}_3\text{O})\text{Fe}(\text{SO}_4)_2 \cdot 3\text{H}_2\text{O}$] and the phase $(\text{H}_3\text{O})\text{Fe}(\text{SO}_4)_2$. The actual compositions of the studied phases are $(\text{H}_3\text{O})_{1.34}\text{Fe}(\text{SO}_4)_{2.17}(\text{H}_2\text{O})_{3.06}$ (molecular mass of 344.919 g/mol) and $(\text{H}_3\text{O})_{1.34}\text{Fe}(\text{SO}_4)_{2.17}$ (289.792 g/mol). Structural details for both phases were refined from synchrotron powder X-ray diffraction data. Enthalpies of formation were determined by acid-solution calorimetry. Low-temperature heat capacity was measured for rhomboclase by relaxation calorimetry but a critical analysis of entropies for several oxysalts showed that these data are too high. Entropies for both phases were estimated from a Kopp-rule algorithm. The enthalpies of formation and entropies were combined with previously published temperature-relative humidity brackets to generate an internally consistent thermodynamic data set for rhomboclase: $\Delta_f H^\circ = -3202.03$ kJ/mol, $S^\circ = 378.7$ J/(mol·K); and for $(\text{H}_3\text{O})_{1.34}\text{Fe}(\text{SO}_4)_{2.17}$: $\Delta_f H^\circ = -2276.25$ kJ/mol, $S^\circ = 253.2$ J/(mol·K). Solubility experiments at room temperature and at $T = 4$ °C agree well with previously reported data in the system Fe_2O_3 - SO_3 - H_2O . An inspection of the extended Pitzer model for Fe^{3+} - SO_4 solutions shows that this model reproduces the general topology of the phase diagram, but the position of the calculated solubility curves deviates substantially from the experimental data. Solid-state ^2H MAS NMR spectra on deuterated rhomboclase show two isotropic chemical shifts $\delta_{\text{iso}}(^2\text{H})$ of 8 ± 1 and 228 ± 1 ppm, assigned to D_2O_2 and Fe-OD_2 groups, respectively. Canonical ensemble (NVT) molecular dynamics simulations for $(\text{H}_3\text{O})\text{Fe}(\text{SO}_4)_2$ at $T = 300$ K showed that the H_3O^+ groups maintain their trigonal pyramidal geometry and perform different types of motion.

Keywords: Rhomboclase, acid mine drainage, thermodynamics, hydrogen mobility