

Electron microprobe technique for the determination of iron oxidation state in silicate glasses

**CHAO ZHANG¹, RENAT R. ALMEEV^{1,*}, ERY C. HUGHES², ALEXANDER A. BORISOV³, ERIC P. WOLFF¹,
HEIDI E. HÖFER⁴, ROMAN E. BOTCHARNIKOV⁵, AND JÜRGEN KOEPKE¹**

¹Leibniz Universität Hannover, Institut für Mineralogie, Callinstrasse 3, D-30167, Hannover, Germany

²School of Earth Sciences, University of Bristol, Bristol BS8 1RJ, U.K.

³Institute of Geology of Ore Deposits, Petrography, Mineralogy, and Geochemistry, Russian Academy of Sciences, Staromonetny 35,
109017 Moscow, Russia

⁴Institut für Geowissenschaften, Mineralogie, Johann Wolfgang Goethe-Universität, Altenhöferallee 1, D-60438 Frankfurt am Main, Germany

⁵Institute für Geowissenschaften, Johannes Gutenberg Universität Mainz, J-J-Becher-Weg 21, D-55128 Mainz, Germany

ABSTRACT

We present a new calibration for the determination of the iron oxidation state in silicate glasses by electron probe microanalysis (EPMA) with the “flank method.” This method is based on the changes in both intensity and wavelength of the *FeLa* and *FeLβ* X-ray emission lines with iron oxidation state. The flank method utilizes the maximum difference for the *FeLa* and *FeLβ* spectra observed at the peak flanks between different standard materials, which quantitatively correlates with the Fe²⁺ content. Provided that this correlation is calibrated on reference materials, the Fe²⁺/ΣFe ratio can be determined for samples with known total Fe content. Two synthetic Fe-rich ferric and ferrous garnet end-members, i.e., andradite and almandine, were used to identify the *FeLa* and *FeLβ* flank method measuring positions that were then applied to the measurement of a variety of silicate glasses with known Fe²⁺/ΣFe ratio (ranging from 0.2 to 1.0). The measured intensity ratio of *FeLβ* over *FeLa* at these flank positions (*Lβ/Lα*) is a linear function of the Fe²⁺ content (in wt%). A single linear trend can be established for both garnets and silicate glasses with 4–18 wt% FeO_T (total iron expressed as FeO). In glasses with up to 18 wt% FeO_T and 15 wt% TiO₂, no systematic compositional (matrix) effects were observed. A possible influence of Ti on the Fe²⁺ determination has only been observed in one high-Ti glass with ~25 wt% TiO₂, a content that is not typical for natural terrestrial silicate melts. The accuracy of the Fe²⁺/ΣFe determination, which depends on both the Fe²⁺ content determined with the flank method and on the total Fe content, is estimated to be within ±0.1 for silicate glasses with FeO_T > 5 wt% and within ±0.3 for silicate glasses with low FeO_T ≤ 5 wt%. The application of the flank method on silicate glasses requires minimization of the EPMA beam damage that can be successfully achieved by continuous movement of the sample stage under the electron beam during analysis, e.g., with a speed of 2 μm/s.

Keywords: Microprobe, ferric-ferrous ratio, silicate glasses, redox state, flank method, pillow glasses