

LETTER

Synthesis and crystal structure of Pb-dominant tourmaline

OLEG S. VERESHCHAGIN<sup>1,\*</sup>, BERND WUNDER<sup>2</sup>, SERGEY N. BRITVIN<sup>1,3</sup>, OLGA V. FRANK-KAMENETSKAYA<sup>1</sup>,  
FRANZISKA D.H. WILKE<sup>2</sup>, NATALIA S. VLASENKO<sup>4</sup>, AND VLADIMIR V. SHILOVSKIKH<sup>4,†</sup>

<sup>1</sup>Institute of Earth Sciences, Saint Petersburg State University, Universitetskaya Nab. 7/9, 199034 St. Petersburg, Russia

<sup>2</sup>GFZ German Research Centre for Geosciences, 14473 Potsdam, Germany

<sup>3</sup>Nanomaterials Research Center, Kola Science Center of Russian Academy of Sciences, Fersman Str. 14, 184209 Apatity, Murmansk Region, Russia

<sup>4</sup>Centre for Geo-Environmental Research and Modelling (Geomodel), Saint Petersburg State University, Ulyanovskaya Str. 1, 198504 St. Petersburg, Russia

ABSTRACT

Pb-dominant tourmaline was synthesized at 700 °C and 200 MPa in two hydrothermal experiments in the system MgO-Al<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>-PbO-H<sub>2</sub>O (run OV-4-2) and MgO-Al<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>-PbO-CaO-Na<sub>2</sub>O-H<sub>2</sub>O (run OV-5-3), respectively. Run OV-4-2 forms needle-like (lengths up to 7 μm), lead-rich (up to 13.3 wt% PbO) crystals that are chemically homogeneous. Run OV-5-3 forms columnar (lengths up to 400 μm) crystals that are chemically zoned (Pb-rich cores, up to 14.7 wt% PbO, and Pb-poor rims, ~2 wt% PbO). Additional phases that form in trace amounts are Pb-feldspar, quartz, diaspore (in OV-4-2) and talc, mullite, spinel, quartz (in OV-5-3). Single-crystal structure refinement (SREF) of the central zone of Pb-rich tourmaline from the run OV-5-3 proves that Pb<sup>2+</sup> cations occupy the X-site in the tourmaline structure. The unit-cell parameters of the studied tourmaline are:  $a = 15.9508(10)$  Å,  $c = 7.2024(6)$  Å. The formula derived from SREF results of this Pb-rich tourmaline is  ${}^X(\text{Pb}_{0.63}\square_{0.37}){}^Y(\text{Al}_{1.71}\text{Mg}_{1.29}){}^Z(\text{Al}_{5.04}\text{Mg}_{0.96}){}^T(\text{Si}_{6.00}\text{O}_{18})(\text{BO}_3)_3{}^V(\text{OH})_{3.00}{}^W(\text{O}_{1.00})$ . Accordingly, the studied crystal is a Pb-analog of hypothetical “oxy-uvite,” and thus referred to here as “Pb-oxy-uvite.” Similarities between (1) the paragenesis of Minh Tien tourmaline, and (2) the final experimental phase assemblages observed here, indicate comparable *P-T* conditions of formation.

**Keywords:** Tourmaline, Pb, crystal chemistry, lead end-member, synthesis