

Phase relationships in the system ZnS-CuInS₂: Insights from a nanoscale study of indium-bearing sphalerite

JING XU^{1,2,*}, CRISTIANA L. CIOBANU², NIGEL J. COOK^{2,†}, ASHLEY SLATTERY³, XIAOFENG LI^{1,4,5}, AND ALKIVIADIS KONTONIKAS-CHAROS²

¹Key Laboratory of Mineral Resources, Institute of Geology and Geophysics, Chinese Academy of Sciences, Beijing 100029, China

²School of Chemical Engineering and Advanced Materials, The University of Adelaide, South Australia 5005, Australia

³Adelaide Microscopy, The University of Adelaide, South Australia 5005, Australia

⁴Institutions of Earth Science, Chinese Academy of Sciences, Beijing 100029, China

⁵College of Earth and Planetary Sciences, University of Chinese Academy of Sciences, Beijing 100049, China

ABSTRACT

Micrometer- to submicrometer-scale indium-rich domains are preserved within sphalerite included in hornfels-hosted pyrrhotite from the Dulong polymetallic skarn, Yunnan, China. The nano-mineralogy of the ZnS-bearing blebs was investigated using scanning transmission electron microscopy on thinned foils extracted in situ from pyrrhotite. Indium incorporation in sphalerite occurs via the coupled substitution $2\text{Zn}^{2+} \leftrightarrow \text{Cu}^+ + \text{In}^{3+}$; the results thus allow insights into phase relationships in the system ZnS-CuInS₂ in which solubility limits are debated with respect to a cubic to tetragonal phase transition. The highest concentrations of In are measured in basket-weave domains from the smallest ZnS blebs or from un-patterned areas in coarser, irregular ZnS inclusions in pyrrhotite. Indium-rich domains contain 17–49 mol% CuInS₂, whereas In-poor sphalerite contains <5 mol% CuInS₂. Atomic-scale metal ordering observed in In-(Cu)-rich ZnS domains was modeled as mixed sites in a cubic structure with $P\bar{4}3m$ symmetry and empirical formula $[(\text{Cu},\text{In},\text{Zn})_3(\text{Zn}_{0.5}\text{Fe}_{0.5})]_4\text{S}_4$. This sphalerite modification is distinct from the cubic-tetragonal phase transition reported elsewhere for analogous, synthetic phases with abundant planar defects. The Zn_{1.5}Fe_{0.5}CuInS₄ nanophase described here potentially represents a Fe-bearing polymorph of Zn₂CuInS₄, considered as an end-member in the sakuraiite solid-solution series. At ≤50 mol% CuInS₂ in the ZnS-CuInS₂ system, incorporation of In via coupled In+Cu substitution is promoted within a cubic ZnS phase with lower symmetry than sphalerite rather than into the spatially coexisting chalcopyrite of tetragonal symmetry. Solid-state diffusion accounts for phase re-equilibration resulting in the basket-weave textures typical of In-(Cu)-rich domains in the smallest blebs, whereas fluid percolation assists grain coarsening in the irregular inclusions. The results show evidence for the existence of a more complex phase transition than previously recognized from experimental studies, and, intriguingly, also to a potential eutectic in the system ZnS-CuInS₂. Pyrrhotite-bearing hornfels in skarns may concentrate In and other critical metals hosted in sphalerite and related sulfides due to the efficient scavenging from fluid by these minerals and the subsequent preservation of those included phases by sealing within the pyrrhotite matrix.

Keywords: Sphalerite, indium, system ZnS-CuInS₂, HAADF STEM