

Sound velocities of iron-nickel (Fe₉₀Ni₁₀) alloy up to 8 GPa and 773 K: The effect of nickel on the elastic properties of bcc-iron at high *P-T*

SIHENG WANG^{1,*}, NAO CAI^{2,†}, XINTONG QI², SIBO CHEN¹, AND BAOSHENG LI^{1,2}

¹Department of Geosciences, Stony Brook University, Stony Brook, New York 11794, U.S.A.

²Mineral Physics Institute, Stony Brook University, Stony Brook, New York 11794, U.S.A.

ABSTRACT

Sound velocities of iron and iron-based alloys at high pressure and high temperature are crucial for understanding the composition and structure of Earth's and other telluric planetary cores. In this study, we performed ultrasonic interferometric measurements of both compressional (v_p) and shear (v_s) velocities on a polycrystalline body-centered-cubic (bcc)-Fe₉₀Ni₁₀ up to 8 GPa and 773 K. The elastic moduli and their pressure and temperature derivatives are derived from least-square fits to third-order finite strain equations, yielding $K_{S0} = 154.2(8)$ GPa, $G_0 = 73.2(2)$ GPa, $K'_{S0} = 4.6(2)$, $G'_0 = 1.5(1)$, $\partial K_s/\partial T = -0.028(1)$ GPa/K, and $\partial G/\partial T = -0.023(1)$ GPa/K. A comparison with literature data on bcc-Fe suggests that nickel not only decreases both P and S wave velocities but also weakens the temperature effects on the elastic moduli of Fe-Ni alloys.

Keywords: Fe-Ni alloy, sound velocity, high pressure and high temperature, ultrasonic interferometry