

## CO<sub>2</sub> quantification in silicate glasses using $\mu$ -ATR FTIR spectroscopy

MAXIMILIAN SCHANOFSKI<sup>1,\*</sup>, LENNART KOCH<sup>1</sup>, AND BURKHARD C. SCHMIDT<sup>1</sup>

<sup>1</sup>Abteilung Experimentelle und Angewandte Mineralogie, Georg August Universität Göttingen, Goldschmidtstrasse 1, 37077 Göttingen, Germany

### ABSTRACT

A new method for measurements of high-CO<sub>2</sub> concentrations in silicate glasses was established using micro-attenuated total reflectance ( $\mu$ -ATR) Fourier transform infrared (FTIR) spectroscopy in the mid-IR (MIR) region. We studied two glass/melt compositions, namely leucitite and granite, to cover samples in which CO<sub>2</sub> is dissolved as carbonate ions (CO<sub>3</sub><sup>2-</sup>) or as CO<sub>2</sub> molecules (CO<sub>2</sub><sup>mol</sup>). In the leucitite glasses a carbonate absorption doublet with maxima at 1510 and 1430 cm<sup>-1</sup> has shown to clearly separate from aluminosilicate lattice vibrations at lower wavenumbers. Due to the lower sensitivity of the  $\mu$ -ATR method, we were able to measure high-CO<sub>2</sub> contents ( $c_{\text{CO}_2} > 0.5$  wt%) in experimental silicate glasses that would only be measurable with great difficulties using established transmission MIR measurements due to detector linearity limit effects even with very thin sample wafers. The peak heights of the 1430 cm<sup>-1</sup> ATR band ( $A_{1430}$ ), normalized to the integral of the T-O lattice vibrations (T = Si, Al, Fe) at about 930 cm<sup>-1</sup> ( $\text{Int}_{930}$ ) show a linear trend with CO<sub>2</sub> contents in the range 0.2–4.3 wt%, yielding a linear correlation with  $c_{\text{CO}_2}$  (wt%) =  $0.4394 \pm 0.006 \cdot A_{1430} \cdot 10000 / \text{Int}_{930}$ . The normalization of the CO<sub>2</sub> related band to a lattice vibration accounts for variations in the quality of contact between ATR crystal and sample, which has a direct effect on signal intensity.

In granitic glasses, where CO<sub>2</sub> is dissolved as CO<sub>2</sub><sup>mol</sup> only, the asymmetric stretching vibration at 2350 cm<sup>-1</sup> overlaps with the signal of atmospheric, gaseous CO<sub>2</sub>. As the ATR signal of dissolved CO<sub>2</sub> is very weak, the atmospheric signal may dominate the spectrum. Since the absorbance spectrum is calculated by division of the single-channel sample spectrum by a single-channel reference spectrum measured in air, keeping the laboratory and spectrometer atmosphere as constant as possible during spectral acquisition can resolve the problem. Nonetheless, a procedure to subtract the signal of remaining atmospheric CO<sub>2</sub> may still be required for the spectral evaluation. We studied a series of 5 granitic glasses with CO<sub>2</sub><sup>mol</sup> contents of 0.08 to 0.27 wt% and found an excellent linear relation between CO<sub>2</sub> concentration and lattice vibration normalized ATR intensity of the 2350 cm<sup>-1</sup> band:  $c_{\text{CO}_2}$  (wt%) =  $0.2632 \pm 0.0016 \cdot A_{2350} \cdot 10000 / \text{Int}_{990}$ . Although the CO<sub>2</sub><sup>mol</sup> concentrations in our granitic glass series can still be analyzed without major difficulties by conventional transmission IR spectroscopy, our data demonstrate the potential of the ATR method for samples with higher CO<sub>2</sub> contents or for samples where a high spatial resolution is required (melt inclusions, vesicular or partially crystallized glasses). The lower limits of the ATR method are approximately 0.2 wt% CO<sub>2</sub> dissolved as carbonate groups or 0.1 wt% CO<sub>2</sub> (or slightly less) dissolved in molecular form.

**Keywords:** ATR-micro spectroscopy, ATR FTIR, silicate glasses, carbon dioxide, CO<sub>2</sub> quantification, CO<sub>2</sub>