

Structural phase transition near 825 K in titanite: Evidence from infrared spectroscopic observations

MING ZHANG,¹ EKHARD SALJE,^{1,2} AND ULRICH BISMAYER^{3,4}

¹Department of Earth Sciences, University of Cambridge, Downing Street, Cambridge CB2 3EQ, U.K.

²Interdisciplinary Research Centre in Superconductivity, Madingley Road, Cambridge, CB3 0HE, U.K.

³Mineralogisch-Petrographisches Institut, Universität Hamburg, Grindelallee 48, D-20146 Hamburg, Germany

⁴SFB 173, Universität Hannover, D-30060 Hanover, Germany

ABSTRACT

We report the direct experimental observation of a structural anomaly near 825 K in synthetic and natural titanite samples by high-temperature, hard-mode infrared spectroscopy. The anomaly in titanite, CaTiSiO_5 , is characterized by a break of the temperature dependence of the 562 cm^{-1} Si-O bending mode, the 675 cm^{-1} Ti-O band, and the 900 cm^{-1} Si-O stretching modes, and the rapid decrease of the IR signal at 873 cm^{-1} . The order parameter, as determined from the temperature evolution of the frequencies of the absorption bands in the middle infrared (MIR) region follows a second-order Landau behavior with an order-parameter exponent $\beta = 1/2$. At $T > 825\text{ K}$, the Ti-O band shows further softening, whereas the Si-O bands at 562 and 900 cm^{-1} show hardening with increasing temperature. In natural samples, the effects of impurities on the high-temperature transition are weak. For pure titanite, the transition temperature, T_c , is about 825 K and increases with increasing impurity concentration.