Toward the crystal structure of nagyagite, [Pb(Pb,Sb)S₂][(Au,Te)]

HERTA EFFENBERGER,[1,*] WERNER H. PAAR,[2] DAN TOPA,[2] FRANZ J. CULETTO,[3] AND GERALD GIESTER[1]

[1]Institut für Mineralogie und Kristallographie, Universität Wien, Althanstrasse 14, A-1090 Vienna, Austria
[2]Institut für Mineralogie, Universität Salzburg, Hellbrunnerstrasse 34, A-5020 Salzburg
[3]Kärntner Elektrizitäts AG, Arnulfplatz 2, A-9021 Klagenfurt, Austria

ABSTRACT

Synthetic nagyagite was grown from a melt as part of a search for materials with high-temperature superconductivity. Electron microprobe analyses of synthetic nagyagite and of nagyagite from the type locality Nagyág, Transylvania (now Săcărîmb, Romania) agree with data from literature. The crystal chemical formula [Pb(Pb,Sb)S₂][(Au,Te)] was derived from crystal structure investigations. Nagyagite is monoclinic pseudotetragonal. The average crystal structure was determined from both synthetic and natural samples and was refined from the synthetic material to $R = 0.045$ for 657 single-crystal X-ray data: space group $P2_1/m$, $a = 4.220(1)$ Å, $b = 4.176(1)$ Å, $c = 15.119(3)$ Å, $\beta = 95.42(3)°$, and $Z = 2$. Nagyagite features a pronounced layer structure: slices of a two slabs thick SnS-archetype with formula Pb(Pb,Sb)S₂ parallel to (001) have a thickness of 9.15 Å. Te and Au form a planar pseudo-square net that is sandwiched between the SnS-archetype layers; it is assumed that planar Au$^{[4Te]}$Te₄ configurations are edge connected to chains and that Te atoms are in a zigzag arrangement. Ordering within the SnS-archetype and gold-tellurium layers, intense twinning and/or stacking variants are responsible for the often observed superstructure reflections. For buckhornite, [(Pb₂Bi)$_{\Sigma 3}$S₃][(AuTe₂)$_{\Sigma 3}$], a structure model is proposed considering a homologous series with nagyagite, [(Pb₃(Pb,Sb)₃)$_{\Sigma 6}$S₆][(Au,Te)₃].