

## **Local Ca-Mg distribution of Mg-rich pyrope-grossular garnets synthesized at different temperatures revealed by $^{29}\text{Si}$ MAS NMR spectroscopy**

**ANNE BOSENICK,<sup>1,\*</sup> CHARLES A. GEIGER,<sup>1</sup> AND BRIAN L. PHILLIPS<sup>2</sup>**

<sup>1</sup>Institut für Geowissenschaften, Christian-Albrechts-Universität zu Kiel, Olshausenstrasse 40, 24098 Kiel, Germany

<sup>2</sup>Department of Chemical Engineering and Materials Science, University of California, Davis, California 95616, U.S.A.

### **ABSTRACT**

Pyrope-grossular solid solutions,  $(\text{Mg,Ca})_3\text{Al}_2\text{Si}_3\text{O}_{12}$ , of composition  $\text{Py}_{85}\text{Gr}_{15}$  and  $\text{Py}_{75}\text{Gr}_{25}$  were synthesized at 1000, 1200, and 1400 °C and 30 kbars in a piston-cylinder device. The synthetic garnets were characterized using optical, microprobe, and X-ray methods and their Ca-Mg distributions were investigated using  $^{29}\text{Si}$  MAS NMR spectroscopy. The syntheses produced 100% garnet except for those undertaken at 1000 °C, where small amounts (up to 3%) of clinopyroxene were present. X-ray powder refinements showed differences up to 0.01 Å in the unit-cell dimension of the garnets synthesized at the three different temperatures. A general decrease of the X-ray diffraction line widths with increasing synthesis temperature is observed. The  $^{29}\text{Si}$  NMR spectra of  $\text{Py}_{85}\text{Gr}_{15}$  show little change as a function of synthesis temperature. In the spectra of  $\text{Py}_{75}\text{Gr}_{25}$  small but measurable changes in the relative peak intensities, depending upon synthesis temperature, were observed with a more random cation distribution corresponding to a higher synthesis temperature. None of the garnets investigated has a completely random Ca-Mg distribution. The reduction in configurational entropy compared to the disordered state is estimated to be less than 2 J/mol·K.